Electrochemical Sensing of Lead in Drinking Water Using MWCNTs and β-Cyclodextrin

Arif Ul Alam,^{1,2} Matiar M. R. Howlader,^{1*} Nan-Xing Hu,² and M. Jamal Deen^{1*}

¹Department of Electrical and Computer Engineering, McMaster University, 1280 Main Street West,

Hamilton, ON, L8S 4K1, Canada

²Advanced Materials Laboratory, Xerox Research Centre of Canada, 2660 Speakman Drive,

Mississauga, ON, L5K 2L1, Canada

KEYWORDS: MWCNT, β -cyclodextrin, electrochemical sensing, heavy metal, lead

ABSTRACT:

Heavy metal pollution is a severe environmental problem affecting many water resources. The nonbiodegradable nature of the heavy metals such as lead (Pb) causes severe human health issues, so their cost-effective, sensitive and rapid detection is needed. In this work, we describe a simple, facile and low cost modifications of multiwalled carbon nanotubes (MWCNT) and β -cyclodextrin (β CD) through non-covalent/physical (Phys) and a covalent Steglich esterification (SE) approaches. The Phys modification approach resulted Pb detection with a limit-of-detection (LoD) of 0.9 ppb, while the SE approach showed an LoD of 2.3 ppb, both of which are well below the WHO Pb concentration guideline of 10 ppb. The MWCNT- β CD (Phys) based electrodes show negligible interference with other common heavy metal ions such as Cd²⁺ and Zn²⁺. The MWCNT- β CD based electrodes were of low-cost owing to their simple synthesis approaches, exhibited good selectivity and reusability. The proposed MWCNT- β CD based electrodes is a promising technology in developing a highly affordable and sensitive electrochemical sensing system of Pb in drinking water. Accessibility to potable water is increasingly challenging in developing and in some developed countries due to contamination of their source waters with heavy metal ion and other pollutants.¹ Heavy metals such as lead (Pb) are non-biodegradable and widely distributed and its presence in drinking water causes greater risks to human health.² The effects of Pb include behavioral disorder and neurodevelopmental problems in children; increased blood pressure and renal dysfunction in adults; and even cancer in kidneys, lung, or brain due to its <u>long-term presence</u> in source and drinking water.^{3–7} According to World Health Organization (WHO) guidelines, the maximum acceptable concentration of Pb in drinking water should be 10 μ g/L or 10 ppb.⁶ However, drinking water authorities such as in Canada are proposing an even stricter limit (e.g., 5 ppb) for Pb in drinking water.⁶ Major challenges in implementing the stricter limit include the lack of on-site monitoring techniques, and detecting contaminant levels across distributed water sources. Therefore, a simple, low-cost and easy to use sensor for the detection of a heavy metal such as Pb is necessary to maintain water safety in resource-limited areas.

Conventional analytical techniques such as inductively coupled plasma mass spectrometry and atomic absorption spectroscopy require qualified testing laboratories and trained personnel.^{8,9} Recently, electrochemical methods have made considerable progress towards simple, on-site and low-cost detection capabilities to allow adequate time for taking safety measures in case of a contamination.¹⁰ The electrochemical sensors, commonly referred to as "electrodes", are ideal candidates as they can be fabricated with low-cost to detect Pb with higher precision and accuracy. The material system of a sensing electrode is the key ingredient in maximizing overall performance of an electrochemical analysis instrument. Specifically, electrode materials based on carbon nanomaterials,¹¹ metal nanoparticles,¹² and a number of selectivity-enhancing polymeric or organic materials^{13–15} have attracted tremendous research interest for their collective attributes such as high effective surface area, enhanced electron transfer, ability to be miniaturized, and improved selectivity. More notably, nanomaterials based electrodes made up of easily available electrode materials by a facile and scalable

synthesis method can be exploited to fabricate low cost electrodes for the analysis of multiple environmental targets such as heavy metals such as lead and pharmaceutical contaminants such as acetaminophen and estrogen in drinking water.^{16,17} The ability to detect multiple environmental targets at low cost and in an easy to use manner requires careful selection of sensing materials to provide high sensitivity and selectivity, development of simple modification approaches and user-friendly analysis steps.

Multiwalled Carbon nanotubes (MWCNTs) are excellent electrode material to realize simple, low cost and easy-to-use electrochemical sensors because of their wide electrical potential window, fast electron transfer rate and large surface area.¹⁸ Unmodified MWCNTs in the form of tower, array, and thread structures were used as an electrode material. These unmodified MWCNTs provided considerable simplicity in electrode fabrication compared to that of modified MWCNTs.¹⁹ However, MWCNTs do not disperse well in most common organic and inorganic solvents due to the high Van der Waals force between them that lead to aggregation and bundling.¹⁰ Therefore, non-covalent modification of MWCNTs through π - π conjugation between MWCNTs surface and the organic modifiers such dodecylbenzene sulfonate and Nafion showed better sensing performances.¹¹ However, non-covalent modifications cannot significantly improve the sensitivity and selectivity of the electrodes since individual nanotubes becomes less interconnected, thus facilitating fewer electron transfer.¹¹ MWCNTs have also been covalently modified by functionalization with amino groups (-NH₂), thiol groups (-SH), amino acids (-NH³⁺ and -COOH), and Bismuth (Bi) which improved the selectivity and limit of detection.¹¹ But then the covalent modification approaches require tedious chemical reaction procedures and thus increase fabrication complexity.

Recently, non-covalent modifications of MWCNTs with β -cyclodextrin (β CD) molecule have shown enhanced sensing performance due to improved dispersion of MWCNTs in the presence of β CD.^{20,21} The improved sensing performance was due to the inclusion complex formation property of β CD towards the detection of emerging pharmaceutical contaminants such as acetaminophen and estrogen in drinking water.^{20,21} Remarkably, β CD have also shown selective formation of inclusion complexes with Pb ions (Pb²⁺) which can be exploited for the detection Pb²⁺.¹⁵ β CD functionalized gold nanoparticles have also shown selective detection of Pb²⁺.¹⁴ Therefore, in this work, we show that the enhanced electrochemical properties of MWCNTs can be combined with the inclusion capability of β CD through their non-covalent and covalent conjugation towards the sensitive detection of Pb²⁺. We demonstrate that the non-covalently modified MWCNT- β CD shows the best Pb²⁺ sensing performance with at least four times reusability. On the other hand, the covalently modified MWCNT- β CD shows moderate Pb²⁺ sensing performance with at least ten times reusability. Thus, the type of conjugation between MWCNTs and β CD, that is, non-covalently and covalently modified MWCNT- β CD, significantly controls the sensing performance of the electrodes.



Scheme 1: Schematic diagram of the MWCNT-βCD (Phys/SE)/SPE electrode fabrication processes.

The non-covalent modification of MWCNTs and β CD was done by physically mixing them in **D**e-Ionized Water (DIW). Twenty milligram of MWCNTs (purchased from U.S. Research Nanomaterials Inc., outer diameter (OD): 5–15 nm, length: ~50 µm, and purity: \geq 95 wt%) was dispersed by using an ultrasonic preprocessor in 10 ml of β CD solution (2 wt%) in DIW to give a 2 mg mL⁻¹ stable black suspension (Scheme 1). The resulting suspension will be termed as MWCNT- β CD (Phys) since the modification process is based on physical mixing of MWCNTs and β CD. An aliquot of 10 µL of 2 mg mL⁻¹ MWCNT- β CD (Phys) solution was drop-casted on a commercial Screen Printed Electrode (SPE) (Zensor, purchased from CH Instruments, with Carbon working and counter electrode, and Ag/AgCl reference electrode). The drop-casted MWCNT- β CD (Phys) solution was dried in air for 20 min at 80 °C in an oven resulting in MWCNT- β CD (Phys)/SPE electrode (Scheme 1).

The covalent modification of MWCNTs and β CD was accomplished by a simple, one-step chemical reaction based on Steglich esterification (SE) principle.¹⁷ Briefly, MWCNT-COOH (purchased from U.S. Research Nanomaterials Inc., OD: 5–15 nm, length: ~50 μ m, and purity: \geq 95 wt%) was first dispersed in anhydrous N,N-dimethylformamide (DMF) into a reactor with Ar environment. The mixture in the reactor was then sonicated to get a uniform suspension. After that 4-(dimethylamino)pyridine (DMAP) and β CD and dicyclohexylcarbodiimide (DCC) were added into the reaction mixture at 0 °C. The resulting suspension was stirred for several hours at 20 °C to precipitate MWCNT-BCD (SE)), also termed as SE modified MWCNTs and BCD. The MWCNT-BCD (SE) was then filtered and washed repeatedly to remove the DCC, DMAP, and unreacted β CD. The SE process couples MWCNT-COOH and β CD through ester bonds resulting in the chemically or covalently modified MWCNTs with β CD. A uniform, black suspension of the covalently modified MWCNT- β CD (SE) was prepared by dispersing 40 mg of the black MWCNT-βCD (SE) powder into 20 mL of DIW using an ultrasonic preprocessor. Finally, an aliquot of 10μ L 2 mg ml⁻¹ MWCNT- β CD (SE) solution was drop-casted on SPE and then dried in air for 20 min at 80 °C in an oven resulting in MWCNT-βCD (SE)/SPE electrode (Scheme 1). For comparison, an SPE electrode was also modified by drop casting only MWCNT (i.e., 2mg/mL MWCNT dispersed in DIW using ultrasonic preprocessor) and dried to get MWCNT/SPE.



Figure 1: DPASV of MWCNT/SPE (blue smaller dashed curve), MWCNT- β CD (SE)/SPE (green larger dashed curve), and MWCNT- β CD (Phys)/SPE (black solid curve) recorded in 0.1 M acetate buffer (pH 5) in the presence of 1 μ M (207 ppb) Pb²⁺ ion.

The Pb²⁺ ion sensing was done by Differential Pulse Anodic Stripping Voltammetry (DPASV) method. The test solutions with different Pb²⁺ ion concentrations were made by dissolving appropriate amount of Pb(NO₃)₂ salt in 0.1 M acetate buffer (pH 5). A miniature USB powered potentiostat (EmStat3 from PalmSens) with PSTrace 5.5 data analyzer software was used in the electrochemical measurements. At the beginning of the electrochemical measurement, a deposition potential of -0.8 V was applied at the working electrode for 600 s under magnetic stirring (250 rpm) in 50 mL solution to reduce Pb²⁺ ions to Pb⁰. The electrodeposited Pb atoms were then stripped from the working electrodes by anodically sweeping the electrode potential from -0.8 to -0.2 V. The optimized DPASV parameters were 4 mV, 50 mV, 50 ms and 40 mV/s for step potential, pulse amplitude, pulse time and scan rate, respectively. The peak currents were measured with respect to linear base line of the current vs. potential curve.

There are two major approaches to improve the performance of an electrochemical sensor. First, the effective surface area of the working electrode plays a key role in achieving high sensitivity. The effective surface area of the MWCNT- β CD (Phys)/SPE and MWCNT- β CD (SE)/SPE is higher compared to that of MWCNT/SPE.¹⁷ Second, the target-capturing ability of the sensing material system can improve its selectivity and dynamic range. A comparison of the sensing performance of the prepared MWCNT- β CD (Phys)/SPE and MWCNT- β CD (SE)/SPE with that of MWCNT/SPE in the presence of 1 μ M (207 ppb) Pb²⁺ is shown in Figure 1. The peak current for MWCNT/SPE was 15.1 μ A. The MWCNT- β CD (SE)/SPE showed increased current peak of 19.3 μ A, whereas the MWCNT- β CD (Phys)/SPE showed the highest peak current of 24.4 μ A. The peak potential of MWCNT- β CD (Phys)/SPE was slightly shifted towards more positive direction and this could be due to modification in the oxidation potential in the presence of β CD.

The enhanced electrochemical sensing of Pb²⁺ ion with MWCNT-βCD (Phys)/SPE can be attributed to higher amount of Pb⁰ deposition during application of the deposition potential or -0.8 V. To confirm this phenomenon, we performed Scanning Electron Microscopy (SEM) observations of the three different electrodes (MWCNT/SPE, MWCNT-βCD (SE)/SPE and MWCNT-βCD (Phys)/SPE) taken out of the electrochemical cell just after the deposition step. These electrodes were used since performing the stripping step will cause anodization induced-stripping of the Pb⁰. Figure 2 shows the corresponding SEM images of the modified electrodes with low (on top, x200) and high (on bottom, x1000) magnifications. The SEM images were taken using a JEOL 7100F SEM microscope with an acceleration voltage of 15 kV and working distance of 6 mm. Figure 2(a) shows that the MWCNT/SPE has dendritic structures of the electrodeposited Pb⁰. On the other hand, as shown in Figure 2(b), the MWCNT-βCD (SE)/SPE surface has island structures of the electrodeposited Pb⁰, which covers more surface area to that of MWCNT/SPE. However, as shown in Figure 2(c), the MWCNT-βCD (Phys)/SPE surface is covered with leaf-life structure of the accumulated Pb⁰. All the low and high magnification SEM images are scaled equally. Therefore, Figure 2 shows that the MWCNT-βCD (Phys)/SPE has the highest amount of surface coverage by the electrodeposited Pb^0 . The highest surface coverage of Pb^0 resulted in the largest peak current due to anodic oxidation stripping from the MWCNT- β CD (Phys)/SPE electrode (Figure 1).



Figure 2: SEM images of the (a) MWCNT/SPE, (b) MWCNT- β CD (SE)/SPE, and (c) MWCNT- β CD (Phys)/SPE with low (upper images) and high (lower images) magnifications after electrodeposition steps (at -0.8 V) of the corresponding electrodes in the presence of 1 μ M (207 ppb) Pb²⁺ ion.

The difference in the surface coverage by Pb in the three types of electrodes could be related to the amount of β CD present with the MWCNTs. We demonstrated before that the amount of β CD is highest in MWCNT- β C (Phys) compared to that of MWCNT- β CD (SE).¹⁷ In fact, there are 1:2 weight ratio of β CD:MWCNTs present in the MWCNT- β CD (Phys) suspension through physical/non-covalent mixing. On the contrary, MWCNT- β C (SE) has much smaller amount of β CD since the chemical attachment of β CD with MWCNT (i.e., the Steglich esterification) depends on the amount of –COOH groups present in the precursor MWCNT-COOH material. It was found that MWCNT- β C (SE) has only ~1:10 weight ratio of β CD:MWCNTs.¹⁷ Thus, it is confirmed that MWCNT- β C (Phys)/SPE

electrode has the highest amount of β CD which are physically/non-covalently attached with MWCNTs. Hence, the increased amount of β CD in MWCNT- β CD (Phys)/SPE facilitated improved electrochemical sensing of Pb²⁺.

The improved electrochemical sensing performance of MWCNT-BCD (Phys)/SPE compared to that of MWCNT/SPE and MWCNT-BCD (SE)/SPE could also be attributed to the formation of the inclusion complexes between β CD and Pb²⁺. The β CD molecule has a porous structure with an average diameter of 18–20 nm which is capable to form host-guest interaction based inclusion complexes with other molecules. A number of researches had investigated its host-guest interaction properties with phenolic organic molecules and steroid hormones.^{16,17} These organic molecules and hormones are attracted to the hydrophobic inner core of the BCD molecule and facilitates redox-based electrochemical sensing of the guest molecules. The β CD also showed affinity towards metal ions. For example, BCD functionalized gold-iron nanoparticles was used for selective and sensitive colorimetric sensing of Cr⁶⁺ ion. In another study,²² carboxymethyl-β-cyclodextrin polymer modified Fe₃O₄ nanoparticles (CDpoly-MNPs) were utilized for selective removal of Pb²⁺, Cd²⁺, and Ni²⁺ ions from water. The CDpoly-MNPs showed preferential adsorption towards Pb²⁺ ions with an affinity order of $Pb^{2+} \gg Cd^{2+} \gg Ni^{2+}$. Moreover, βCD functionalized gold nanoparticles were used for the selective detection of Pb²⁺ ions from aqueous solution. The electrochemical evidence of the interaction between the Pb^{2+} ions and the βCD was also described where the formation constants of surface inclusion complexes between Pb²⁺ and β CD were electrochemically measured (727.5±20.2 M⁻¹) using a carbon paste electrode.^{15,23} Therefore, in this study, the inclusion complex formation of β CD has been combined with the superior electrochemical properties of MWCNTs towards sensing of Pb^{2+} ion.

The linear detection range of MWCNT- β CD (Phys)/SPE electrode for the detection of Pb2+ ion was measured to determine its feasibility for use in drinking water monitoring. Figure 3 shows the DPASV curves and the corresponding linear calibration curve in the presence of 0.015–20 μ M (3.1–103.3 ppb) Pb²⁺ ion. The optimized DPASV conditions used in these measurements are similar to that of Figure 1.

Figure 3(a) shows that the current peak for lowest Pb²⁺ ion concentration is located at -0.6 V. The peak current slightly shift towards more anodic value with the increased concentration of Pb²⁺ ion. This peak shifting could be due to diffusional control reaction influenced by concentration difference.²⁴ Figure 3(b) shows the calibration curves for the concentration ranges of 0.015–20 μ M (3.1-103.3 ppb). The error bars for each data point was calculated by taking six measurements using newly prepared sensors each time and by multiplying Student's *t*-distribution *k* value of 2.57 to get 95% confidence interval. The linear regression equations can be expressed as $I_p = 0.098 C + 0.0266$, where I_p is the peak current (in μ A) and *C* is the Pb²⁺ concentration (in ppb).



Figure 3: (a) DPASV of MWCNT- β CD (Phys)/SPE in 0.1 M acetate buffer (pH 5) in the presence of 0.025–20 μ M (3.1–103.3 ppb) Pb²⁺. (b) Calibration curve (i.e., peak current vs Pb²⁺ concentration) for MWCNT- β CD (Phys)/SPE. All experiments were done with a deposition potential of –0.8 V for 600 s under magnetic stirring before measurements.

The sensitivity of the MWCNT- β CD (Phys)/SPE electrode is 98 nA/ppb. The limit of detection (LoD), defined as LoD = 3s/m (where, *s* is the standard deviation of the blank solution (0.03 μ A), and *m* is the slope of the calibration curve), was estimated to be 0.9 ppb. Therefore, the linear range and the

LoD value of the MWCNT- β CD (Phys)/SPE sensor to detect lead concentration in drinking water are much better than those specified by the WHO guideline. The LoD value is compared with other recent reports for the detection of Pb²⁺ using electrodes based on MWCNTs, as shown in Table S1.^{25–30} It is observed that the MWCNT- β CD (Phys)/SPE sensor has comparable linear range and one of the lowest limit of detection (LoD) for the detection of Pb²⁺. For comparison, the linear range and calibration curves of MWCNT- β CD (SE)/SPE electrode was also measured and are shown in Figure S1. The MWCNT- β CD (SE)/SPE electrode showed a linear detection range of 6.2 – 103.5 ppb with an LoD of 2.3 ppb. Thus, the sensitivity of the MWCNT- β CD (SE)/SPE electrode is 38.6 nA/ppb, which is ~2.5 times lower than that of MWCNT- β CD (Phys)/SPE. However, the MWCNT- β CD (SE)/SPE electrode showed better performance in terms of stability.

The stability of the MWCNT- β CD (Phys)/SPE and MWCNT- β CD (SE)/SPE electrodes were investigated to examine their repeatability and reusability. The two types of electrode were repeatedly reused in similar and different concentrations of Pb²⁺ solutions. Before reusing the electrodes, they were electrochemically cleaned/regenerated by applying 0.31 V under magnetic stirring in a blank solution for 300 s to desorb the Pb molecules from the electrode surface, as shown in Figure S2. The cleaning procedure was found to be more effective and faster when magnetic stirring was used, as shown in Figure S2(a) and S2(b). Figure S2(c) shows the DPASV response of a newly prepared MWCNT- β CD (Phys)/SPE electrode with 207 ppb of Pb²⁺ (curve (1)), which was then electrochemically cleaned to give a DPASV curve in blank solution with no peak current (curve (2)), signifying successful regeneration of the electrode. After that, the same electrode was used to DPASV measurement of 5.2 ppb of Pb²⁺ with peak current of 0.4 μ A (curve (3)), which is within the error bar range of the calibration line of MWCNT- β CD (Phys)/SPE. However, the MWCNT- β CD (Phys)/SPE electrode showed stable sensing performance when reused/regenerated for four consecutive measurements of 207 ppb of Pb²⁺ solutions.

12

On the other hand, the MWCNT-βCD (Phys)/SPE electrode performed at least six consecutive reuse/regeneration cycles with negligible degradation in sensing performance when low concentrations of Pb²⁺ solution (in the range of 5–20 ppb) were used. Therefore, the MWCNT-βCD (Phys)/SPE electrode tends to degrade faster when measuring higher concentration of Pb²⁺. This could be due to dissolution of βCD molecule from the electrode surface when increased amounts of Pb⁰ molecules adsorb which ultimately leads to delamination and disintegration of the MWCNTs network during the electrode regeneration step. In contrast, the MWCNT-βCD (SE)/SPE electrode showed reusability for at least 10 reuse/regeneration cycles at both low and high concentrations of Pb²⁺. The better reusability of the MWCNT-βCD (SE)/SPE electrode can be attributed to the chemical/covalent attachment of βCD with MWCNTs which is stronger than that of the MWCNT-βCD (Phys) that provides better electrode surface adhesion during cleaning/regeneration steps. Consequently, the MWCNT-βCD (SE)/SPE can provide better reusability when measuring higher levels of Pb²⁺, and the MWCNT-βCD (Phys)/SPE can offer better sensitivity as well as reusability when lower levels of Pb²⁺ is measured.

The MWCNT- β CD (Phys)/SPE and MWCNT- β CD (SE)/SPE electrodes are low cost and can be used utilized in resource limited areas. The low cost of fabrication of these electrodes is due to the simple MWCNTs modification processes (covalent/non-covalent), use of simple equipment and lowcost commercial carbon SPE electrodes. Furthermore, apart from the electrochemical cleaning/regeneration procedure described above, the SPE electrode can also be reused by simply wiping off the MWCNT- β CD from its surface using Kim Wipes and cleaning with solvents like isopropyl alcohol followed by drop-casting another aliquot of 10 μ L of MWCNT- β CD solution. The SPE electrode showed negligible degradation in sensing performance over at least 50 cycles of cleaning and remaking of the electrodes.

The reusability of the SPE electrode provides further economic benefits to reduce the overall cost to run a single experiment. Table S2 shows the breakdown of materials cost (in US\$) to fabricate a new MWCNT-βCD (Phys)/SPE or MWCNT-βCD (SE)/SPE electrode and to run a single experiment to

highlight the cost-effectiveness of the proposed Pb^{2+} sensor. Table S2 shows that the materials cost a 10 µL drop of MWCNT- β CD (Phys/SE) required to fabricate a single sensor is only \$0.0026 which is only 0.21% compared to the price of a single SPE (\$1.25). Additionally, the prices included on Table S2 can be reduced more since it lists the retail prices. Also, if a MWCNT- β CD (Phys/SE)/SPE sensor is cleaned/regenerated for 10 times, then the cost of each measurement will be much smaller. Therefore, the MWCNT- β CD (Phys/SE)/SPE electrode can be fabricated with extremely low cost. The fabrication costs can be further reduced by fabricating the SPE electrode also instead of using the commercial one.



Figure 4: DPASV of MWCNT- β CD (Phys)/SPE with 5.2 ppb and 103.5 ppb of Pb²⁺ in the presence of 207 ppb of Zn²⁺ and Cd²⁺ in 0.1 M acetate buffer (pH = 5).

An important performance parameter of an electrochemical heavy metal sensor is its selectivity in the presence of other interfering ions in the solution. The selectivity of the MWCNT- β CD (Phys)/SPE electrode with 103.5 ppb of Pb²⁺ was measured in the presence of 207 ppb of Cadmium (Cd²⁺) and Zinc (Zn²⁺) ions (Figure 4). The Cd²⁺ peak was clearly separated from the Pb²⁺ peak. Also, the Pb²⁺

peak showed negligible change in the peak current. However, the Zn^{2+} peak was not observed since the oxidation potential of Zn^{2+} is lower than -1.2 V and the deposition potential (-0.8 V) did not cause any deposition of Zn^{0} molecule on the electrode surface. The peak current for 207 ppb of Cd²⁺ was very small compared to that of Pb²⁺. Therefore, the MWCNT- β CD (Phys)/SPE electrode showed more selectivity towards Pb²⁺ ion.

In this research work, we developed low-cost and easy-to-use electrochemical sensors for the determination of Pb²⁺ using non-covalent/physical and a one-step covalent modifications (Steglich esterification) of MWCNT with β CD. The modified MWCNT- β CD electrodes demonstrated excellent sensing performance for the detection of Pb²⁺ with limits-of-detection of 0.9 and 2.3 ppb for the non-covalent/physical and covalent modifications, respectively. The physically modified MWCNT- β CD based electrode exhibited the highest sensitivity compared to that of MWCNT and covalently modified MWCNT- β CD. The electrodes fabrications and materials were of extremely low cost which was calculated to be only \$2.64 per 1000 MWCNT- β CD modifications. The final cost of each measurement could be further reduced because of the reusability of the MWCNT- β CD based electrodes for at least four times. The sensors also showed good selectivity in the presence of other interfering heavy metal ions such as Zn²⁺ and Cd²⁺ with very high concentrations. The developed sensor may be used in low-cost and point-of-care sensing systems for drinking water quality monitoring.

AUTHOR INFORMATION

Corresponding Author

*Email: jamal@mcmaster.ca, mrhowlader@ece.mcmaster.ca

Author Contributions

The manuscript was written through contributions of all authors. All authors have given approval to the final version of the manuscript.

Notes

The authors declare no competing financial interest.

ACKNOWLEDGEMENTS

The authors acknowledge the valuable feedback and suggestions given by the research group members of Dr. M Jamal Deen during the research and writing of the manuscript. This research is supported by Discovery Grants from the Natural Science and Engineering Research Council of Canada, an infrastructure grant from the Canada Foundation for Innovation, an Ontario Research Fund for Research Excellence Funding Grant, a FedDev of Southern Ontario grant, the Canada Research Chair program, NSERC RES'EAU strategic network and the NCE IC-IMPACTS.

REFERENCES

- Gobal Water Crisis: The Facts http://inweh.unu.edu/wp-content/uploads/2017/11/Global-Water-Crisis-The-Facts.pdf (accessed Nov 5, 2018).
- (2) Adverse Health Effects of Heavy Metals in Children http://www.who.int/ceh/capacity/heavy_metals.pdf (accessed Nov 5, 2018).
- (3) Goyer, R. A. Lead Toxicity: Current Concerns. *Environ. Health Perspect.* 1993, 100, 177–187.
- (4) Canfield, R. L.; Henderson, C. R.; Cory-Slechta, D. A.; Cox, C.; Jusko, T. A.; Lanphear, B. P. Intellectual Impairment in Children with Blood Lead Concentrations below 10 Mg per Deciliter. *N. Engl. J. Med.* 2003, *348* (16), 1517–1526.
- Lanphear, B. P.; Dietrich, K.; Auinger, P.; Cox, C. Cognitive Deficits Associated with Blood Lead Concentrations <10 Microg/DL in US Children and Adolescents. *Public Health Rep. 115* (6), 521–529.
- (6) Lead in Drinking Water https://www.canada.ca/en/health-canada/programs/consultation-leaddrinking-water/document.html (accessed Nov 5, 2018).
- (7) Childhood Lead Poisoning http://www.who.int/ceh/publications/leadguidance.pdf (accessed Nov 5, 2018).
- (8) Jenner, G. A.; Longerich, H. P.; Jackson, S. E.; Fryer, B. J. ICP-MS A Powerful Tool for High-Precision Trace-Element Analysis in Earth Sciences: Evidence from Analysis of Selected U.S.G.S. Reference Samples. *Chem. Geol.* **1990**, *83* (1–2), 133–148.
- Smith, J. C.; Butrimovitz, G. P.; Purdy, W. C. Direct Measurement of Zinc in Plasma by Atomic Absorption Spectroscopy. *Clin. Chem.* 1979, 25 (8), 1487–1491.

- (10) Aragay, G.; Pons, J.; Merkoçi, A. Recent Trends in Macro-, Micro-, and Nanomaterial-Based
 Tools and Strategies for Heavy-Metal Detection. *Chem. Rev.* 2011, *111* (5), 3433–3458.
- Wang, T.; Yue, W. Carbon Nanotubes Heavy Metal Detection with Stripping Voltammetry: A Review Paper. *Electroanalysis* 2017, 29 (10), 2178–2189.
- (12) Podešva, P.; Gablech, I.; Neužil, P. Nanostructured Gold Microelectrode Array for Ultrasensitive Detection of Heavy Metal Contamination. *Anal. Chem.* 2018, 90 (2), 1161–1167.
- (13) Lu, muxin; Deng, Y.; Luo, Y.; Lv, J.; Li, T.; Xu, J.; Chen, S.-W.; Wang, J. Graphene Aerogel–Metal-Organic Framework-Based Electrochemical Method for Simultaneous Detection of Multiple Heavy Metal Ions. *Anal. Chem.* **2018**, acs.analchem.8b03764.
- (14) Aswathy, B.; Avadhani, G. S.; Suji, S.; Sony, G. Synthesis of β-Cyclodextrin Functionalized Gold Nanoparticles for the Selective Detection of Pb 2+ Ions from Aqueous Solution. *Front. Mater. Sci.* 2012, 6 (2), 168–175.
- (15) Roa-Morales, G.; Galicia, L.; Rojas-Hernández, A.; Ramírez-Silva, M. T. Electrochemical Study on the Selective Formation of [Pb(Cyclodextrin)2+]Surfaceinclusion Complexes at the Carbon Paste Electrode/ClO4-1 M Interphase. *Electrochim. Acta* 2005, *50* (9), 1925–1930.
- (16) Alam, A. U.; Qin, Y.; Howlader, M. M. R.; Hu, N.-X.; Deen, M. J. Electrochemical Sensing of Acetaminophen Using Multi-Walled Carbon Nanotube and β-Cyclodextrin. *Sensors Actuators B Chem.* 2018, 254, 896–909.
- (17) Alam, A. U.; Qin, Y.; Catalano, M.; Wang, L.; Kim, M. J.; Howlader, M. M. R.; Hu, N. X.; Deen, M. J. Tailoring MWCNTs and β-Cyclodextrin for Sensitive Detection of Acetaminophen and Estrogen. ACS Appl. Mater. Interfaces 2018, 10 (25), 21411–21427.
- (18) Schroeder, V.; Savagatrup, S.; He, M.; Lin, S.; Swager, T. M. Carbon Nanotube Chemical

Sensors. Chem. Rev. 2018, acs.chemrev.8b00340.

- (19) Zhao, D.; Guo, X.; Wang, T.; Alvarez, N.; Shanov, V. N.; Heineman, W. R. Simultaneous Detection of Heavy Metals by Anodic Stripping Voltammetry Using Carbon Nanotube Thread. *Electroanalysis* 2014, 26 (3), 488–496.
- Wang, S.; Shang, J.; Wang, Q.; Zhang, W.; Wu, X.; Chen, J.; Zhang, W.; Qiu, S.; Wang, Y.;
 Wang, X. Enhanced Electrochemical Performance by Strongly Anchoring Highly Crystalline
 Polyaniline on Multiwalled Carbon Nanotubes. ACS Appl. Mater. Interfaces 2017, 9 (50),
 43939–43949.
- (21) Rajavel, K.; Lalitha, M.; Radhakrishnan, J. K.; Senthilkumar, L.; Rajendra Kumar, R. T. Multiwalled Carbon Nanotube Oxygen Sensor: Enhanced Oxygen Sensitivity at Room Temperature and Mechanism of Sensing. ACS Appl. Mater. Interfaces 2015, 7 (43), 23857–23865.
- (22) Badruddoza, A. Z. M.; Shawon, Z. B. Z.; Tay, W. J. D.; Hidajat, K.; Uddin, M. S. Fe 3O
 4/Cyclodextrin Polymer Nanocomposites for Selective Heavy Metals Removal from Industrial Wastewater. *Carbohydr. Polym.* 2013, 91 (1), 322–332.
- (23) Szejtli, J. Introduction and General Overview of Cyclodextrin Chemistry. *Chem. Rev.* 1998, 98
 (5), 1743–1754.
- (24) Dai, Y.; Liu, C. C. A Simple, Cost-Effective Sensor for Detecting Lead Ions Inwater Using under-Potential Deposited Bismuth Sub-Layer with Differential Pulse Voltammetry (DPV). *Sensors (Switzerland)* 2017, 17 (5).
- (25) Chamjangali, M. A.; Kouhestani, H.; Masdarolomoor, F.; Daneshinejad, H. A Voltammetric Sensor Based on the Glassy Carbon Electrode Modified with Multi-Walled Carbon

Nanotube/Poly(Pyrocatechol Violet)/Bismuth Film for Determination of Cadmium and Lead as Environmental Pollutants. *Sensors Actuators B Chem.* **2015**, *216*, 384–393.

- (26) Cerovac, S.; Guzsvány, V.; Kónya, Z.; Ashrafi, A. M.; Švancara, I.; Rončević, S.; Kukovecz, Á.; Dalmacija, B.; Vytřas, K. Trace Level Voltammetric Determination of Lead and Cadmium in Sediment Pore Water by a Bismuth-Oxychloride Particle-Multiwalled Carbon Nanotube Composite Modified Glassy Carbon Electrode. *Talanta* **2015**, *134*, 640–649.
- (27) Li, X.; Zhou, H.; Fu, C.; Wang, F.; Ding, Y.; Kuang, Y. A Novel Design of Engineered Multi-Walled Carbon Nanotubes Material and Its Improved Performance in Simultaneous Detection of Cd(II) and Pb(II) by Square Wave Anodic Stripping Voltammetry. *Sensors Actuators B Chem.* 2016, 236, 144–152.
- (28) Zhang, B.; Chen, J.; Zhu, H.; Yang, T.; Zou, M.; Zhang, M.; Du, M. Facile and Green Fabrication of Size-Controlled AuNPs/CNFs Hybrids for the Highly Sensitive Simultaneous Detection of Heavy Metal Ions. *Electrochim. Acta* 2016, *196*, 422–430.
- (29) Zhao, D.; Siebold, D.; Alvarez, N. T.; Shanov, V. N.; Heineman, W. R. Carbon Nanotube Thread Electrochemical Cell: Detection of Heavy Metals. *Anal. Chem.* 2017, *89* (18), 9654– 9663.
- (30) Sebastian, M.; Mathew, B. Ion Imprinting Approach for the Fabrication of an Electrochemical Sensor and Sorbent for Lead Ions in Real Samples Using Modified Multiwalled Carbon Nanotubes. J. Mater. Sci. 2018, 53 (5), 3557–3572.

 TABLE OF CONTENT GRAPHIC (Width and Length Ratio: 3.6 × 8.4)
 Participation



Supporting Information:



Figure S1: (a) DPASV of MWCNT- β CD (SE)/SPE in 0.1 M acetate buffer (pH 5) in the presence of 0.025–20 μ M (6.2–103.3 ppb) Pb²⁺. (b) Calibration curve (i.e., peak current vs Pb²⁺ concentration) for MWCNT- β CD (Phys)/SPE. All of the experiments were done with a deposition potential of –0.8 V for 600 s under magnetic stirring before measurements.



Figure S2: Electrochemical process of electrode surface cleaning/regeneration by applying a +0.31 V under magnetic stirring for 300 s. The resulting current response of the electrodes are shown with logarithmic (a) and (b) general numbers with respect to elapsed time. (c) The DPASV curves for new sensor (1), cleaned sensor (2) and reused sensor (3) for the detection of 207 ppb, blank and 5.2 ppb of Pb^{2+} .

Electrode	Modifications	Linear Range	Detection Limit	Comments	Year ^{Ref.}
MWCNT-GC	Poly(PCV)/Bi	1-200 ppb	0.4 ppb	MWCNT modified with poly(PCV) and Bi film	2015 ²⁵
MWCNT-GC	BiOCl/Nafion	5-50 ppb	0.57 ppb	bismuth- oxychloride particle- MWCNT composite	2015 ²⁶
MWCNTs/Bi- GC	-SH, -NH2, -COO- , -OH	2-50 ppb	0.3 ppb	N-doping and thiol- modification of MWCNT	2016 ²⁷
AuNPs-CNFs- GCE	Isopropanol/Nafion	20.7-207.2 ppb	20.7 ppb	AuNPs/CNFs fabricated via electrospinning and in situ thermal reduction	2016 ²⁸
CNT Thread	None	207-1035 ppb	0.12 ppb	electrochemical cell fabricated by CNT thread	2017 ²⁹
MWCNT- IIP/Pt	Ion Imprinted polymer	1-5 ppm	0.02 ppb	binding sites for lead ions sculpted with lead ion as template and NNMBA- crosslinked polyacrylamide as the solid matrix on MWCNTs	2018 ³⁰
MWCNT-βCD	Physical, Steglich esterification	3.1-103.3 ppb	0.9 ppb	Physically and Steglich esterification modified MWCNT and βCD	This work

Table S1: Comparison of the MWCNTs-based electrochemical sensors for Pb²⁺

Name of	Unit Price	Price	Price (for one sensor)	Price for one
Materials		(each)		experiment
MWCNTs	\$125/25gm	\$.005	$0.02 \text{ mg} \times \$0.005 = \0.0001	
		(each mg)	[10 μ L solution with 2 mg/mL	
			concentration of MWCNT]	
βCD	\$220/100gm	\$0.0022	$0.02 \text{mg} \times \$0.0022 =$	
		(each mg)	\$0.00044	
			[10 µL solution with 2 mg/mL	
			concentration of β CD]	
SPE	\$50/40	\$1.25	\$1.25 (each)	
	pieces	(each)		
MWCNT-βCD			\$2.64×10 ⁻³	\$2.64×10 ⁻⁴
				[for reusing 10
			Cost of one drop of MWCNT-βCD	times]
			with respect to one SPE	
			= \$2.64×10 ⁻³ / \$1.25	
			= 0.21%	
MWCNT-βCD			1.25+0.0001+0.00044 =	\$0.0250108
/SPE			\$1.25054	[for 50
				measurements]

Table S2: Breakdown of materials cost to fabricate a single MWCNT- β CD (Phys/SE)/SPE electrode