

Intrinsic and extrinsic x-ray absorption effects in soft x-ray diffraction from the superstructure in magnetite

C. F. Chang,¹ J. Schlappa,¹ M. Buchholz,¹ A. Tanaka,² E. Schierle,³ D. Schmitz,³ H. Ott,¹ R. Sutarto,¹ T. Willers,¹ P. Metcalf,⁴ L. H. Tjeng,^{1,5} and C. Schüßler-Langeheine¹

¹*II. Physikalisches Institut, Universität zu Köln, Zùlpicher Str. 77, 50937 Köln, Germany*

²*Department of Quantum Matter, ADSM, Hiroshima University, Higashi-Hiroshima 739-8530, Japan*

³*Helmholtz-Zentrum Berlin, Albert-Einstein-Str. 15, 12489 Berlin, Germany*

⁴*Department of Chemistry, Purdue University, West Lafayette, Indiana 47907, USA*

⁵*Max Planck Institute for Chemical Physics of Solids, Nöthnitzerstr. 40, 01187 Dresden, Germany*

(Dated: October 26, 2018)

We studied the $(00\frac{1}{2})$ diffraction peak in the low-temperature phase of magnetite (Fe_3O_4) using resonant soft x-ray diffraction (RSXD) at the Fe- $L_{2,3}$ and O- K resonance. We studied both molecular-beam-epitaxy (MBE) grown thin films and *in-situ* cleaved single crystals. From the comparison we have been able to determine quantitatively the contribution of intrinsic absorption effects, thereby arriving at a consistent result for the $(00\frac{1}{2})$ diffraction peak spectrum. Our data also allow for the identification of extrinsic effects, e.g. for a detailed modeling of the spectra in case a "dead" surface layer is present that is only absorbing photons but does not contribute to the scattering signal.

PACS numbers: 71.30.+h, 61.05.cp

Magnetite, Fe_3O_4 , shows a first order anomaly in the temperature dependence of the electrical conductivity at $T_V \sim 120$ K, the famous Verwey transition.¹ It is accompanied by a structural phase transition from the cubic inverse spinel to a distorted structure. One usually connects this transition with charge ordering of the Fe^{2+} and Fe^{3+} ions on the octahedrally coordinated, so-called B-sites. In a recent diffraction study, Wright, Attfield and Radaelli found long-range charge order from the pattern of shorter and longer bond lengths between B-site iron and oxygen ions below T_V .^{2,3} Subsequently, using this structure as input, local density approximation + Hubbard U (LDA+ U) band structure studies have calculated the corresponding orbital ordering, which involves mainly the minority spin electron in the t_{2g} state of the 2+ B-sites.^{4,5}

Recently this t_{2g} orbital order has been studied using RSXD at the O $1s \rightarrow 2p$ (K)⁶ and Fe $2p \rightarrow 3d$ ($L_{2,3}$)⁷ resonance. The O- K edge resonance enhancement of the $(00\frac{1}{2})$ diffraction peak (notation refers to the cubic room-temperature unit cell) on an *ex-situ* polished bulk single crystal was interpreted by Huang *et al.* as a signature of a particular charge/orbital order at the oxygen-sites.⁶ At the Fe $L_{2,3}$ -edges, using MBE-grown thin films, the $(00\frac{1}{2})$ maximum energy coincides with the resonance of the 2+ B-site ions and was assigned by Schlappa *et al.* to Fe t_{2g} -orbital order on these sites.⁷

Very recently these results have been challenged. Wilkins and coauthors have presented RSXD data from the $(00\frac{1}{2})$ peak [(001) in the orthorhombic notation used in Ref. 8] of bulk magnetite at the O- K and Fe- $L_{2,3}$ resonance.⁸ Their O- K spectrum is similar to that of Huang *et al.*⁶ but their Fe- $L_{2,3}$ data are very different from those of Schlappa *et al.*⁷ Almost at the same time García *et al.*⁹ reported a Fe- $L_{2,3}$ RSXD spectrum from a bulk sample, which is very different from those of

both Wilkins *et al.* and Schlappa *et al.*. In both recent publications^{8,9} the shape of the respective Fe- $L_{2,3}$ spectra are explained by absorption effects. Presently, hence, at least three different Fe- $L_{2,3}$ RSXD spectra for the $(00\frac{1}{2})$ peak of magnetite have been published and very different conclusions have been drawn about the electronic origin of the peak.

Here we report our efforts to resolve the confusion about the RXSD data on magnetite. Our strategy is to carry out the experiments using a magnetite bulk single crystal which was carefully cleaved *in-situ* in order to obtain the best possible surface quality, and to compare the results with the measurements on high quality MBE-grown magnetite thin films. In this manner we are able to distinguish intrinsic absorption effects from extrinsic effects. Taking intrinsic effects properly into account, we find consistent results for *in-situ* cleaved bulk samples and thin films. Furthermore, taking a so-called "dead" surface into account, which leads to extrinsic absorption, we are able to provide a quantitative explanation for the varying RSXD spectra reported in the literature so far.

The soft x-ray scattering experiments were performed at the HZB beam line UE46-1 at BESSY using the two-circle UHV diffractometer designed at the Freie Universität Berlin. We used 40 nm thick magnetite films epitaxially grown on an epi-polished MgO(001) substrates and several magnetite bulk single crystals. The samples were oriented such that two base vectors of the cubic room-temperature unit cell ($a = 8.396$ Å) were parallel to the scattering plane. The polarization of incoming light was either parallel or perpendicular to the scattering plane (π - or σ -polarization, respectively). A silicon-diode photon detector without polarization analysis was used with the angular acceptance set to 1° in the scattering plane and 5° perpendicular to it. The energy dependence of the diffraction-peak intensities (diffraction spectra) from




FIG. 1: (color online) RSXD spectra of the $(00\frac{1}{2})$ peak of bulk magnetite (open symbols) and magnetite thin film (filled symbols) at (a) Fe $L_{2,3}$ -edges and at (b) O K -edge. The spectra are scaled to equal height.

the film sample were recorded by varying the photon energy and keeping the momentum transfer constant. For bulk samples this method leads to distorted spectra because of the much narrower peaks and refraction effects. We therefore performed longitudinal (L) scans at every photon energy and integrated the $(00\frac{1}{2})$ -peak intensity.

Fig. 1 displays the $(00\frac{1}{2})$ resonance spectra at the Fe $L_{2,3}$ and at O K -edges for bulk magnetite and magnetite thin film. One can observe very distinct differences between the bulk and the thin film. At the Fe edge, for example, the first peak at 707 eV is much more pronounced in the bulk than in the thin film. At the O edge, the energy position of the peak of the bulk is clearly shifted with respect to that of the thin film. We ascribe these differences to a change of the scattering volume due to variations of the penetration depth of the light as a function of its energy. This effect is quite severe for energy variations across resonances in the soft x-ray regime due to the very high photo-absorption coefficients. For a bulk sample, the scattered intensity in specular geometry is proportional to $1/\mu$, with μ being the absorption coefficient.¹⁰ This absorption effect can be accounted for by multiplying the resonance spectra by μ ; μ can be reliably obtained from the x-ray absorption spectroscopy (XAS) signal recorded in the total electron yield mode.

The effect of this correction is shown for bulk magnetite in Fig. 2 for both the Fe- $L_{2,3}$ and O- K resonances. The open symbols are the raw data and the filled symbols are those after correction. The absorption signals are shown as solid lines. The correction for the Fe-spectrum affects mainly the relative intensities of the spectral fea-




FIG. 2: (color online) RSXD spectra of the $(00\frac{1}{2})$ peak of bulk magnetite without (open symbols) and with absorption correction (filled symbols) at (a) Fe $L_{2,3}$ -edges and at (b) O K -edge. The spectra are scaled to equal height. XAS spectra are shown as solid lines.

tures, while in the O-spectrum, the main peak, which is just on the slope of the absorption signal, becomes shifted in energy.

For a film of thickness D the factor to correct for absorption effects is $\mu/(1 - \exp(-2\mu d))$. $d = D/\sin\theta$ describes the effective photon path length at incident angle θ . To perform this correction requires to know μ in absolute units. Because of the thinness of the films, the correction should be smaller than for the bulk.

In Fig. 3 we now compare again the corrected spectra from the bulk (filled symbols) with the uncorrected film spectra as presented in Ref. 7 (open symbols). For the O- K spectra the agreement between bulk and film data is now close to perfect. Also for the Fe resonance the overall agreement between the spectra is very good, all spectral features agree. The main discrepancy here is in the relative intensities of the L_3 and L_2 part of the Fe-resonance spectra. The application of an absorption correction on also the thin film data would probably resolve much of this discrepancy. Thus, apart for this, we find very similar spectra from the film and the bulk at both resonances. We can, hence, safely conclude that the resonant diffraction data recorded from the thin film sample are representative for the material magnetite as such and that the conclusions derived from the data of magnetite thin films in our former Letter⁷ stand for the intrinsic properties of magnetite.

We now compare our experimental data with those from Huang *et al.*⁶, Wilkins *et al.*⁸, and García *et al.*⁹ from bulk magnetite. We first focus on the Fe $L_{2,3}$ -edges




FIG. 3: (color online) RSXD spectra of the $(00\frac{1}{2})$ peak from magnetite thin film and bulk crystal at (a) Fe $L_{2,3}$ -edges and (b) O K -edge using π polarized light.




FIG. 4: (color online) Fe $L_{2,3}$ -edges RSXD spectra of the $(00\frac{1}{2})$ peak and XAS spectra taken from our magnetite bulk crystal (red) and from Wilkins *et al.*⁸ (black). The green thick line is the result of a simulation multiplied by a factor 500 (see text). The XAS spectra are included as energy reference.

data. In Fig. 4 we present our data and those reproduced from the paper of Wilkins *et al.*⁸. The energy scales were aligned using the XAS data to account for small energy-scale offsets between different soft x-ray monochromators. The energy scale given at the top of Fig. 4 refers to the one used by Wilkins *et al.*⁸, and the bottom scale is the one of our experiment. It was claimed by Wilkins *et al.* that their data were strongly distorted by absorption effects, which suppressed all scattered intensity when the absorption increases. However, this cannot be the case

because our raw data are already very different. In fact, it is quite unlikely that absorption in an otherwise intact sample can suppress the scattered intensity completely.¹¹

What could cause such strong distortions, however, is a layer on top of the sample, which does absorb photons but does not contribute to the scattered signal. This could be either a polycrystalline layer or a crystalline layer with different surface orientation as the bulk or a layer of different chemical composition. That this "dead" layer scenario is likely is demonstrated in Fig. 4. The diamond symbols are the experimental data from Wilkins *et al.*⁸ and the green thick solid line is a simulation in which we describe the presence of an absorbing layer of thickness D_a by multiplying our experimental RSXD spectrum by $e^{-2d_a\mu(h\nu)}$ with $d_a = D_a/\sin\theta$.

We find the best agreement between data and simulation for $d_a \times \mu \approx 18$ at the absorption maximum. The resulting spectrum reproduces not only the peak position but also the shape of the data from Wilkins *et al.*⁸ very well. We note that as compared to our experimental spectrum the green line has been multiplied by a factor 500; more than 99 percent of the intensity of the diffraction spectrum is taken away by the absorbing dead layer. Concerning the Fe $L_{2,3}$ data from García *et al.*⁹ we note that their (raw) data are closer to ours, although there are appreciable quantitative differences. It therefore appears likely that the effect of an absorbing dead layer is present also in their data, although of a much thinner one than in the work of Wilkins *et al.*⁸

We now address the oxygen resonance spectra. Experimentally both in the papers by Wilkins *et al.*⁸ and Huang *et al.*⁶ a single resonance peak is observed, while our data show clearly a satellite 1.3 eV higher in energy. Huang *et al.* observe additionally a broad hump at about 4 eV higher photon energy, which is missing in our data. The 1.3-eV satellite occurs at energies where the absorption cross section is high and the filter effect discussed above for the Fe resonance may suppress this feature. Since no absorption data for energy reference are given by Wilkins *et al.*⁸ we focus on those from Huang *et al.*⁶. In Fig. 5 (a) we reproduce the O- K RSXD data from Huang *et al.*⁶. Again, we aligned the energy scales using the O- K XAS spectra (thin/dotted lines). Since our experiment was performed with higher energy resolution, we broadened our experimental XAS data slightly to obtain the same energy resolution as in the experiment of Huang *et al.*⁶. On such a calibrated energy scale we find the resonance peak at a by 230 meV higher photon energy, i.e. much closer to the absorption maximum than Huang *et al.* did.

We have carried out the same simulation as in the Fe $L_{2,3}$ -edges analysis above for O K -resonance as shown in Fig. 5 (a). The triangle symbols are the experimental data from Huang *et al.*⁶ and the green thick solid line is the simulation result. The resulting spectrum reproduces the main peak position and shape, and also contains the weak and broad hump at 4 eV above the main peak, i.e. a structure which is not present in the real spectrum and




FIG. 5: (color online) (a) O K -edge REXD spectra of the $(00\frac{1}{2})$ peak and XAS spectra taken from our magnetite bulk crystal (red) and from Ref. 6 (black). The green thick line is a simulated result (see text). The XAS spectra are included as energy reference. (b) Red line and symbols is our REXD spectrum, and green thick line is the same simulated result as in (a) but now both on the same vertical scale, showing that more than 95 percent of signal is taken away by the absorbing layer.

which is artificially generated by the local minimum in the absorption at that photon energy. In panel (b) we plot our original spectrum (red line and symbols) and the one generated by assuming an absorbing layer (green solid line) on the same vertical scale. One can also see

how much intensity of the diffraction spectrum is taken away by the absorbing dead layer: more than 95 percent of the signal is gone. The shape of the spectrum of Huang *et al.*⁶ is completely destroyed, the 1.3-eV satellite is suppressed, and the 4-eV feature is artificially generated by the dead surface layer.

We note that assuming a photon mean free path ($1/\mu$) of about 1300 Å (a value proposed by Huang *et al.*⁶) at the energy between 528 and 531 eV, and considering the detection geometry with photon incidence and detection angle around 45 degrees, we find a thickness of the "dead" surface layer of about a quarter of a micrometer. A similar thickness comes out for the data of Wilkins *et al.*⁸ at the Fe- L_3 when we estimate the photon mean free path at the Fe- L_3 maximum based on our XAS data.

In summary, we have recorded REXD spectra of the $(00\frac{1}{2})$ peak at both Fe $L_{2,3}$ -edges and O K -edge from in-vacuo cleaved magnetite single crystals, which essentially agree with those from magnetite thin films published earlier. We found that our spectra differ strongly from those published by Huang *et al.*⁶ and Wilkins *et al.*⁸, and to lesser extent, from García *et al.*⁹ We were able to ascribe the distortions in their spectra to extrinsic effects, namely the presence of a dead surface layer. Both our bulk and thin film data can hence be used for a reliable modeling of the charge and orbital ordering phenomena in magnetite.

We acknowledge BESSY for excellent working conditions and Eugen Weschke for the making his soft x-ray diffractometer available for the experiment. We thank Lucie Hamdan and the mechanical workshop of the II. Physikalisches Institut for their skillful technical assistance. The research in Cologne is supported by the Deutsche Forschungsgemeinschaft through SFB 608 and by the BMBF through contract 05KS7PK1; work at BESSY by the BMBF through contract 05ES3XBA/5.

¹ E. J. W. Verwey, *Nature (London)* **144**, 327 (1939).

² J. P. Wright, J. P. Attfield, and P. G. Radaelli, *Phys. Rev. Lett.* **87**, 266401 (2001).

³ J. P. Wright, J. P. Attfield, and P. G. Radaelli, *Phys. Rev. B* **66**, 214422 (2002).

⁴ I. Leonov, A. N. Yaresko, V. N. Antonov, M. A. Korotin, and V. I. Anisimov, *Phys. Rev. Lett.* **93**, 146404 (2004).

⁵ H.-T. Jeng, G. Y. Guo, and D. J. Huang, *Phys. Rev. Lett.* **93**, 156403 (2004).

⁶ D. J. Huang, H.-J. Lin, J. Okamoto, K. S. Chao, H.-T. Jeng, G. Y. Guo, C.-H. Hsu, C.-M. Huang, D. C. Ling, W. B. Wu, *et al.*, *Phys. Rev. Lett.* **96**, 096401 (2006).

⁷ J. Schlappa, C. Schüßler-Langeheine, C. F. Chang, H. Ott, A. Tanaka, Z. Hu, M. W. Haverkort, E. Schierle, E. Weschke, G. Kaindl, *et al.*, *Phys. Rev. Lett.* **100**, 026406 (2008).

⁸ S. B. Wilkins, S. Di Matteo, T. A. W. Beale, Y. Joly, C. Mazzoli, P. D. Hatton, P. Bencok, F. Yakhou, and

V. A. M. Brabers, *Phys. Rev. B* **79**, 201102(R) (2009).

⁹ J. García, G. Subías, J. Herrero-Martín, J. Blasco, V. Cuartero, M. C. Sánchez, C. Mazzoli, and F. Yakhou, *Phys. Rev. Lett.* **102**, 176405 (2009).

¹⁰ J. Als-Nielsen and D. McMorrow, *Elements of Modern X-ray Physics* (Wiley, New York, 2001).

¹¹ P. Abbamonte, private communication: For a single resonance the scattered intensity $I = |f' + if''|^2$ at the resonance maximum is proportional to μ^2 , because the real part of the scattering amplitude, f' is zero at the resonance maximum and $f'' \propto \mu$. The absorption effect, however, is linear in μ , which means that the observed intensity will still be finite and proportional to μ . While the actually probed linear combination of scattering amplitudes may weaken this simple argument, it is still very unlikely that absorption can reduce the scattered intensity to zero for a wide range of photon energies.