Calorimetric study of the superconducting and normal state properties of $Ca(Fe_{1-x}Co_x)_2As_2$

M. Abdel-Hafiez¹, L. Harnagea¹, S. Singh², U. Stockert³, S. Wurmehl¹, R. Klingeler⁴, A. U. B. Wolter¹, B. Büchner¹

¹ Leibniz-Institute for Solid State and Materials Research, D-01171 Dresden, Germany

² Indian Institute of Science Education and Research (IISER), Maharashtra 411008, India

³ MPI for Chemical Physics of Solids, D-01187 Dresden, Germany

⁴ Kirchhoff Institute for Physics, University of Heidelberg, D-69120 Heidelberg, Germany

E-mail: m.mohamed@ifw-dresden.de

Abstract. We present a calorimetric study on single crystals of $Ca(Fe_{1-x}Co_x)_2As_2$ (x = 0, 0.032, 0.051, 0.056, 0.063, and 0.146). The combined first order spin-density wave/structural transition occurs in the parent CaFe₂As₂ compound at 168 K and gradually shifts to lower temperature for low doping levels (x = 0.032 and x = 0.051). It is completely suppressed upon higher doping $x \ge 0.056$. Simultaneously, superconductivity appears at lower temperature with a transition temperature around $T_c \sim 14.1$ K for Ca(Fe_{0.937}Co_{0.063})₂As₂. The phase diagram of Ca(Fe_{0.937}Co_{0.063})₂As₂ has been derived and the upper critical field is found to be $\mu_0 H_{c2}^{(c)} = 11.5$ T and $\mu_0 H_{c2}^{(ab)} = 19.4$ T for the *c* and *ab* directions, respectively.

1. Introduction

After the discovery of superconductivity in LaFeAsO (1111 compound) with a transition temperature $T_c \sim 26$ K [1], a lot of investigations have been undertaken finding an increase of T_c by replacing La with smaller size rare earth ions [2] reaching up to $T_c = 55$ K in $SmO_{1-x}F_{x}FeAs$ [3]. Simultaneously, several other families of Fe-based layered superconductors have been discovered, such as the ThCr₂Si₂ structure-type AFe_2As_2 (122 family, A = Ca, Sr, Ba, Eu). They adopt a structure analogous to oxypnictides with LaO layers replaced by layers of A. These series are of great interest because large single crystals can be grown [4] which show a structural transition from a tetragonal to an orthorhombic structure combined with an antiferromagnetic ground state due to a spin-density wave (SDW) formation [5]. Furthermore, the parent compound of the 122 series becomes superconducting upon electron and hole doping [6], [7]. The CaFe₂As₂ system is of particular interest because the application of a pressure of 0.69 GPa is sufficient to suppress the SDW/structural transition completely and to induce superconductivity with a T_c exceeding 10 K [8],[9] while for SrFe₂As₂ and BaFe₂As₂ higher pressure up to 4 GPa are needed [10]. We should also mention that the electron and hole doped BaFe₂As₂ and SrFe₂As₂ series of compounds have remained very much in focus, while studies on the analogous CaFe₂As₂ compounds are very scarce.

Since specific heat measurements can provide useful information about the electronic and the gap structural properties, it is important to explore the normal state and superconducting properties of $Ca(Fe_{1-x}Co_x)_2As_2$ single crystals using this technique. In this



Figure 1. Temperature dependence of the specific heat of $Ca(Fe_{1-x}Co_x)_2As_2$ for x = 0, 0.032, 0.051, 0.056, 0.063, and 0.146 measured in zero magnetic field. The lower inset depicts the low temperature specific heat of the parent CaFe₂As₂ compound together with a fit to $c_p = \gamma T + \beta T^3$ shown as a red solid line. The upper insets show a zoom into the region around the phase transition for CaFe₂As₂ plotted as c_p vs. T and upon Co doping.

contribution, we present a first calorimetric study of both antiferromagnetic and superconducting $Ca(Fe_{1-x}Co_x)_2As_2$ for (x = 0, 0.032, 0.051, 0.056, 0.063 and 0.146) and report on the superconducting properties of the $Ca(Fe_{0.937}Co_{0.063})_2As_2$ single crystal.

2. Experimental

Single crystals of $Ca(Fe_{1-x}Co_x)_2As_2$ were grown by the high temperature solution growth method using Sn flux. All room-temperature processing (weighing, mixing, grinding and storage) of these materials was carried out in an Ar filled glove-box (O₂ and moisture level less than 0.1 ppm). The crystal growth and the physical properties of the $Ca(Fe_{1-x}Co_x)_2As_2$ series are presented in details in ref.[4],[11]-[15] and the x values are indicating the composition as measured by Energy-dispersive X-ray spectroscopy (EDX) [4]. The specific heat measurements have been performed in a Physical Property Measurement System (PPMS) using a relaxation technique. For the measurements $B \parallel ab$ a small copper block has been used to mount the sample on the specific heat puck. The heat capacity of the copper block was determined in a separate measurement and directly subtracted. Because of the nature of the structural transition, a temperature rise of only 0.5 % was used for those measurements in the vicinity of the transition.

3. Results and discussions

Fig. 1 summarizes the temperature dependence of the zero-field specific heat at various Codopings of Ca(Fe_{1-x}Co_x)₂As₂ between 1.8 and 220 K. In the parent compound (x = 0) a sharp first-order structural transition coincides with a SDW transition at $T_s = 168$ K (upon warming), which is in a good agreement with literature [4],[12],[16]. The transition width is estimated to be about 4 K. To determine the Sommerfield coefficient γ of our CaFe₂As₂ single crystal, the low-temperature specific heat data are plotted as c_p/T as a function of T^2 . These data can be fitted to a $c_p = \gamma T + \beta T^3$ power law, where γ and β are determined by the electronic and



Figure 2. Specific heat measurements of Ca(Fe_{0.937}Co_{0.063})₂As₂ measured in zero and 9 T for $B \parallel c$. The upper inset shows the difference between the zero and 9 T data, $\Delta c_p/T$, which depicts a specific heat jump with a superconducting transition temperature of about 14.1 K for $B \parallel c$. The lower inset shows the difference between the zero and 9 T data, $\Delta c_p/T$, for $B \parallel ab$.

phononic contributions, respectively, as shown in the lower inset in Fig. 1. The γ value is found to be around 5.4 mJ/mol K², which is in agreement with values ranging between 4.7 -8.2 mJ/mol K² in the literature [5],[16]. At present we do not understand this relatively large sample dependent variation in the measured values of γ . It is, however, conceivable that this difference is due to a different single crystal growth technique which is leading to differences in the crystal quality. The phononic coefficient β is found to be ~ 0.508 mJ/mol K⁴. Using the relation $\theta_D = (12\pi^4 RN/5\beta)^{-1/3}$, where R is the molar gas constant and N = 5 is the number of atoms per formula unit, we obtain the Debye temperature $\theta_D = 267$ K.

Upon Co doping of the system the combined SDW/structural transition is shifted to lower temperature and becomes broader and considerably reduced in magnitude, with the transition being shifted to 148 K and 128 K for x = 0.032 and x = 0.051, respectively, as shown in the upper inset in Fig. 1. Contrary to the magnetization, resistivity and neutron diffraction studies [4],[15], in our specific heat studies no evident splitting of the structural and magnetic transition was found in our sample x = 0.051 and x = 0.056. For higher Co doping the transitions are completely suppressed and superconductivity evolves at low temperature. The transitions observed in the specific heat data are in general consistent with those found in the resistivity, magnetization and neutron diffraction [4],[11],[15] measurements performed in few of Ca(Fe_{1-x}Co_x)₂As₂ single crystals from the same batch like those used in the present study.

Figure 2 shows the temperature dependence of the heat capacity of Ca(Fe_{0.937}Co_{0.063})₂As₂ in zero and 9 T for $B \parallel c$. Taking into account the relatively broad superconducting transition in both resistivity and susceptibility measurements on the same single crystal as discussed in detail in [4], the apparent lack of the anomaly at T_c may be due to the relatively large transition width. This is strongly supported by specific-heat data on superconducting CaFe_{1.94}Co_{0.06}As₂ single crystals, where no superconducting transition has been observed either [17]. This probably reflects the presence of nanoscopic inhomogeneities intrinsic to the Ca-system which is beyond the detection limit of EDX or we can speculate that the broad nature of superconducting transitions is related to the extreme pressure sensitivity of this compound.

However, in order to obtain information about the electronic properties in the superconducting state, we subtracted our 9 T specific heat data from the zero-field data for both directions, labeled as $\Delta c_p/T$ in the insets of Fig. 2. The extracted superconducting transition temperature is found to be 14.1 K, which is in agreement with resistivity and magnetization studies on single crystals from the same batch [4],[11]. Note, that this analysis for the estimation of the transition temperature T_c can be applied since the superconducting transition of Ca(Fe_{0.937}Co_{0.063})₂As₂ is strongly suppressed and shifted to lower temperatures in an external magnetic field of 9T. The same procedure has been used to extract T_c for other



Specific heat data Figure 3. $\Delta c_n/T$ $c_p(B) - c_p(9T)$ = of $Ca(Fe_{0.937}Co_{0.063})_2As_2$ in various magnetic fields for $B \parallel c$. The upper inset shows $\Delta c_p/T$ for $B \parallel ab$. The lower inset depicts the phase diagram estimating the upper critical fields. where the blue dotted lines show the theoretical curves based on the G-L theory and the red dotted lines represent linear fits with average slopes of $-\mu_0 dH_{c2}^{(c)}/dT=1.2~{\rm T/K}$ and $-\mu_0 dH_{c2}^{(ab)}/dT = 1.95$ T/K for the c and *ab* directions, respectively.

Figure 4. The electronic specificheat coefficient c_p/T vs. T^2 of $\operatorname{Ca}(\operatorname{Fe}_{0.937}\operatorname{Co}_{0.063})_2\operatorname{As}_2$ for magnetic fields $B \parallel c$ up to 9 T. The upper inset shows the data for $B \parallel ab$. Both data show a rather linear behavior and no Schottky anomaly is detected at low temperatures. The lower inset depicts the field dependence of $\Delta\gamma(H)$ for $B \parallel$ c. The solid red line represents a fit to $\Delta\gamma(H) = A(\mu_0 H)^{0.5}$.

fields up to 6 T (shown in Fig. 3) using the half jump height. From Fig. 3 it can be clearly seen that the superconducting transition is systematically shifted to lower temperature and reduced in height with increasing magnetic field. This behavior occurs for both field directions.

From the field dependence of T_c the phase diagram of Ca(Fe_{0.937}Co_{0.063})₂As₂ can be drawn, which is shown in the lower inset of Fig. 3 depicting the experimental data as well as the estimated upper critical field values H_{c2} for both directions. According to the Ginzburg-Landau (GL) equation [18], H_{c2} can be expressed as

$$H_{c2}(t) = H_{c2}(0) \left[\frac{1-t^2}{1+t^2}\right],\tag{1}$$

where t is the reduced temperature $t = T/T_c$. The upper critical field at T = 0 has been evaluated to be $\mu_0 H_{c2}^{(c)}(0) = 12.7$ T and $\mu_0 H_{c2}^{(ab)}(0) = 25.4$ T for the c and ab direction, respectively. Another possibility to extract the upper critical field is to consider the single-band Werthamer-Helfand-Hohenberg (WHH) model [19]:

 $H_{c2}(0) = -0.69 T_c (dH_{c2}/dT)_{T_c}$. Our data are perfectly described by a linear fit to the WHH model with an average slope $-\mu_0 dH_{c2}/dT = 1.2$ T/K and 1.95 T/K yielding upper critical fields $\mu_0 H_{c2}(0) = 11.5$ T and 19.4 T for the *c* and *ab* direction, respectively. Note, that resistivity studies on CaFe_{1.94}Co_{0.06}As₂ single crystals show similar values for the average slopes, i.e., $-\mu_0 dH_{c2}^{(c)}/dT = 1.4$ T/K for B || *c* and $-\mu_0 dH_{c2}^{(ab)}/dT = 1.8$ T/K for B || *ab* [17].

Figure 4 depicts the low temperature specific heat of Ca(Fe_{0.937}Co_{0.063})₂As₂ plotted as c_p/T vs. T^2 in different applied magnetic fields for $B \parallel c$. In the upper inset the experimental data for $B \parallel ab$ are depicted. One can see the roughly linear behavior for both directions and the absence of magnetic impurities in our sample, as usually evidenced by a Schottky anomaly at low temperatures. It is clear that the magnetic field enhances the low-temperature specific heat continuously, indicating the increase of the quasiparticle density-of-states at the Fermi level induced by a magnetic field. A linear extrapolation of the low-T data to zero temperature yields the field dependence of the field-induced contribution $\Delta\gamma(H) = (C(T, H) - C(T, 0))/T$ at T = 0. The lower inset of Fig. 4 shows $\Delta\gamma(H)$ for $B \parallel c$, clearly indicating a non-linear behavior in magnetic fields. In fact, this non-linear behavior can be fitted by the simple equation $\Delta\gamma(H) = A(\mu_0 H)^{0.5}$ predicted for d-wave symmetry in the clean limit [20], matching our experimental data. In Ba(Fe_{1-x}Co_x)₂As₂ single crystal at (x = 0.045, 0.08, 0.103, and 0.105), the $\gamma(H)$ values of the low-temperature specific heat data also fit well within this clean-limit d-wave model [21]. However, it is difficult to solely judge from specific heat data wether nodes exist or not and it should be noted that other pairing mechanisms can also result in a non-linear behavior of $\gamma(H)$.

4. Conclusions

In summary, we have studied the heat capacity of single crystals of $Ca(Fe_{1-x}Co_x)_2As_2$ (x = 0, 0.032, 0.051, 0.056, 0.063, and 0.146). Here, a combined magnetic and structural ordering has been observed for the parent compound evidenced by a first order transition around 168 K. For higher doping levels this transition shifts to lower temperatures, until it is completely suppressed for x = 0.056 and superconductivity appears around 14.1 K. From the low temperature specific heat data of the Co-doped superconducting $Ca(Fe_{0.937}Co_{0.063})_2As_2$ single crystal, the upper critical field has been determined using the WHH model. It is found to be 11.5 T and 19.4 T for $B \parallel c$ and $B \parallel ab$, respectively. A non-linear behavior of the field dependence of $\gamma(H)$ in the low-temperature region hints towards d-wave superconductivity in this compound.

Acknowledgments

We thank M. Deutschmann, S. Müller-Litvanyi, R. Müller, J. Werner, S. Pichl, K. Leger and S. Gass for technical support. This project was supported by the DFG through BE1749/13.

References

- [1] Kamihara Y, Watanabe T, Hirano M and Hosono H 2008 J. Am. Chem. Soc. 130 3296.
- [2] Chen G F, Wu D, Li G, Hu W Z, Dong J, Zheng P, Luo J L and Wang N L 2008 Phys. Rev. Lett. 100 247002.
- [3] Zhi-An R et al 2008 Chinese Phys. Lett. 25 2215.
- [4] Harnagea L et al 2011 Phys. Rev. B 83 094523.
- [5] Ni N, Nandi S, Kreyssig A, Goldman A I, Mun E D, Bud'ko S L and Canfield P C 2008 Phys. Rev. B 78 014523.
- [6] Rotter M, Tegel M and Johrendt D 2008 Phys. Rev. Lett. 101 107006.
- [7] Ni N, Thaler A, Kracher A, Yan J Q, Bud'ko S L and Canfield P C 2009, Phys. Rev. B 80, 024511.
- [8] Park T, Park E, Lee H, Klimczuk T, Bauer E D, Ronning F and Thompson J D 2008 J. Phys.: Condens. Matter 20 322204.
- [9] Baek S.-H, Lee H, Brown S E, Curro N J, Bauer E D, Ronning F, Park T, and Thompson J D 2009 Phys. Rev. Lett. 102 227601.
- [10] Alireza P L et al 2009 J. Phys.: Condens. Matter 21, 012208.
- [11] Klingeler R et al 2010 Phys. Rev. B 81 024506.
- [12] Kumar N et al 2009 Phys. Rev. B 80 144524.
- [13] Pramanik A K, Harnagea L, Singh S, Aswartham S, Behr G, Wurmehl S, Hess C, Klingeler R, and Büchner B 2010 Phys. Rev. B 82 014503.
- [14] Baek S.-H, Grafe H.-J, Harnagea L, Singh S, Wurmehl S, Büchner B Pre-print-Condmat/1103.0146.
- [15] Prokes K, Mat'as S, Harnagea L, Singh S, Wurmehl S, Argyriou D N and Büchner B 2011 Phys. Rev. B 83 104414.
- [16] Ronning F, Klimczuk T, Bauer E D, Volz H and Thompson J D 2008 J. Phys.: Cond. Matter 20 322201.

- [17] Kumar N, Nagalakshmi R, Kulkarni R, Paulose P L, Nigam A K, Dhar S K and Thamizhavel A 2009 Phys. Rev. B 79 012504.
- [18] Woollam J A, Somoano R B and O'Connor P 1964 Phy. Rev. Lett. 32 712.
- [19] Werthamer N R, Helfand E and Hohenberg P C 1966 Phys. Rev. 147 295.
- [20] Volovik G E 1993 JETP Lett. 58 469.
- [21] Gofryk K, Sefat A S, McGuire M A, Sales B C, Mandrus D, Thompson J D, Bauer E D and Ronning F 2010 Phys. Rev. B. 81 184518.