

Determining the Short-Range Spin Correlations in Cuprate Chain Materials with Resonant Inelastic X-ray Scattering

Claude Monney¹, Valentina Bisogni², Ke Jin Zhou¹, Roberto Kraus², Vladimir N. Strocov¹, Günter Behr^{2*}, Jiří Málek^{2,3}, Roman Kuzian^{2,4}, Stefan-Ludwig Drechsler², Steve Johnston², Alexandre Revcolevschi⁵, Bernd Büchner^{2,6}, Henrik M. Rønnow⁷, Jeroen van den Brink^{2,6}, Jochen Geck^{2,†} and Thorsten Schmitt^{1‡}

¹Research Department Synchrotron Radiation and Nanotechnology,
Paul Scherrer Institut, CH-5232 Villigen PSI, Switzerland

²Leibniz Institute for Solid State and Materials Research IFW-Dresden,
Helmholtzstrasse 20, D-01171 Dresden, Germany

³Institute of Physics, ASCR, Na Slovance 2, CZ-18221 Praha 8, Czech Republic

⁴Donostia International Physics Center (DIPC), Donostia-San Sebastian, Spain

⁵Laboratoire de Physico-Chimie de l'Etat Solide, ICMMO,
Université Paris-Sud, 91405 Orsay Cedex, France

⁶Department of Physics, TU-Dresden, D-01062 Dresden, Germany

⁷Laboratory for Quantum Magnetism, ICMP, Ecole Polytechnique Fédérale de Lausanne (EPFL), Switzerland

(Dated: November 20, 2021)

We report a high-resolution resonant inelastic soft x-ray scattering study of the quantum magnetic spin-chain materials Li_2CuO_2 and CuGeO_3 . By tuning the incoming photon energy to the oxygen K -edge, a strong excitation around 3.5 eV energy loss is clearly resolved for both materials. Comparing the experimental data to many-body calculations, we identify this excitation as a Zhang-Rice singlet exciton on neighboring CuO_4 -plaquettes. We demonstrate that the strong temperature dependence of the inelastic scattering related to this high-energy exciton enables to probe short-range spin correlations on the 1 meV scale with outstanding sensitivity.

PACS numbers: 78.70.En, 71.27.+a, 74.72.Cj

Two-dimensional cuprate materials play an essential role in condensed matter physics as they show high temperature superconductivity upon charge doping. For better understanding these complex materials, it is important to tackle simpler model systems sharing similar key components and showing reduced complexity, namely one dimensional cuprate chains made out of CuO_4 plaquettes. In this context, Zhang-Rice singlets (ZRS) are fundamental elementary excitations being composite objects generic to hole doped or photon excited strongly correlated charge transfer insulators, and that are especially well-known in the cuprates [1]. However, more than two decades after their theoretical discovery and numerous observations afterwards, there is still significant theoretical and experimental activity aimed at clarifying their complex details e.g. with respect to additional orbitals [2] or specific magnetic correlations beyond their centers [3].

Edge-shared cuprate chains represent a particular class of quantum magnets in which the local geometry gives rise to competing nearest ferromagnetic (FM) or antiferromagnetic (AFM) exchange coupling J_1 and frustrating next-nearest neighbor AFM J_2 superexchange couplings. The AFM one-dimensional spin-1/2 J_1 - J_2 Heisenberg model describes such frustrated magnetic interactions, due to which quantum fluctuations can alter both

ground state and spin correlations [4]. Generalizing this model by varying the signs and ratio of J_1 and J_2 gives rise to a rich phase diagram with ground states spanning FM, AFM, helical, and gapped singlet states. In real materials, the presence of interchain coupling and occasionally coupling to the lattice adds complexity to this behavior, rendering theoretical treatment more difficult [5]. It is therefore desirable to obtain experimental access to nearest neighbor spin correlations both within the ground state probed at very low-temperature and in thermally occupied excited spin-states as a function of temperature (T) [6]. Both Li_2CuO_2 and CuGeO_3 realize frustrated edge-shared chain systems that exhibit ground states with completely different intrachain spin correlations. While CuGeO_3 , on the one hand, displays the well-established spin-Peierls phase below $T_{SP} = 14$ K resulting in a gapped singlet state with pronounced AFM nearest neighbor spin correlations in the chain direction [7, 8], Li_2CuO_2 , on the other hand, shows FM long-range spin-order along the chains below $T_N = 9$ K [9].

In this letter, we demonstrate that resonant inelastic x-ray scattering (RIXS) at the oxygen K -edge allows to probe ZRS excitations [10, 11] for these two quantum magnetic spin-chain materials, Li_2CuO_2 and CuGeO_3 with unique sensitivity. Comparing the experimental results to theoretical calculations, we also show that these excitations display an extraordinarily strong temperature dependence, which is directly related to the spin texture of the studied materials. This effect together with the high sensitivity of RIXS is shown to be a powerful probe

*Deceased




FIG. 1: (a) XAS measured at the oxygen K -edge for Li_2CuO_2 with σ -polarized light at 20K and (b) for CuGeO_3 measured with π -polarized light at 40K (using the total fluorescence yield). Pre-edge peaks are related to the upper Hubbard band. (c) RIXS spectra (on an energy loss scale) measured at the oxygen K -edge for Li_2CuO_2 with σ -polarization at 20K and (d) for CuGeO_3 with π -polarization at 40K. The incident energies used for the different spectra are indicated by full triangles on the corresponding XAS spectra in graphs a and b. The RIXS spectra are normalised to the acquisition time.

to study nearest and next nearest neighbor spin correlations in cuprate chains.

RIXS experiments were performed at the ADDRESS beamline [12] of the Swiss Light Source, Paul Scherrer Institut, using the SAXES spectrometer [13]. RIXS spectra were recorded in typically 2h acquisition time, achieving a statistics of 100-150 photons on the peaks of interest. A scattering angle of 130° was used and all the spectra were measured at the specular position, i.e. at an incidence angle of 65° (see e.g. Fig. 1 in Ref. [14] for a sketch of the scattering geometry), meaning that no light momentum is transferred to the system along the chain direction. The combined energy resolution was 60 meV at the oxygen K -edge (~ 530 eV). Li_2CuO_2 single crystals (which are hygroscopic crystals) [15] were cleaved in-situ at the pressure of about $5 \cdot 10^{-10}$ mbar and at 20 K, while CuGeO_3 single crystals were cleaved at 10^{-7} mbar and RT, producing both mirror like surfaces. In the case of Li_2CuO_2 , the surface is perpendicular to the [101] axis, so that the CuO_4 plaquettes are 21° tilted away from the




FIG. 2: Schematic illustration of how a ZRS exciton is created in the RIXS process at the oxygen K -edge. See text for detailed explanations. Unoccupied states are depicted with empty orbitals.

surface. In CuGeO_3 [16], the surface is oriented perpendicular to the [100] axis, so that the CuO_4 plaquettes are 56° tilted away from the surface.

RIXS probes low-energy charge, spin, orbital and lattice excitations of solids [17, 18]. The RIXS process is based on the coherent absorption and reemission of photons. The incoming photon with energy $\hbar\omega_i$ virtually excites the electronic system from an initial state $|i\rangle$ to an intermediate state $|m\rangle$, which then decays again into a final state $|f\rangle$ by emitting an outgoing photon with energy $\hbar\omega_f$ [17]. We tuned $\hbar\omega_i$ to the oxygen K pre-edge, as shown by full triangles on the x-ray absorption spectra (XAS) in Figs. 1a and b. At this energy, O 1s core electrons are directly excited into the so-called upper Hubbard band (UHB) [19, 20], which yields a strong resonant enhancement of electronic excitations involving hybridised $\text{Cu } 3d$ and $\text{O } 2p$ valence states. Choosing different incident energies corresponds to exciting different intermediate states in the RIXS process.

In Figs. 1c and d, RIXS intensities for Li_2CuO_2 and CuGeO_3 are plotted as a function of the photon-energy loss $\hbar\Omega = \hbar(\omega_i - \omega_f)$. The unprecedented energy resolution of these data reveals remarkably rich spectra, exhibiting different sharp peaks. For both materials intense and broad structures are observed at $\hbar\Omega > 4.5$ eV that shift with $\hbar\omega_i$ and can be identified as conventional x-ray fluorescence [21]. These transitions will not be considered in the following. Instead we will focus on the excitations observed at $\hbar\Omega < 4.5$ eV. These excitations occur at fixed energy losses and have the largest intensity when $\hbar\omega_i$ is tuned to the UHB pre-peak of the oxygen K -edge.

In agreement with previous RIXS studies [22, 23] and ab initio quantum chemical calculations [24], we assign the sharp peaks at about $\hbar\Omega = 2$ eV in Li_2CuO_2 and 1.9 eV in CuGeO_3 to onsite dd -excitations, where the hole, which occupies the $3d_{x^2-y^2}$ orbital in the ground state, is excited to a different $3d$ -level.

In addition to this, well-resolved excitations are observed at resonance in between the dd -excitations and the fluorescence for both Li_2CuO_2 ($\hbar\Omega = 3.2$ eV) and CuGeO_3 ($\hbar\Omega = 3.8$ eV), as indicated by arrows in Fig. 1c and d. These two modes are essential for our further analysis. In the case of CuGeO_3 , this excitation was observed




FIG. 3: (a) Temperature dependent RIXS data for Li_2CuO_2 measured with σ -polarization and an excitation energy of 530.1 eV and (b) for CuGeO_3 measured with π -polarization and an excitation energy of 530.8 eV. The spectra are plotted in an energy loss scale. The spectra have been normalised to the area of the dd -excitations (see Supplementary Material [35]).

previously and is known to be a ZRS exciton [25–27]. Fig. 2 illustrates how such an exciton is created in the RIXS process at the oxygen K -edge. Starting from two neighboring CuO_4 plaquettes (d^9, d^9), the system reaches an intermediate state ($d^9, \underline{1s}d^{10}$) after absorbing the incoming photon tuned at the $1s \rightarrow 2p$ resonance of oxygen. In the final step, the $\underline{1s}$ oxygen core hole is filled by a ligand electron from the left plaquette, which results in a ZRS $d^9 \underline{L}$ on this plaquette [28] and a d^{10} state on the right plaquette. The extra hole on the left plaquette and the extra electron on the right plaquette form a ZRS exciton. The total spin during this process is conserved at the oxygen K -edge. Fig. 2 illustrates also that the RIXS intensity of this ZRS exciton will strongly depend on the orientation of the spins on neighboring CuO_4 plaquettes.

As we will show in the following, the 3.2 eV excitation of Li_2CuO_2 also corresponds to a ZRS exciton. In Li_2CuO_2 , the situation is more controversial, because in previous experiments with RIXS [22] and other experimental techniques [29–31], the ZRS exciton could not be unambiguously observed.

The most striking characteristic in the RIXS data is the dramatic T -dependence of the spectral peaks at about 3.5 eV, which is present in both materials, see Fig. 3. Interestingly, the T -dependence in the two materials is opposite (Fig. 3 a and b): in Li_2CuO_2 the exciton intensity decreases whereas in CuGeO_3 it increases upon cooling. These temperature dependences imply that high energy excitations at about 3.5 eV are strongly affected by thermal fluctuations corresponding to an energy scale of merely $k_B T \sim 1$ meV. We will show that these high-energy modes thereby directly reflect the character of nearest neighbor spin correlations (see Fig. 2), as the probability for a ZRS to be excited in RIXS strongly depends on the relative orientation of neighboring copper spins. In order to obtain a more detailed microscopic understanding of the nature of this strong temperature de-

pendence, we performed many-body cluster calculations based on a pd -Hamiltonian for three up to five CuO_4 plaquettes (trimers, tetramers, and pentamers) [10, 32–34] (see Ref. 35 for more details). The use of a small cluster is justified by the fact that the electronic system of the edge-shared cuprates is well-localized.

We illustrate the underlying physics with the trimer results for the sake of simplicity. Analogous results have been obtained on tetramers (not shown in this work) and pentamers (as shown in Fig. S3 of the supplementary material [35]). The trimer has eigenstates $|i, S_i\rangle$ with total spin $S_i = 1/2$ and $S_i = 3/2$, corresponding to the spin configurations $\uparrow\downarrow\uparrow$ (AFM) and $\uparrow\uparrow\uparrow$ (FM), respectively. At finite temperature T , not only the ground state, but all eigenstates $|i, S_i\rangle$ within an energy range $\sim k_B T$ will be populated. This includes states with different S_i and corresponds to thermal spin fluctuations. For both Li_2CuO_2 and CuGeO_3 three $|i, S_i\rangle$ were found to be significantly populated within the studied temperature range (see Ref. 35 and Figs. 4 a,b): two doublets with $S_i = 1/2$ ($D_{1,2}$), differing from each other in charge distribution among hybridised p and d states, and one quadruplet with $S_i = 3/2$ (Q_1). However, their energy sequence is reversed for the two systems.

Each of the thermally populated $|i, S_i\rangle$ acts as an initial state for RIXS and opens specific excitation channels $|i, S_i\rangle \rightarrow |f, S_f\rangle$. Hence, every populated $|i, S_i\rangle$ contributes with a partial intensity \mathcal{I}_i , properly weighted in the total RIXS signal $\mathcal{I}(T)$ at a specific temperature T as explained in Refs. 10 and 35.

The calculated \mathcal{I}_i for Li_2CuO_2 and CuGeO_3 are presented in Fig. 4 a and b, respectively. It can be seen that the \mathcal{I}_i originating from D_1 , D_2 and Q_1 are all distinctly different and, moreover, that a low energy charge transfer excitation exists, which can only be reached from $D_{1,2}$. The calculations identify this excitation as the ZRS exciton (d^9, d^9) \rightarrow ($d^{10}, d^9 \underline{L}$) as illustrated in Fig. 2.

The fact that the ZRS exciton can only be reached from the initial states $D_{1,2}$ and not from Q_1 , is a direct consequence of the conservation of spin ($S_f = S_i$) in oxygen K -edge RIXS. Such selection rules explain the strong T -dependence of the ZRS exciton intensity as shown in Fig. 4 c and d, which is given by the thermal population of the excited multiplet D states in case of Li_2CuO_2 .

Both, the excitation energies and the T -dependence of the ZRS exciton obtained in the model calculations for Li_2CuO_2 (Fig. 4 c) and CuGeO_3 (Fig. 4 d), agree very well with the T -dependent peak found in our experiment (Fig. 3 a and b). This unambiguously identifies the experimentally observed excitations at 3.2 eV in Li_2CuO_2 and at 3.8 eV in CuGeO_3 as ZRS excitons.

The fact that creating a ZRS exciton depends on the probability of two neighboring spins being antiparallel has an important consequence: it enables to study intrachain nearest neighbor spin correlations by oxygen K -edge RIXS. In CuGeO_3 , for instance, spins along the




FIG. 4: (a) Partial RIXS intensity \mathcal{I}_i calculated from the ground state (black line) of a Cu_3O_8 cluster and the two excited states (red and green lines), respectively, for Li_2CuO_2 and (b) for CuGeO_3 . Using the same color code, a schematic representation of the eigenstates and corresponding eigenenergies is shown. (c), Total RIXS signal $\mathcal{I}(T)$ as a function of temperature for Li_2CuO_2 and (d) CuGeO_3 (Fig. S3 of the Supplementary material shows analogous results for a Cu_5O_{12} cluster for comparison).

chain are antiparallel in the ground state. Upon decreasing T , thermally driven fluctuations out of this ground state therefore decrease, yielding a higher intensity of the corresponding ZRS exciton. Vice versa, if the spins along the chain are parallel in the ground state, the ZRS exciton peak becomes weaker upon cooling.

The results in Fig. 3 a therefore not only resolve the issue of the ZRS exciton assignment in Li_2CuO_2 , but also verify that the spins within chains in Li_2CuO_2 are FM ordered at low temperatures. Another important observation for Li_2CuO_2 is that even at 9 K the ZRS exciton peak does not disappear, but retains a significant intensity (see Fig. 3 a) at variance with the weaker structure of the low-T spectrum calculated for pentamers (see our Fig. S3 in Ref. 35). This spectral structure is fully lacking for trimers as shown in Fig. 4 c.

The observation of such a significant residual spectral weight of the ZRS exciton at low temperatures is therefore surprising. The experimental results point to sizeable residual quantum and thermal fluctuations out of the intrachain FM ground state and shows that excited spin flipped states must be very close in energy. More precisely, the presence of these excitations at 9 K directly implies that the corresponding excitation energy must be less than $10 \text{ K} \simeq 1 \text{ meV}$. The present data therefore indicates that magnetic fluctuations in Li_2CuO_2 persist down to low temperatures and that this system may be very close to the quantum critical point, which separates FM from helical (AFM) intrachain order. This observation agrees very well with a previous neutron study, where

the proximity to a quantum critical point was inferred from an analysis of the magnon dispersion [9], whereas in the present case we observe the thermal and quantum nearest neighbor spin correlations directly.

Following Ref. 10, we remind that the Zeeman splitting of the non-singlet excited states caused by an external magnetic field affects thereby their thermal population. In the perspective of our present work, this suggests that RIXS measurements in magnetic fields might be helpful to resolve the nature of the involved spin states.

In conclusion, we have performed RIXS measurements at the oxygen K -edge on the edge-sharing chain compounds, Li_2CuO_2 and CuGeO_3 . Supported by calculations within the five-band extended $\text{Cu } 3d \text{ O}2p$ Hubbard model, we have shown that our temperature dependent measurements give access to the nearest neighbor spin correlations of these materials. This is brought about via the entanglement of spin, orbital and charge degrees of freedom that characterizes strongly correlated, magnetically frustrated materials. RIXS at the oxygen K -edge can therefore be used as a versatile and powerful photon-in/photon-out method to investigate the low-energy magnetic short-range spin fluctuations in large gap charge transfer insulators with great sensitivity.

V.B. and C.M., as well as J.G. and T.S., contributed equally to this work. This work was performed at the ADDRESS beamline using the SAXES instrument jointly built by Paul Scherrer Institut, Switzerland and Politecnico di Milano, Italy. This project was supported by the Swiss National Science Foundation and its National Centre of Competence in Research MaNEP as well as the Sinergia network MPBH. We acknowledge fruitful discussions with K. Wohlfeld. V.B., R.K. and J.G. gratefully acknowledge the financial support through the Emmy-Noether Program (Grant GE1647/2-1). V.B. also acknowledges the financial support from Deutscher Akademischer Austausch Dienst. S.J. acknowledges financial support from the Foundation for Fundamental Research on Matter (The Netherlands).

[†] Electronic address: j.geck@ifw-dresden.de

[‡] Electronic address: thorsten.schmitt@psi.ch

- [1] F.C. Zhang and T.M. Rice, Phys. Rev. B **37**, 3759 (1988).
- [2] C.-C. Chen, B. Moritz, F. Vernay, J.N. Hancock, S. Johnston, C.J. Jia, G. Chabot-Couture, M. Greven, I. Elfimov, G.A. Sawatzky and T.P. Devereaux, Phys. Rev. Lett. **105**, 177401 (2010).
- [3] T. Morinari, J. Jpn. Phys. Soc. **81** 07416 (2012).
- [4] H.-J. Mikeska and A.K. Kolezhuk, One dimensional magnetism, Lecture Notes in Physics, **645**, 1, Springer, Berlin (2004).
- [5] R. Zinke, S.-L. Drechsler and J. Richter, Phys. Rev. B **79**, 094425 (2009).
- [6] N.N. Kovaleva, A.V. Boris, C. Bernhard, A. Kulakov, A. Pimenov, A.M. Balbashov, G. Khaliullin and B. Keimer,

- Phys. Rev. Lett. **93**, 147204 (2004).
- [7] M. Hase, I. Terasaki and K. Uchinokura, Phys. Rev. Lett. **70**, 3651 (1993).
- [8] G. Castilla, S. Chakravarty and V.J. Emery, Phys. Rev. Lett. **75**, 1823 (1995).
- [9] W.E.A. Lorenz, R.O. Kuzian, S.-L. Drechsler, W.-D. Stein, N. Wizen, G. Behr, J. Málek, U. Nitzsche, H. Rosner, A. Hiess, W. Schmidt, R. Klingeler, M. Loewenhaupt and B. Büchner, Euro. Phys. Lett. **88**, 37002 (2009).
- [10] J. Málek, S.-L. Drechsler, U. Nitzsche, H. Rosner and H. Eschrig, Phys. Rev. B **78**, 060508(R) (2008).
- [11] Y. Matiks, P. Horsch, R.K. Kremer, B. Keimer and A.V. Boris, Phys. Rev. Lett. **103**, 187401 (2009).
- [12] V.N. Strocov, T. Schmitt, U. Flechsig, T. Schmidt, A. Imhof, Q. Chen, J. Raabe, R. Betemps, D. Zimoch, J. Krempasky, X. Wang, M. Grioni, A. Piazzalunga and L. Patthey, J. Synchrotron Rad. **17**, 631 (2010).
- [13] G. Ghiringhelli, A. Piazzalunga, C. Dallera, G. Trezzi, L. Braicovich, T. Schmitt, V.N. Strocov, R. Betemps, L. Patthey, X. Wang and M. Grioni, Rev. Sci. Instrum. **77**, 113108 (2006).
- [14] L. Braicovich, M. Moretti Sala, L.J.P. Ament, V. Bisogni, M. Minola, G. Balestrino, D. Di Castro, G.M. De Luca, M. Salluzzo, G. Ghiringhelli and J. van den Brink, Phys. Rev. B **81**, 174533 (2010).
- [15] N. Wizen, G. Behr, W. Löser, B. Büchner and R. Klingeler, J. Cryst. Growth **318**, 995 (2011).
- [16] G. Dhalenne, A. Revcolevschi, J.C. Rouchaud and M. Fedoroff, Mater. Res. Bull. **32**, 939 (1997).
- [17] L. J. P. Ament, M. van Veenendaal, T. P. Devereaux, J. P. Hill, J. van den Brink, Rev. Mod. Phys. **83** 705 (2011).
- [18] J. Schlappa, K. Wohlfeld, K.J. Zhou, M. Mourigal, M.W. Haverkort, V.N. Strocov, L. Hozoi, C. Monney, S. Nishimoto, S. Singh, A. Revcolevschi, J.-S. Caux, L. Patthey, H.M. Ronnow, J. van den Brink and T. Schmitt, Nature, doi:10.1038/nature10974 (2012).
- [19] R. Neudert, H. Rosner, S.-L. Drechsler, M. Kielwein, M. Sing, Z. Hu, M. Knupfer, M.S. Golden, J. Fink, N. Nucker, M. Merz, S. Schuppler, N. Motoyama, H. Eisaki, S. Uchida, M. Domke and G. Kaindl, Phys. Rev. B. **60**, 13413 (1999).
- [20] V. Corradini, A. Goldoni, F. Parmigiani, C. Kim, A. Revcolevschi, L. Sangaletti and U. del Pennino, Surf. Sci. **420**, 142 (1998).
- [21] A. Kotani and S. Shin, Rev. Mod. Phys. **73**, 203 (2001).
- [22] T. Learmonth, C McGuinness, P.-A. Glans, J.E. Downes, T. Schmitt, L.-C. Duda, J.-H. Guo, F.C. Chou and K.E. Smith, Euro. Phys. Lett. **79**, 47012 (2007).
- [23] L.-C. Duda, J.E. Downes, C. McGuinness, T. Schmitt, A. Augustsson, K.E. Smith, G. Dhalenne and A. Revcolevschi, Phys. Rev. B **61**, 4186 (2000).
- [24] H.-Y. Huang, N.A. Bogdanov, L. Siurakshina, P. Fulde, J. van den Brink and L. Hozoi, Phys. Rev. B **84**, 235125 (2011).
- [25] F. Bondino, M. Zangrando, M. Zacchigna, G. Dhalenne, A. Revcolevschi and F. Parmigiani, Phys. Rev. B **75**, 195106 (2007).
- [26] S. Atzkern, M. Knupfer, M.S. Golden, J. Fink, A. Hubsch, C. Waidacher, K.W. Becker, W. von der Linden, M. Weiden and C. Geibel, Phys. Rev. B **64**, 075112 (2001).
- [27] J. Kim, D. S. Ellis, H. Zhang, Y.-J. Kim, J. P. Hill, F. C. Chou, T. Gog and D. Casa, Phys. Rev. B **79**, 094525 (2009).
- [28] F.C. Zhang and T.M. Rice, Phys. Rev. B **37**, 3759 (1988).
- [29] S. Atzkern, M. Knupfer, M. S. Golden, J. Fink, C. Waidacher, J. Richter, and K. W. Becker, N. Motoyama, H. Eisaki, and S. Uchida, Phys. Rev. B **62**, 7845 (2000).
- [30] Y. Mizuno, T. Tohyama, S. Maekawa, T. Osafune, N. Motoyama, H. Eisaki and S. Uchida, Phys. Rev. B **57**, 5326 (1998).
- [31] Y.-J. Kim, J. P. Hill, F. C. Chou, D. Casa, T. Gog, and C. T. Venkataraman, Phys. Rev. B **69**, 155105 (2004).
- [32] K. Okada and A. Kotani, Phys. Rev. B **65**, 144530 (2002).
- [33] K. Okada and A. Kotani, J. Phys. Soc. Jap. **76**, 123706 (2007).
- [34] K. Okada and A. Kotani, Phys. Rev. B **63**, 045103 (2001).
- [35] See Supplementary Material at ... for a detailed description of our theoretical model.