

Colossal electromagnon excitation in the non-cycloidal phase of TbMnO_3 under pressure

Ian Aupiais¹, Masahito Mochizuki², Hideaki Sakata³, Romain Grasset^{1,4}, Yann Gallais¹, Alain Sacuto¹ & Maximilien Cazayous¹

¹*Laboratoire Matériaux et Phénomènes Quantiques (UMR 7162 CNRS), Université Paris Diderot-Paris 7, 75205 Paris cedex 13, France*

²*Department of Applied Physics, Waseda University, Shinjuku-ku Tokyo 169-8555, Japan*

³*Department of Physics, Tokyo University of Science, 1-3 Kagurazaka Shinjyuku-ku Tokyo 162-8601, Japan*

⁴*Present address: Laboratoire des Solides Irradiés, Ecole polytechnique, Route de Saclay 91128 Palaiseau, France*

ABSTRACT

The magnetoelectric coupling, i.e., cross-correlation between electric and magnetic orders, is a very desirable property to combine functionalities of materials for next-generation switchable devices. Multiferroics with spin-driven ferroelectricity presents such a mutual interaction concomitant with magneto- and electro-active excitations called electromagnons. TbMnO_3 is a paradigmatic material in which two electromagnons have been observed in the cycloidal magnetic phase. However, their observation in TbMnO_3 is restricted to the cycloidal spin phase and magnetic ground states that can support the electromagnon excitation are still un-

der debate. Here, we show by performing Raman spectroscopy measurements under pressure that the lower-energy electromagnon (4 meV) disappears when the ground state enters from a cycloidal phase to an antiferromagnetic phase (E-type). On the contrary, the magneto-electric activity of the higher-energy electromagnon (8 meV) increases in intensity by one order of magnitude. Using microscopic model calculations, we demonstrate that the lower-energy electromagnon, observed in the cycloidal phase, originates from a higher harmonic of the magnetic cycloid, and we determine that the symmetric exchange-striction mechanism is at the origin of the higher-energy electromagnon which survives even in the E-type phase. The colossal enhancement of the electromagnon activity in TbMnO_3 paves the way to use multiferroics more efficiently for generation, conversion and control of spin waves in magnonic devices.

INTRODUCTION

In the so-called improper multiferroics such as perovskite manganites RMnO_3 with R being a rare-earth ion, the electric polarization is induced by a spin order breaking the spatial inversion symmetry via the spin-orbit interaction¹⁻⁵ or the magnetic exchange striction^{6,7}. TbMnO_3 is one of the most studied multiferroic materials of this class. Such a compound is fundamental to study novel coupling between microscopic degrees of freedom such as spin and charge⁸. In 2006, Pimenov *et al.*⁹ succeeded in exciting spin waves with the electric-field component of terahertz (THz) light in TbMnO_3 . They called these excitations electromagnons, excitations theoretically put forth by Smolenskii and Chupis¹⁰ more than 20 years ago. They also showed that the electromagnons could

be suppressed by applying a magnetic field, directly demonstrating magnetic-field-tuned electric excitations ^{9,11}. Their signatures have been evidenced by a large number of techniques : THz ^{9,11}, infrared (IR) ^{12,13}, Raman ¹⁴ spectroscopies and inelastic neutron scattering ¹⁵. The interest for the electromagnons extends to applications. Tuning magnetic properties of multiferroics is the first step to build a new technology based on spin waves called magnonics using these promising materials ^{16,17}. In particular, it has been demonstrated that the electromagnons can be exploited to directly manipulate atomic-scale magnetic structures in the rare-earth manganites using THz optical pulses ¹⁸.

Considerable efforts have been devoted to determine the origin of the electromagnons. Katsura *et al.* ¹⁹ firstly proposed a model for a dynamical coupling based on the inverse Dzyaloshinskii-Moriya (DM) interaction, originally developed to explain the static ferroelectricity in TbMnO₃ ¹. However, the light polarization predicted to observe such excitations is in contradiction with the two electromagnons observed in IR ¹³ and THz spectroscopies ¹¹. The two electromagnons are observed around 60 cm⁻¹ (7.4 meV) and 35 cm⁻¹ (3.7 meV) in the cycloidal magnetic phase. The higher-energy electromagnon has already been explained as a zone-edge magnon activated purely by the magnetostriction mechanism ^{13,20,21}, but the origin of the lower-energy electromagnon is still under debate. Two models have been proposed, one based on the anharmonic component of the cycloidal ground state ²¹, and another assuming an anisotropic magnetostriction coupling ²⁰.

In this work, we investigate the dynamical part of the magnetism in TbMnO₃ under hydrostatic pressure to determine the exact spin ground state responsible for the electromagnon activity. At

ambient pressure and below $T_C = 28\text{K}$, the Mn magnetic moments exhibits an incommensurate cycloidal magnetic order propagating along the b direction with a wave vector $Q_C = (0, 0.28, 1)$ ³. The magnetic order combined with an inverse DM interaction induces an electrical polarization along the c axis^{7,22,23}. At around 5 GPa and 10K, the spin ground state changes from this cycloidal state to the E-type antiferromagnetic state with a wave vector $Q_E = (0, 0.5, 1)$ ^{24,25}, in which a giant spin-driven ferroelectric polarization has been observed along the a axis^{26,27}. Tracking the electromagnons, low energy excitations with small Raman intensity, requires the development of dedicated instrumentation to optically study them under pressure. The experimental setup is based on a diamond anvil cell in a non-colinear scattering geometry. It allows to increase the numerical aperture collection and reduces the background signal to measure small Raman signal at low energy. We have then been able to measure the electromagnon Raman signal on TbMnO_3 as low as 10 cm^{-1} and up to 8 GPa.

RESULTS

Experiments

Figure 1a shows the low-energy part of the A_g Raman spectra at 11 K for different pressures with light polarizations parallel to the a axis (for more details see Methods). At 0 GPa, two low energy excitations, associated with electromagnons, are observed at 60 cm^{-1} (e_2) and 35 cm^{-1} (e_1). The mode at 60 cm^{-1} corresponds to the zone-edge magnon of the cycloid activated by the pure exchange-striction mechanism^{13,21}. Even if its origin is still under debate, the mode at 35 cm^{-1}




Figure 1: **Raman signature of electromagnons along the a axis in $TbMnO_3$ under hydrostatic pressure.** (a) Low-energy Raman spectra at 11K for different hydrostatic pressures for A_g symmetry with a light polarization along the a axis. The spectrum at 0 GPa has been measured outside the diamond anvil cell. The e_1 electromagnon disappears between 2.13 GPa and 3.40 GPa (see Supplementary Information). Dashed lines correspond to the backgrounds. (b) Raman shift and Full Width of Half Maximum (FWHM) of the e_1 (stars) and the e_2 (triangles) electromagnons. Dashed line is a guide for the eyes. The insert is a plot of the integrated Raman intensity of the e_1 electromagnon as a function of pressure.

has been attributed to a magnon located at $2Q_C$ away from the zone-edge, which corresponds to a replica of the e_2 mode and hence is referred to as a twin electromagnon^{20,21}. As seen in the insert of Fig. 1b, the integrated Raman intensity of the twin electromagnon (e_1) decreases as the pressure increases and finally it disappears between 2.13 GPa and 3.4 GPa. On the contrary, the intensity of the zone-edge electromagnon (e_2) is strongly enhanced above 4.5 GPa. Its energy decreases continuously as the pressure increases. The FWHM of the e_2 electromagnon in Fig. 1b presents a step around 4.5 GPa, corresponding to the transition from the cycloidal phase to the E-type phase. The transition between the cycloid and the E-type phase is expected to be sharp. However, we suspect the transition is smoothed by domains which are averaged under our laser spot (size of 30 μm). Peaks above 100 cm^{-1} are ascribed to phonon modes. The frequencies of the two phonons at 110 cm^{-1} and 145 cm^{-1} increase under pressure due to the decrease of the crystal volume. We notice that an additional peak appears at 124 cm^{-1} above 4.75 GPa. Since no structural transition has been reported at this pressure previously, the activation of this mode is not trivial. This might be a Raman-activated infrared phonon mode coupled to magnetic excitations or a two-magnon excitation coupled with phonon modes¹².

Figure 2 represents the integrated Raman intensity of the zone-edge e_2 electromagnon peak extracted from Fig. 1a as a function of the pressure. The integrated intensity of the e_2 mode is a signature of the electro- and magneto-activity of the electromagnon. Above the transition to the E-type phase at 4.5 GPa, the activity of this electromagnon increases and is multiplied by an order of magnitude at 8.07 GPa. Moreover, a jump is observed around 4.5 GPa which reflects the switching of the ferroelectric polarization vector from the c axis to the a axis as seen by




Figure 2: **Colossal enhancement of the electromagnon activity in the E-type phase of TbMnO_3 .** Integrated Raman intensity of the zone-edge e_2 electromagnon (triangles) as a function of the pressure. Measured spontaneous ferroelectric polarization (squares) in the a direction as functions of the pressure at 10 K extracted from T. Aoyama *et al.*²⁷. Dashed line is a guide for the eyes.

the P-E ferroelectric hysteresis loop^{26,27}. The measured spontaneous ferroelectric polarization²⁷ under pressure is included in Fig. 2. We find that both set of data follow a similar behavior. The experimental polarization reaches a maximum value of $1.1 \mu\text{C}\cdot\text{cm}^{-2}$ at 9 GPa, an order of

magnitude larger than the value at ambient pressure. It is clear that the continuous increase of the zone-edge electromagnon activity is correlated with the emergence and the hardening of the electric polarization along the a axis observed in the E-type phase. This underlines that the mechanism of the spin-driven ferroelectricity is also involved in the origin of the electromagnon activity in this phase.

Theory

To shed light on a physical mechanism of the electromagnons in the E-type phase, we developed calculations based on microscopic spin Hamiltonian consisting of five terms as $H = H_{\text{ex}} + H_{\text{DM}} + H_{\text{sia}}^{\text{D}} + H_{\text{sia}}^{\text{E}} + H_{\text{biq}}$. The first term H_{ex} describes superexchange interactions for which four kinds of exchange couplings are taken into account. The competition between the ferromagnetic coupling J_{ab} and the antiferromagnetic coupling J_{b} in the ab plane induces a cycloidal magnetic order. The interplane antiferromagnetic coupling J_{c} causes a staggered stacking along the c -axis. A ferromagnetic coupling J_{a} along the a -axis is necessary to reproduce the E-type phase although it plays only a minor role in the cycloidal phase. H_{DM} is the DM interaction. The terms $H_{\text{sia}}^{\text{D}}$ and $H_{\text{sia}}^{\text{E}}$ describe the single-ion magnetic anisotropies, both of which introduces anharmonicity to the magnetic cycloid. The last term H_{biq} represents the biquadratic interaction, which reinforces anharmonicity in the cycloidal phase and stabilizes the E-type phase (see Supplementary Information).

Spin- and helicity-correlation functions are calculated to identify the magnetic order. The low-




Figure 3: **Theoretical calculations based on the microscopic spin model.** (a) Coupling between the electric field of light, $E^\omega \parallel a$, and magnetic order in the ab plane via the symmetric exchange-striction mechanism. (b) The zone-edge magnon induced by this mechanism, small blue arrows represent the out of phase oscillation of the spins. (c) Electromagnon absorption spectra calculated for the bc -plane cycloidal phase under a low pressure and the E-type antiferromagnetic phase under a high pressure.

pressure phase is generated with $J_b = 0.64$ meV which reproduces the bc -plane cycloid with anharmonic components. Application of pressures to TbMnO_3 decreases the crystal volume and reduces the bond length²⁶. The exchange paths of J_{ab} and J_b are Mn(1)-O-Mn(2) and Mn(1)-O-O-Mn(3), respectively (see Supplementary Information). Hence the former is mediated by one O ion, whereas the latter by two O ions with p-p hybridization between their 2p orbitals. Because the p-p hybridization increases more significantly with pressure than the d-p hybridization, we simulate the effect of pressure on the magnetic structure by increasing the value of J_b . The electric polarization in the E-type phase results from the oxygen displacements in the ab -plane along the x or y axis due to symmetric exchange striction, the so-called symmetric exchange-striction mechanism. Therefore we adopt a bond alternation for the in-plane Mn-O-Mn bonds as $J_{ab} \pm \Delta J_{ab}$. To generate the high-pressure phase we set $J_b = 1.20$ meV and $\Delta J_{ab} = 0.04$ meV, we obtain the commensurate E-type antiferromagnetic phase with spins pointing in the b direction.

The electromagnon and magnon excitations has been calculated with the microscopic spin model. We consider the coupling $-\mathbf{E}^\omega \cdot \mathbf{P}$ between the external electric field \mathbf{E}^ω and the spin-dependent electric polarization \mathbf{P} given by:

$$P_\gamma = \Pi_\gamma \sum_i [(-1)^{i_x+i_y+m} \mathbf{S}_i \cdot \mathbf{S}_{i+x} + (-1)^{i_x+i_y+n} \mathbf{S}_i \cdot \mathbf{S}_{i+y}] \quad (1)$$

where $(m, n) = (0, 0)$ for $\gamma = a$, $(m, n) = (1, 0)$ for $\gamma = b$, $(m, n) = (i_z + 1, i_z + 1)$ for $\gamma = c$.

In the E-type phase, this term shifts oxygen atoms along the x and y axes and gives rise to a ferroelectric polarization along the a axis as observed experimentally^{26,27}. We first prepare spin

configurations at a low temperature by the Monte-Carlo thermalization, and then let the spins configuration relaxed with a sufficient time evolution using the Landau-Lifshitz-Gilbert (LLG) equation. We apply a short pulse of electric field $\mathbf{E}^\omega \parallel \mathbf{a}$ to the relaxed system at $t=0$ and trace the time evolution of ferroelectric polarization by numerically solving the LLG equation using the fourth-order Runge-Kutta method (see Supplementary Information). The Fourier transform of the obtained time profiles of the spin-dependent electric polarization gives the electromagnon absorption spectrum.

DISCUSSION

The calculated electromagnon spectra for the two phases are displayed in Fig. 3c. We obtain two modes at 30 cm^{-1} and 80 cm^{-1} in the bc -plane cycloidal phase. These two modes correspond to the twin (e_1) and the zone-edge (e_2) electromagnons, respectively. On the other hand, we obtain only one mode at 60 cm^{-1} in the E-type phase which corresponds to the down shifted e_2 electromagnon. Aguilar *et al.*¹³ argued that the exchange-striction mechanism does not work in the collinear spin phase. Since the E-type phase has long been believed to be a collinear order, we expect that the electromagnon excitation mediated by the exchange-striction mechanism should disappear in the E-type phase. However, our calculation reproduced a large electromagnon resonance in the E-type phase. This can be understood from the non collinear nature of the E-type order. The Mn spins in the E-type phase are not perfectly collinear but are considerably canted to form a depressed commensurate ab-cycloid as found in previous theoretical studies^{28,29}. Importantly, this canted E-type phase has a magnetic periodicity of $Q_E = (0, 0.5, 1)$ that fits with a

crystal periodicity of the orthorhombically distorted perovskite lattice of TbMnO_3 . Therefore, the E-type order does not contain any higher harmonic components, which explains the absence of the lower-lying mode observed in the incommensurate cycloidal phase because it originates from the Brillouin-zone folding due to the magnetic higher harmonics of the cycloidal order²¹. As a result, the electromagnon spectrum has a single peak corresponding to the higher-lying zone-edge mode only.

These results are in good agreement with our experimental data shown in Fig. 1. In the E-type phase, the e_1 electromagnon disappears, whereas the e_2 electromagnon has its frequency downshifted. This evidences that the anharmonicity is a mandatory condition for emergence of the twin electromagnon. The fact that the twin electromagnon (e_1) disappears before the transition may be due to weakening of the anharmonicity of the cycloid or/and to the spatial coexistence of the cycloid and the E-type state in the vicinity.

In conclusion, we investigated the dynamical magnetoelectric properties of TbMnO_3 under hydrostatic pressure with both Raman spectroscopy and microscopic model calculations. We find that the lower-lying e_1 electromagnon in the anharmonic cycloidal order disappears in the E-type phase for which anharmonic components are absent. Our finding provides the evidence that the activation of the low-energy electromagnon requires an anharmonicity of the cycloid in TbMnO_3 . As in the case of the multiferroic BiFeO_3 ^{30,31}, the anharmonicity is the key to understand the finest properties of the cycloidal multiferroics. We also have shown that an electrical polarization in-

duced by the exchange-striction mechanism increases the activity of the zone-edge electromagnon by one order of magnitude. Such conditions have been realized at ambient pressure in strained TbMnO_3 thin films³² in which enhanced electromagnon excitations might be observed, providing more efficient building blocks for magnonics devices.

METHODS

Samples

Single crystals of TbMnO_3 were grown by floating-zone method and aligned using Laue X-ray back-reflection. The crystals have been polished to obtain high surface quality for optical measurements. TbMnO_3 crystallizes in the orthorhombic symmetry ($Pbnm$) with lattice parameters equal to $a = 5.3 \text{ \AA}$, $b = 5.86 \text{ \AA}$, $c = 7.49 \text{ \AA}$.³³ TbMnO_3 becomes antiferromagnetic below the Néel temperature $T_N = 42K$ ³⁴. In this phase the Mn magnetic moments form an incommensurate sinusoidal wave with a modulation vector along the b axis. The ferroelectric order appears below $T_C = 28K$ where the Mn magnetic moment transit to an incommensurate cycloidal phase^{3,35}. In this phase the spin of Mn^{3+} rotates in the bc plane, and the ferroelectric polarization appears along the c axis. We have probed one TbMnO_3 single crystals with a ac plane.

Light scattering

Raman scattering measurements are performed in a diamond anvils cell equipped with a membrane for change of the hydrostatic pressure. The fluorescence of ruby balls is used as a

pressure gauge. The pressure transmitting medium is helium. The incident laser spot is about 20 μm diameter size. We have used a triple spectrometer Jobin Yvon T64000 equipped with a liquid-nitrogen-cooled CCD detector and solid laser with a line at 561 nm.

DATA AVAILABILITY

The authors declare that [the/all other] data supporting the findings of this study are available within the paper [and its supplementary information files].

ACKNOWLEDGEMENTS

M. Mochizuki thanks supports from JSPS KAKENHI (Grant No. 17H02924), Waseda University Grant for Special Re-search Projects (Project Nos. 2017S-101, 2018K-257), and JST PRESTO (Grant No. JPMJPR132A). The authors want to thank Marie Aude Measson for her technical support.

AUTHOR CONTRIBUTIONS

The samples were grown by H.S.; I.A., R.G. and M.C. performed experiments; I.A. and M.C. analyzed data; M.M developed the model and analyzed data. All authors discussed the results and wrote the manuscript.

Competing Interests: the Authors declare no Competing Financial or Non-Financial Interests.

Correspondence: Correspondence and requests for materials should be addressed to M. Cazayous (email: maximilien.cazayous@univ-paris-diderot.fr).

REFERENCES

1. Sergienko, I. A. & Dagotto, E. Role of the Dzyaloshinskii-Moriya interaction in multiferroic perovskites. *Phys. Rev. B* **73**, 094434 (2006).
2. Mostovoy, M. Ferroelectricity in spiral magnets. *Phys. Rev. Lett.* **96**, 067601 (2006).
3. Kenzelmann, M. *et al.* Magnetic inversion symmetry breaking and ferroelectricity in TbMnO_3 . *Phys. Rev. Lett.* **95**, 087206 (2005).
4. Mochizuki, M. & Furukawa, N. Microscopic model and phase diagrams of the multiferroic perovskite manganites. *Phys. Rev. B* **80**, 134416 (2009).
5. Hu, J. Microscopic origin of magnetoelectric coupling in noncollinear multiferroics. *Phys. Rev. Lett.* **100**, 077202 (2008).
6. Picozzi, S. Yamauchi, K. Sanyal, B. Sergienko, I. A. & Dagotto, E. Dual nature of improper ferroelectricity in a magnetoelectric multiferroic. *Phys. Rev. Lett.* **99**, 227201 (2007).
7. Sergienko, I. A. Sen, C. & Dagotto, E. Ferroelectricity in the magnetic E-Phase of orthorhombic perovskites. *Phys. Rev. Lett.* **97**, 227204 (2006).

8. Khomskii, D. Classifying multiferroics: Mechanisms and effects. *Physics* **2**, 20 (2009).
9. Pimenov, A. *et al.* Possible evidence for electromagnons in multiferroic manganites. *Nature Physics* **2**, 97 (2006).
10. Smolenski, G. A. & Chupis, I. E. Ferroelectromagnets. *Soviet Physics Uspekhi* **25**, 475 (1982).
11. Pimenov, A. *et al.* Magnetic and magnetoelectric excitations in TbMnO_3 . *Phys. Rev. Lett.* **102**, 107203 (2009).
12. Takahashi, Y. *et al.* Evidence for an electric-dipole active continuum band of spin excitations in multiferroic TbMnO_3 . *Phys. Rev. Lett.* **101**, 187201 (2008).
13. Valdés Aguilar, R. *et al.* Origin of electromagnon excitations in multiferroic RMnO_3 . *Phys. Rev. Lett.* **102**, 047203 (2009).
14. Rovillain, P. Cazayous, M. Gallais, Y. Sacuto, A. Measson, M-A. & Sakata A. Magnetolectric excitations in multiferroic TbMnO_3 by Raman scattering. *Phys. Rev. B* **81**, 054428 (2010).
15. Senff, D. *et al.* Magnetic excitations in multiferroic TbMnO_3 : Evidence for a hybridized soft mode. *Phys. Rev. Lett.* **98**, 137206 (2007).
16. Kruglyak, V. V. Demokritov, S. O. & Grundler, D. Magnonics. *J. Phys. D: Appl. Phys.* **43**, 264001 (2010).
17. Eerenstein, W. Mathur, N. D. & Scott, J. F. Multiferroic and magnetoelectric materials. *Nature* **10**, 1038 (2006).

18. Kubacka, T. *et al.* Large-amplitude spin dynamics driven by a thz pulse in resonance with an electromagnon. *Science* **343**, 1333 (2014).
19. Katsura, H. Balatsky, A. V. & Nagaosa, N. Dynamical Magnetoelectric Coupling in Helical Magnets. *Phys. Rev. Lett.* **98**, 027203 (2007).
20. Stenberg, M. P. V & de Sousa, R. Model for twin electromagnons and magnetically induced oscillatory polarization in multiferroic TbMnO₃. *Phys. Rev. B* **80**, 094419 (2009).
21. Mochizuki, M. Furukawa, N. & Nagaosa, N. Theory of electromagnons in the multiferroic mn perovskites: The vital role of higher harmonic components of the spiral spin order. *Phys. Rev. Lett.* **104**, 177206 (2010).
22. Kimura, T. *et al.* Magnetic control of ferroelectric polarization. *Nature* **426**, 55 (2003).
23. Walker, H. C. *et al.* Femtoscale magnetically induced lattice distortions in multiferroic TbMnO₃. *Science* **333**, 1273 (2011).
24. Makarova, O. L. Mirebeau, I. Kichanov, S. E. Rodriguez-Carvajal, J. & Forget, A. Pressure-induced change in the magnetic ordering of TbMnO₃. *Phys. Rev. B* **84**, 020408 (2011).
25. Terada, N. *et al.* Magnetic ordering in pressure-induced phases with giant spin-driven ferroelectricity in multiferroic TbMnO₃. *Phys. Rev. B* **93**, 81104 (2016).
26. Aoyama, T. Iyama, A. Shimizu, K. & Kimura, T. Giant spin-driven ferroelectric polarization in TbMnO₃ under high pressure. *Nat. Com.* **5**, 4927 (2014).

27. Aoyama, T. Iyama, A. Shimizu, K. & Kimura, T. Multiferroicity in orthorhombic RMnO_3 (R = Dy, Tb and Gd) under high pressure. *Phys. Rev. B* **91**, 081107 (2015).
28. Mochizuki, M. Furukawa, N. & Nagaosa, N. Theory of spin-phonon coupling in multiferroic manganese perovskites RMnO_3 . *Phys. Rev. B* **84**, 144409 (2011).
29. Mochizuki, M. Furukawa, N. & Nagaosa, N. Spin model of magnetostrictions in multiferroic Mn perovskites. *Phys. Rev. Lett.* **105**, 037205, (2010).
30. De Sousa, R. & Moore, J. E. Optical coupling to spin waves in the cycloidal multiferroic BiFeO_3 . *Phys. Rev. B* **77**, 012406 (2008).
31. Fishman, R. S. Haraldsen, J. T. Furukawa, N. & Miyahara, S. Spin state and spectroscopic modes of multiferroic BiFeO_3 . *Phys. Rev. B* **87** 134416 (2013).
32. Shimamoto, K. *et al.* Tuning the multiferroic mechanisms of TbMnO_3 by epitaxial strain. *Sci. Report* **7**, 44753 (2017).
33. Alonso, J. A. Martinez-Lope, M. J. Casais, M. T. & Fernández-Diaz, M. T. Evolution of the Jahn Teller distortion of MnO_6 octahedra in RMnO_3 perovskites (R = Pr, Nd, Dy, Tb, Ho, Er, Y): A neutron diffraction study. *Inorganic Chemistry* **39**, 917 (2000).
34. Quezel, S. Tcheou, F. Rossat-Mignod, J. Quezel, G. & Roudaut, E. Magnetic structure of the perovskite-like compound TbMnO_3 . *Physica B+C* **86-88** 916 (1977).
35. Kimura, T. Lawes, G. Goto, T. Tokura, Y. & Ramirez, A. P. Magnetoelectric phase diagrams of orthorhombic RMnO_3 (R = Gd, Tb and Dy). *Phys. Rev. B* **71**, 24425 (2005).