# Dynamical Formation of Graphene and Graphane Nanoscrolls.

M. L. Pereira Júnior<sup>a,\*\*</sup>, L. A. Ribeiro Júnior<sup>b,\*\*</sup>, D. S. Galvão<sup>c,d</sup>, J. M. De Sousa<sup>e,c,\*\*</sup>

<sup>b</sup>Institute of Physics, University of Brasília, 70910-900, Brasília, Brazil

<sup>c</sup>Applied Physics Department, University of Campinas, Campinas, São Paulo, Brazil

<sup>d</sup>Center for Computing in Engineering and Sciences, University of Campinas, Campinas, São Paulo, Brazil.

<sup>e</sup>Instituto Federal de Educação, Ciência e Tecnologia do Piauí - IFPI, Primavera, São Raimundo Nonato,

Piauí, 64770-000, Brazil

<sup>f</sup>Applied Physics Department, State University of Campinas – UNICAMP, Campinas, 13083-859, SP, Brazil.

### Abstract

Carbon nanoscrolls (CNSs) are nanomaterials with geometry resembling graphene layers rolled up into a spiral (papyrus-like) form. Effects of hydrogenation and temperature on the self-scrolling process of two nanoribbons interacting with a carbon nanotube (CNT) have been studied by molecular dynamics simulations for three configurations: (1) graphene/graphene/CNT; (2) graphene/graphane/CNT, and (3) graphane/graphane/CNT. Graphane refers to a fully hydrogenated graphene nanoribbon. Nanoscroll formation is observed for configurations (1) and (2) for temperatures 300-1000 K, while nanoribbons wrap CNT without nanoscroll formation for configuration (3).

Keywords: Reactive Molecular Dynamics, Graphene Nanoribbons, Graphane Nanoribbons, Carbon Nanoscrolls, Self-Scrolling

### 1. Introduction

After isolation of a single layer of graphite (Graphene) [1], obtained by mechanical exfoliation, there is a renewed interest in obtaining new 2D materials [2, 3]. From a topological point of view, graphene layers can be considered as the basis to generate other structures, such as carbon nanotubes [4] and nanoscrolls [5]. Carbon nanotubes are understood as graphene layers rolled up into cylinders, while nanoscrolls are graphene layers rolled up into a papyrus-like form. There are many theoretical and experimental works investigating nanoscrolls of different materials [6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16].

In contrast to carbon nanotubes (CNTs), carbon nanoscrolls (CNSs) have open ends, which allows an easily radial expansion (tunable interlayer distances) explored in different

<sup>&</sup>lt;sup>a</sup>Department of Electrical Engineering, Faculty of Technology, University of Brasília, 70910-900, Brasília, Brazil.

<sup>\*</sup>I am corresponding author

<sup>\*\*</sup>I am corresponding author

 $<sup>\</sup>label{logist} \textit{Email addresses:} \ \texttt{marcelo.lopes@unb.br} \ (M. \ L. \ Pereira \ Júnior), \ \texttt{ribeirojr@unb.br} \ (L. \ A. \ Ribeiro \ Júnior), \ \texttt{josemoreiradesousa@ifpi.edu.br} \ (J. \ M. \ De \ Sousa)$ 

applications [17, 18]. The most significant barrier in their usage has been the limited synthesis of high-quality structures. It leads to a controlling inability of some crucial aspects, among them, the number of scrolled layers [19, 20, 21]. To overcome this barrier, new alternative routes in obtaining CNSs that allow higher control over the final structure to broaden their applications are desirable [22, 23, 24]. CNSs exhibit distinct electronic and mechanical behaviors when compared with graphene and CNTs [25, 26]. The CNSs nucleus presents vibrational properties that can be useful in developing nano-actuators and electromechanical devices with excellent performance as cathodes in lithium-sulfur batteries [27, 28, 29]. It is worth mentioning that Density Functional Theory (DFT) calculations were used to address the synthetic growth concept of carbon-based materials [30].

Recently, molecular dynamics simulations have been used to investigate other possible synthetic routes [17, 13, 31]. Results showed that CNT triggers the self-scrolling process of graphene nanoribbons. As a result, the layer spontaneously rolls itself around the CNT to lower the surface energy, a process governed by van der Waals interactions. The advantage of this method is that it imposes dry, non-chemical, and room-temperature conditions [17, 13, 31]. An experimental study was conducted by *Xie et. al.* to obtain stable CNSs focused on offering higher control over the final product [32]. In their method, graphite is mechanically exfoliated, deposited over SiO<sub>2</sub> substrate, and then immersed in a solution of water and isopropyl alcohol. After resting for a few minutes, the system spontaneously formed CNSs [32]. Another possibility is to use functionalized structures such as graphene oxides and hydrogenated ones [29, 33].

Herein, we used fully-atomistic reactive (ReaxFF) molecular dynamics (MD) simulations to investigate the effects of hydrogenation on the self-scrolling mechanism of graphene and graphane nanoribbons when triggered by CNTs. Our results show that it is possible to obtain stable CNT-wrapped CNSs from pure and hydrogenated graphane nanoribbons.

# 2. Computational Methodology

In the present work, we used fully atomistic (ReaxFF) molecular dynamics simulations for C/H/O [34], as implemented in LAMMPS code [35]. The initial configurations of our model systems are presented in Figure 1, where we shown three atomic models identified as Complex-A (graphene/graphene/CNT, Complex-B (graphene/graphane/CNT), and Complex-C (graphane/graphane/CNT). The two graphene-based nanoribbons have a length and width of 150 Å and 21 Å, respectively. The CNT used to trigger the self-scrolling mechanism is a conventional zigzag CNT (0, 22) with a diameter of 17.21 Å and length of 100 Å. The graphene nanoribbon and CNT have 1296 and 2112 carbon atoms, respectively. The initial distance between the nanoribbons and the CNT wall is 5.41 Å.In the initial assembly, the nanoribbons are placed into contact with the nanotubes as shown in Figures 1(d-f). The nanoribbons were placed on opposite sides regarding the CNT center.

The composite systems (Complexes –A, –B, and –C) were equilibrated/thermalized within an NVT ensemble at 300, 600, and 1000 K using the Nosé-Hoover thermostat [36]. We considered 1000 K as the uppermost temperature limit, envisioned carbon-based optoelectronic applications. Scroll structures are resilient to high temperatures (up to




Figure 1: Model systems used to simulate the formation of CNT-wrapped CNSs. Illustration of the atomic configuration for (a) graphene and (b) graphane nanoribbons. The dashed lines highlight the structural units. (c) Diagrammatic representation for the initial arrangement of the system involving two nanoribbons and a CNT, where  $d_1 = 150$  Å (nanoribbon length),  $d_2 = 17.21$  Å (CNT diameter),  $d_3 = 28.03$  Å (initial distance between the nanoribbons), and  $d_4 = 23.00$  Å (ribbon length into contact with nanotube). Initial configurations for the systems studied here: (d) graphene/graphene/CNT (Complex–A), (e) graphene/graphane/CNT (Complex–B), (f) and graphane/graphane/CNT (Complex–C). In the color scheme, the gray and yellow spheres represent carbon and hydrogen atoms, respectively.

4000K), as recently demonstrated in references [14, 37]. The system equilibration was initially performed to eliminate any residual stress during 100 ps. The time step for the simulations was 0.1 fs. The MD snapshots and trajectories were obtained by using the free visualization and analysis program VMD [38].

In the present work, we performed 10 MD runs (with different seeds) for each temperature. The random seeds defined distinct initial sets of atomic velocities in the equilibration of the systems. All the MD runs yielded the same products for each complex. In this sense, the results reported in the manuscript are the most representative outcomes obtained for all the simulations.

# 3. Results and Discussions

We begin our discussion by presenting the dynamical behavior of the self-scrolling process for all complexes studied here (see Figure 1). In Figure 2 we show a sequence of representative MD snapshots (in lines) for Complex-A, -B, and -C from top to bottom, respectively, for simulations at 300 K. In the very first stage of the simulation (about 2.5 ps), the nanoribbons are in contact with the CNT surface, and the self-scrolling process takes place. This trend

is realized in the simulations for all complexes, as shown in Figure 2. Such behavior also occurred for the self-scrolling mechanism of a single graphene nanoribbon [39].




Figure 2: Representative MD snapshots for the spontaneous self-scrolling process at 300 K, for the complexes presented in Figure 1.

At 12.5 ps of simulation, the nanoribbons start to curl around the CNT. Subsequently, for Complexes A and B, the overlap between the nanoribbons occurs. The graphane nanoribbons in Complex-C do not form a scroll. Instead, it simply wraps the CNT by covering its surface and is temperature independent (for the temperature values considered here, up to 1000 K), creating a lock-like mechanism (see Figure S1 in the Supplementary Material). This behavior is attributed to stereo hydrogen-hydrogen interactions when the graphane layers move to create an opposing force to the sliding. This trend is similar to observed for other hydrocarbon structures, such as the lander molecule, where this lock-like mechanism is present [40] and it is based on the same concept of the lock-and-key protein-protein interactions [41].It is worth mentioning that this process also occurred for the self-scrolling mechanism of a single graphene nanoribbon (see Supplementary Material).

Differences in the complexes dynamics become clear at 37.5 ps. At this stage, in Complexes A and B, the nanoribbons are almost completely wrapped, as a consequence of the interlayer interaction presented by graphene and graphane [20, 42, 43]. Graphene/graphane bilayer (Complex-B) presents an interlayer interaction energy smaller than graphene/graphene one (Complex-A) [44]. Even so, the self-scrolling process for both complexes takes the same time yielding a completely scrolled configuration at 50 ps. For Complex-C, the graphane nanoribbons wrap the entire CNT wall at 130 ps. In all cases, the nanoribbons showed discontinuous wrinkles and corrugations during the spontaneous self-scrolling process. Other reactive MD simulations performed within the scope of the AIREBO interatomic potential

[45, 26] also pointed for such instabilities. The Supplementary Material includes the videos for the dynamics of the complexes A-C. It is worth mentioning that the degree of instability for the nanoribbons was more pronounced for temperatures higher than 300 K.

The Supplementary Material presents the case in which a single graphane nanoribbon is interacting with a CNT. The main conclusion for the graphane/CNT interaction presented above holds, and the system evolves to a final state in which the graphane wraps the CNT wall. Isolated graphane nanoscrolls were already investigated by molecular dynamics simulations [43], and the results are consistent with the ones presented here.

It is important to stress that depending on the area of the nanoribbon, the most stable configuration is not planar but a scrolled one. This trend is related to the size of the overlapped region that enables van der Waals gains to overcome the elastic cost to scroll the structures [9]. Even for small graphene nanobelts, the self-scrolling can be a self-sustained process [46].




Figure 3: Total energy time evolution as function of simulation time for the Complex-A at 10 K. The insets are MD snapshots extracted from the simulation trajectory at  $t_1 = 2.5$ ,  $t_2 = 20$ ,  $t_3 = 40$ ,  $t_4 = 65$ , and  $t_2 = 80$  ps, respectively.

In Figure 3 we present the time evolution for the total energy for the Complex-A at 10 K at five different stages. During the dynamical process for the CNSs formation, there is a linear downhill trend that ends at 65 ps, which represents a completely formed scroll. From that moment on, the total energy stabilizes, and a flat region persists (neglecting thermal fluctuations, scroll "breathing" - see video) until the end of the simulation. For all the temperature regimes simulated here (300, 600, and 1000 K), the time evolution of the total energy shows a similar trend. An overall picture of the CNSs formation is presented in Figure 4. The existence of an energy plateau is the signature of the scroll formation. At high temperatures, the CNSs total energies are larger due to the higher degree of atomic

thermal vibrations, which tends to difficult the spontaneous scrolling process. Even so, one can realize a well-defined plateau in all the cases, standing for the scroll's formation.




Figure 4: Total energy time evolution as a function of the simulation time for all complexes at 300, 600, and 1000 K. The red, blue, and green data points refer to the total energy values during the simulation time for the Complex-A, Complex-B, and Complex-C, respectively. The lines were obtained from the data interpolation.

# 4. Conclusions and remarks

Through fully-atomistic reactive (ReaxFF) MD simulations, we have studied the hydrogenation effects on the self-scrolling process of graphene and graphane (hydrogenated graphene) nanoribbons interacting with a carbon nanotube (CNT). We have considered different configurations: (1) graphene/graphene/CNT; (2) graphene/graphane/CNT, (3) graphane/graphane/CNT; and different temperatures, 300, 600, and 1000 K. Our results show that the scroll formation is possible for configurations (1) and (2), for all temperatures. Configuration (3) does not yield scrolls. The scroll formation is related to the existence of

an energy plateau in the total energy as a function of the simulation time. The approach used here to assemble the nanoribbons and CNT is prototypical and extensible to other species of 2D materials beyond graphene. The usage of nanotubes for triggering the scrolling processes of sheets and nanoribbons was investigated for carbon and boron nitrides systems [47, 48, 49]. The tribology of carbon-based nanostructures has been an object of research in the last years [50, 51]. In this sense, the present study can stimulate further investigations along these lines.

## 5. Acknowledgements

The authors gratefully acknowledge the financial support from Brazilian research agencies CNPq, FAPESP, and FAP-DF. M.L.P.J gratefully acknowledges the financial support from CAPES grant 88882.383674/2019-01. J.M.S. and D.S.G. thanks the Center for Computing in Engineering and Sciences at Unicamp for financial support through the FAPESP/CEPID Grants #2013/08293-7 and #2018/11352-7. J.M.S acknowledges CENAPAD-SP (Centro Nacional de Alto Desenpenho em São Paulo - Universidade Estadual de Campinas - UNICAMP) for computational support process (proj842). L.A.R.J acknowledges the financial support from a Brazilian Research Council FAP-DF and CNPq grants 00193.0000248/2019 – 32 and 302236/2018 – 0, respectively. L.A.R.J and J.M.S acknowledge CENAPAD-SP for providing the computational facilities. L.A.R.J. gratefully acknowledges the financial support from IFD/UnB (Edital 01/2020) grant 23106.090790/2020 – 86. The authors acknowledge the National Laboratory for Scientific Computing (LNCC/MCTI, Brazil) for providing HPC resources of the SDumont supercomputer, which have contributed to the research results reported within this paper. URL: http://sdumont.lncc.br.

#### References

- [1] K. S. Novoselov, A. K. Geim, S. V. Morozov, D. Jiang, Y. Zhang, S. V. Dubonos, I. V. Grigorieva, A. A. Firsov, Electric field effect in atomically thin carbon films, science 306 (5696) (2004) 666–669.
- [2] Y. Zhang, Y.-W. Tan, H. L. Stormer, P. Kim, Experimental observation of the quantum hall effect and berry's phase in graphene, nature 438 (7065) (2005) 201–204.
- [3] A. A. Balandin, S. Ghosh, W. Bao, I. Calizo, D. Teweldebrhan, F. Miao, C. N. Lau, Superior thermal conductivity of single-layer graphene, Nano letters 8 (3) (2008) 902–907.
- [4] S. Iijima, T. Ichihashi, Single-shell carbon nanotubes of 1-nm diameter, nature 363 (6430) (1993) 603–605.
- [5] R. Bacon, Growth, structure, and properties of graphite whiskers, Journal of Applied Physics 31 (2) (1960) 283–290.
- [6] D. Tománek, Mesoscopic origami with graphite: scrolls, nanotubes, peapods, Physica B: Condensed Matter 323 (1-4) (2002) 86–89.
- [7] M. Lisa, Viculis a chemical route to carbon nanoscrolls viculis, julia j. mack, richard b. kaner, Science. 299 (5611) (2003) 1361.
- [8] L. M. Viculis, J. J. Mack, R. B. Kaner, A chemical route to carbon nanoscrolls, Science 299 (5611) (2003) 1361–1361.
- [9] S. F. Braga, V. R. Coluci, S. B. Legoas, R. Giro, D. S. Galvão, R. H. Baughman, Structure and dynamics of carbon nanoscrolls, Nano letters 4 (5) (2004) 881–884.
- [10] V. Coluci, S. Braga, R. Baughman, D. Galvao, Prediction of the hydrogen storage capacity of carbon nanoscrolls, Physical Review B 75 (12) (2007) 125404.

- [11] X. Shi, Y. Cheng, N. M. Pugno, H. Gao, Tunable water channels with carbon nanoscrolls, Small 6 (6) (2010) 739–744.
- [12] T. Uhm, J. Na, J.-U. Lee, H. Cheong, S. W. Lee, E. E. Campbell, S. H. Jhang, Structural configurations and raman spectra of carbon nanoscrolls, Nanotechnology 31 (31) (2020) 315707.
- [13] E. Perim, R. Paupitz, D. S. Galvão, Controlled route to the fabrication of carbon and boron nitride nanoscrolls: A molecular dynamics investigation, Journal of Applied Physics 113 (5) (2013) 054306.
- [14] M. L. P. Junior, W. F. da Cunha, D. S. Galvão, L. A. R. Junior, A reactive molecular dynamics study on the mechanical properties of a recently synthesized amorphous carbon monolayer converted into a nanotube/nanoscroll, Physical Chemistry Chemical Physics 23 (15) (2021) 9089–9095.
- [15] R. M. Tromer, L. C. Felix, L. A. Ribeiro, D. S. Galvao, Optoelectronic properties of amorphous carbon-based nanotube and nanoscroll, Physica E: Low-dimensional Systems and Nanostructures 130 (2021) 114683.
- [16] E. Perim, L. D. Machado, D. S. Galvao, A brief review on syntheses, structures, and applications of nanoscrolls, Frontiers in Materials 1 (2014) 31.
- [17] Z. Zhang, T. Li, Carbon nanotube initiated formation of carbon nanoscrolls, Applied physics letters 97 (8) (2010) 081909.
- [18] X. Shi, N. M. Pugno, H. Gao, Mechanics of carbon nanoscrolls: a review, Acta Mechanica Solida Sinica 23 (6) (2010) 484–497.
- [19] P. Liu, Z. Jin, G. Katsukis, L. W. Drahushuk, S. Shimizu, C.-J. Shih, E. D. Wetzel, J. K. Taggart-Scarff, B. Qing, K. J. Van Vliet, et al., Layered and scrolled nanocomposites with aligned semi-infinite graphene inclusions at the platelet limit, Science 353 (6297) (2016) 364–367.
- [20] A. Savin, E. Korznikova, I. Lobzenko, Y. A. Baimova, S. Dmitriev, Symmetric scrolled packings of multilayered carbon nanoribbons, Physics of the Solid State 58 (6) (2016) 1278–1284.
- [21] A. Savin, E. Korznikova, S. Dmitriev, E. Soboleva, Graphene nanoribbon winding around carbon nanotube, Computational Materials Science 135 (2017) 99–108.
- [22] Y. Kuroda, K. Ito, K. Itabashi, K. Kuroda, One-step exfoliation of kaolinites and their transformation into nanoscrolls, Langmuir 27 (5) (2011) 2028–2035.
- [23] T. Tojo, K. Fujisawa, H. Muramatsu, T. Hayashi, Y. A. Kim, M. Endo, M. Terrones, M. S. Dresselhaus, Controlled interlayer spacing of scrolled reduced graphene nanotubes by thermal annealing, Rsc Advances 3 (13) (2013) 4161–4166.
- [24] Y.-E. Shin, Y. J. Sa, S. Park, J. Lee, K.-H. Shin, S. H. Joo, H. Ko, An ice-templated, ph-tunable self-assembly route to hierarchically porous graphene nanoscroll networks, Nanoscale 6 (16) (2014) 9734–9741.
- [25] Y. Chen, J. Lu, Z. Gao, Structural and electronic study of nanoscrolls rolled up by a single graphene sheet, The Journal of Physical Chemistry C 111 (4) (2007) 1625–1630.
- [26] H. Song, S. Geng, M. An, X. Zha, Atomic simulation of the formation and mechanical behavior of carbon nanoscrolls, Journal of Applied Physics 113 (16) (2013) 164305.
- [27] X. Shi, N. M. Pugno, Y. Cheng, H. Gao, Gigahertz breathing oscillators based on carbon nanoscrolls, Applied Physics Letters 95 (16) (2009) 163113.
- [28] X. Shi, Y. Cheng, N. M. Pugno, H. Gao, A translational nanoactuator based on carbon nanoscrolls on substrates, Applied Physics Letters 96 (5) (2010) 053115.
- [29] P. Zuo, W. Zhang, J. Hua, Y. Ma, C. Du, X. Cheng, Y. Gao, G. Yin, A novel one-dimensional reduced graphene oxide/sulfur nanoscroll material and its application in lithium sulfur batteries, Electrochimica Acta 222 (2016) 1861–1869.
- [30] R. Freitas, R. Rivelino, F. d. B. Mota, G. K. Gueorguiev, C. de Castilho, Energy barrier reduction for the double proton-transfer reaction in guanine—cytosine dna base pair on a gold surface, The Journal of Physical Chemistry C 119 (27) (2015) 15735—15741.
- [31] D. Zhang, H. Yang, Formation of carbon nanoscrolls from graphene sheet: A molecular dynamics study, Journal of Molecular Structure 1125 (2016) 282–287.
- [32] X. Xie, L. Ju, X. Feng, Y. Sun, R. Zhou, K. Liu, S. Fan, Q. Li, K. Jiang, Controlled fabrication of high-quality carbon nanoscrolls from monolayer graphene, Nano letters 9 (7) (2009) 2565–2570.

- [33] C. A. Amadei, I. Y. Stein, G. J. Silverberg, B. L. Wardle, C. D. Vecitis, Fabrication and morphology tuning of graphene oxide nanoscrolls, Nanoscale 8 (12) (2016) 6783–6791.
- [34] C. Ashraf, A. C. Van Duin, Extension of the reaxff combustion force field toward syngas combustion and initial oxidation kinetics, The Journal of Physical Chemistry A 121 (5) (2017) 1051–1068.
- [35] S. Plimpton, Fast parallel algorithms for short-range molecular dynamics, Journal of computational physics 117 (1) (1995) 1–19.
- [36] W. G. Hoover, Canonical dynamics: equilibrium phase-space distributions, Physical review A 31 (3) (1985) 1695.
- [37] D. Lee, J. Kim, G. Park, H. W. Bae, M. An, J. Y. Kim, Enhanced operating temperature stability of organic solar cells with metal oxide hole extraction layer, Polymers 12 (4) (2020) 992.
- [38] W. Humphrey, A. Dalke, K. Schulten, et al., Vmd: visual molecular dynamics, Journal of molecular graphics 14 (1) (1996) 33–38.
- [39] D. Xia, Q. Xue, J. Xie, H. Chen, C. Lv, F. Besenbacher, M. Dong, Fabrication of carbon nanoscrolls from monolayer graphene, Small 6 (18) (2010) 2010–2019.
- [40] R. Otero, F. Hümmelink, F. Sato, S. B. Legoas, P. Thostrup, E. Lægsgaard, I. Stensgaard, D. S. Galvão, F. Besenbacher, Lock-and-key effect in the surface diffusion of large organic molecules probed by stm, Nature materials 3 (11) (2004) 779–782.
- [41] J. L. Morrison, R. Breitling, D. J. Higham, D. R. Gilbert, A lock-and-key model for protein–protein interactions, Bioinformatics 22 (16) (2006) 2012–2019.
- [42] E. M. Pérez, N. Martín,  $\pi$ - $\pi$  interactions in carbon nanostructures, Chemical Society Reviews 44 (18) (2015) 6425–6433.
- [43] A. V. Savin, R. A. Sakovich, M. A. Mazo, Using spiral chain models for study of nanoscroll structures, Physical Review B 97 (16) (2018) 165436.
- [44] D. Umadevi, G. Narahari Sastry, Graphane versus graphene: a computational investigation of the interaction of nucleobases, aminoacids, heterocycles, small molecules (co2, h2o, nh3, ch4, h2), metal ions and onium ions, Phys. Chem. Chem. Phys. 17 (2015) 30260–30269. doi:10.1039/C5CP05094D. URL http://dx.doi.org/10.1039/C5CP05094D
- [45] J. Huang, C. H. Wong, Mechanical properties of bundled carbon nanoscroll, Mechanics of Materials 87 (2015) 1–10.
- [46] B. Martins, D. Galvao, Curved graphene nanoribbons: structure and dynamics of carbon nanobelts, Nanotechnology 21 (7) (2010) 075710.
- [47] Y. Li, Boron-nitride nanotube triggered self-assembly of hexagonal boron-nitride nanostructure, Physical Chemistry Chemical Physics 16 (38) (2014) 20689–20696.
- [48] E. Perim, D. S. Galvao, Novel nanoscroll structures from carbon nitride layers, ChemPhysChem 15 (11) (2014) 2367–2371.
- [49] A. I. Siahlo, N. A. Poklonski, A. V. Lebedev, I. V. Lebedeva, A. M. Popov, S. A. Vyrko, A. A. Knizhnik, Y. E. Lozovik, Structure and energetics of carbon, hexagonal boron nitride, and carbon/hexagonal boron nitride single-layer and bilayer nanoscrolls, Physical Review Materials 2 (3) (2018) 036001.
- [50] W. Guo, W. Zhong, Y. Dai, S. Li, Coupled defect-size effects on interlayer friction in multiwalled carbon nanotubes, Physical Review B 72 (7) (2005) 075409.
- [51] I. Lebedeva, A. Knizhnik, A. Popov, Y. E. Lozovik, B. Potapkin, Dissipation and fluctuations in nanoelectromechanical systems based on carbon nanotubes, Nanotechnology 20 (10) (2009) 105202.