

Spectral signatures of a unique charge density wave in Ta₂NiSe₇

Matthew D. Watson,^{1,*} Alex Louat,¹ Cephise Cacho,¹ Sungkyun Choi,^{2,3} Young Hee Lee,^{2,4} Michael Neumann,^{2,3} and Gideok Kim^{2,3}

¹*Diamond Light Source Ltd, Harwell Science and Innovation Campus, Didcot, OX11 0DE, UK*

²*Center for Integrated Nanostructure Physics (CINAP),*

Institute for Basic Science (IBS), Suwon 16419, Republic of Korea

³*Sungkyunkwan University, Suwon 16419, Republic of Korea*

⁴*Department of Energy Science, Sungkyunkwan University, Suwon 16419, Republic of Korea*

(Dated: June 12, 2023)

Charge Density Waves (CDW) are commonly associated with the presence of near-Fermi level states which are separated from others, or "nested", by a wavevector of \mathbf{q} . Here we use Angle-Resolved Photo Emission Spectroscopy (ARPES) on the CDW material Ta₂NiSe₇ and identify a total absence of any plausible nesting of states at the primary CDW wavevector \mathbf{q} . Nevertheless we observe spectral intensity on replicas of the hole-like valence bands, shifted by a wavevector of \mathbf{q} , which appears with the CDW transition. In contrast, we find that there is a possible nesting at $2\mathbf{q}$, and associate the characters of these bands with the reported atomic modulations at $2\mathbf{q}$. Our comprehensive electronic structure perspective shows that the CDW-like transition of Ta₂NiSe₇ is unique, with the primary wavevector \mathbf{q} being unrelated to any low-energy states, but suggests that the reported modulation at $2\mathbf{q}$, which would plausibly connect low-energy states, might be more important for the overall energetics of the problem.

Introduction

Charge density wave (CDW) instabilities, originally formulated by Peierls for a single 1D band at half-filling, can be naively generalised to real materials by the concept of Fermi surface nesting (FSN) [1–3]. If some portions of the Fermi surface can be mapped to others by a wavevector \mathbf{q} , a joint electronic and lattice instability with that periodicity can occur when a finite electron-phonon coupling is considered. However it has been argued that the FSN picture is very often

* matthew.watson@diamond.ac.uk

insufficient to understand the emergence of charge density waves (CDWs) in real materials, and that the momentum-dependence of the electron-phonon coupling is equally, if not more, important [4–7]. Still, for the CDW to be energetically favourable, one would generically expect at least some low-energy states to be separated by the CDW wavevector \mathbf{q} , in order for their hybridisation in the modulated phase to lead to an overall electronic energy gain.

At first glance, the structural phase transition in Ta_2NiSe_7 [8, 9] appears superficially similar to prototypical FSN-driven CDWs as found in e.g. ZrTe_3 [10, 11], with a moderate transition temperature of ~ 63 K, incommensurate periodicity [9], a sharp bump-shaped anomaly in resistivity [12, 13], and sensitivity of T_c to disorder [12, 14, 15]. Several literature reports therefore naively assume the FSN picture to be applicable, and the observed modulations at \mathbf{q} [9] and $2\mathbf{q}$ [16] have been sometimes referred to as “ $2k_F$ ” and “ $4k_F$ ” respectively [14]. However, there is actually a lack of support for this scenario from an electronic structure perspective. Early tight-binding models [17] and recent DFT calculations [13, 18], as well as transport measurements [12, 13], agree that the starting point is a semimetal with small hole- and electron-like Fermi surfaces, very far from the Peierls paradigm of a single metallic band at half-filling. Furthermore, the Fermi surfaces inferred from semimetallic-like magnetotransport behaviour [12] and calculations [12, 13, 18] are small, seemingly inconsistent with the ordering at a large wavevector of $\mathbf{q}=(0,0.483,0)$. Thus, the driving force for the incommensurate CDW in Ta_2NiSe_7 cannot be easily ascribed to a FSN-driven CDW, while the $2q$ structural modulation [16] is another intriguing component, previously only reported in organics [19].

In this work, we reveal the 3D Fermi surface of Ta_2NiSe_7 using high-resolution ARPES and confirm the scenario of small hole- and electron-like Fermi surfaces. Importantly, we identify the total absence of any plausible nesting of states at \mathbf{q} . We nevertheless observe a backfolding of valence bands in the CDW phase by a wavevector of \mathbf{q} , with the backfolded bands appearing in a projected band gap. Thus Ta_2NiSe_7 exhibits the extremely peculiar phenomenology of a prominent backfolding of spectral weight with a wavevector that does not seem to connect any low energy states. However, we find that there is a possible nesting at $2\mathbf{q}$, and associate the characters of these bands with the reported atomic modulations at $2\mathbf{q}$. The results lead us to speculate that the CDW may be best understood as a unique instability involving both \mathbf{q} and $2\mathbf{q}$, suggesting an intricate and unique microscopic mechanism that qualitatively differs from the paradigmatic CDW materials.

Results

The structure of Ta_2NiSe_7 consists of three distinct chains, as shown in Fig. 1(a). The Ta1 atoms

have bicapped trigonal prismatic coordination (BTP), similar to trichalcogenides such as TaSe₃ [20], forming double-chain units. The Ta₂ sites take octahedral (OCT) coordination (as in 1T-TaSe₂), and also form double chains of edge-sharing octahedra, akin to those found in Ta₂NiSe₅. In between, Ni atoms form chains of extremely distorted octahedra (d-OCT) with substantially varying bond lengths. The seven Se sites are all inequivalent, leading to a rich structure in measurements of the Se 3d core levels (Supplemental Information, [21]).

While possessing the quasi-1D chain structures along b , Ta₂NiSe₇ can also be considered a 2D material, with a staggered van der Waals gap which yields neutral cleavage in the $b - c$ plane. However the sawtooth-like structure gives an intrinsically three-dimensionality to the system, and some relatively short interlayer Se-Se distances allow for some inter-layer hopping, meaning the 3D character is also important, both structurally and electrically. Thus one might fairly describe the dimensionality as "1+1+1D", or a "dimensional hybrid" [22]. The layers stack according to the a axis, orthogonal to b but not to c , and the overall structure is described by a centered monoclinic space group $C2/m$ (number 12).

Substitution of Ni for Pt to form Ta₂PtSe₇ was reported in the original synthesis paper of Sunshine and Ibers [8], but no further stoichiometries have been reported in this "217" structure. Structural similarities with FeNb₃Se₁₀ were previously mentioned [9, 15], but a more contemporary analogy is with Ta₄Pd₃Te₁₆, recently discovered to exhibit both an incommensurate CDW and superconductivity [22–25], which has the same space group as Ta₂NiSe₇ and similarly contains two distinct Ta chains.

We measured the resistivity of our samples to characterise the T_c and their overall quality. For the sample presented in Fig. 1(b), we find T_c , defined by the peak in $d\rho/dT$, at 59.5 K, and a residual resistivity ratio (RRR) of 5.2; a second sample (not plotted) showed slightly lower values of 58.8 K and 4.54 respectively [21]. These values align well with the literature [12] and indicate a good sample quality, albeit that some previous samples achieved slightly improved purity with T_c up to 62.5 K [13] or 63 K [14]. There is a slight hysteresis in the temperature-dependent resistivity, which has been also observed in previous measurements [12, 15] and discussed as an impurity-related effect [26].

To give an overview of the electronic structure, we present the calculated density of states in Fig. 1(c). The occupied states have primarily Se $4p$ and some Ni $3d$ character. Interestingly, the DOS exhibits a pronounced dip near E_F , although remaining ungapped. Conceptually, this can be attributed to a slight overlap of the topmost Se/Ni-derived valence band and the bottom-most

Ta2-derived conduction bands [17]. For the rest of this paper we focus on these low-energy states at and near E_F , but we emphasise that the global picture for the normal state electronic structure of Ta₂NiSe₇ is certainly a semimetal.

For an in-depth understanding of the 3D Fermi surface, it is first necessary to consider the somewhat complex geometry of the Brillouin zone, shown in Fig. 2(a). From the Γ point, a path along the chain direction, k_{ch} direction first intersects the Brillouin zone boundary and then encounters the Y point at $(0, 2\pi/b, 0)$. Note that although we use the notation of the conventional unit cell for describing the real space lattice and the CDW ordering wavevector, for convenience and consistency with previous studies, in k -space it is essential to consider the primitive reciprocal lattice vectors and correct Brillouin zone. Importantly, Fig. 2(a) shows that the Y point, outside of the first Brillouin zone, is related to a formally equivalent point Y_1 on the boundary of the first Brillouin zone, by a primitive reciprocal lattice vector translation.

We align our samples such that the k_{ch} direction is parallel to the entrance slit of our analyser. Then the normal protocol for Fermi surface mapping, i.e. rotating the sample perpendicular to the analyser entrance slit, corresponds to a map in the $k_{i.p.}$ - k_{ch} plane. Here $k_{i.p.}$ is the in-plane direction, parallel to the c axis of the real space structure, however in reciprocal space this is not any kind of high-symmetry direction, instead corresponding to the cut shown by the 2D and 3D projections of the calculated Fermi surface in Fig. 2(d). With the photon energy tuned to a bulk Γ point, and remaining within the first Brillouin zone, we can use this geometry to nicely map the the larger hole-like Fermi surface around Γ in Fig. 2(e), revealing a shape consistent with the calculations. Since $k_{i.p.}$ is not a high-symmetry direction in k -space, however, this direction is somewhat awkward to make use of, as it will not strictly intersect any other high-symmetry points, and it becomes an even more complicated cut to interpret outside of the first Brillouin Zone. A related feature of the Ta₂NiSe₇ structure is that there is no rotational or mirror symmetry about the normal to the the cleavage plane, as seen by the lack of symmetry in Fig. 2(e) (i.e. positive and negative $k_{i.p.}$ are not equivalent). Thus, azimuthal rotation of the sample by 180 degrees - typically an innocuous operation on needle-like samples - does not result in equivalent spectra, as explained further in the SI [21].

Since the calculations shown in Fig. 2(b,c) predict a 3D electronic structure, and additionally $k_{i.p.}$ is not the most intuitive direction to probe in this case, it is especially important to make full use of the out-of-plane direction, k_{\perp} , which at normal emission corresponds to a path along Γ - Y_1 - Γ . Relying on the nearly free electron final state model, (which seems to work adequately

in this case), k_{\perp} becomes experimentally accessible by varying the photon energy in our ARPES experiment. After performing the standard conversion to k_{\perp} , in Fig. 2(f) we present the Fermi surface as projected in the $k_{\perp} - k_{ch}$ plane. We find periodic structure, matching the expected stacking of the 3D Brillouin zones for this cut. The data reveals a larger Fermi pocket centered around each Γ point. Taken together with Fig. 2(e), this confirms the 3D character of the hole pocket by its dispersion in the $k_{ch}, k_{i.p.}$ and k_{\perp} directions.

The data in Fig. 2(f) also shows streaks of intensity near the Y and Y_1 points, consistent with the electron-like Fermi surface expected from calculations. The corresponding dispersions are shown in Fig. 2(g-i), where at the Y point, and more clearly at the Y_1 points, we observe a fully occupied hole-like band, above which a small electron-like dispersion reaches up to E_F . Despite best efforts, this band always appears somewhat broadened and poorly-resolved compared with the sharp hole bands at Γ . We understand this principally as an effect of k_{\perp} -averaging [27, 28], not helped by a weak matrix element, but an electron-like band is consistently observed around each Y or Y_1 point.

Overall we find that the experimental closely matches the calculated 3D Fermi surface, and qualitatively at least, we confirm the scenario that Ta_2NiSe_7 is a semimetal with relatively small, 3D, hole- and electron-like Fermi pockets, as implied by transport measurements [12, 13]. There are a few notable differences, however, between the calculations and the experiment. Although the band structure at the Γ point seems to agree well with the calculation, the outermost k_F of the hole pocket $k_{F,ch}$ is smaller in experiment (0.18 \AA^{-1}) than in the calculation (0.27 \AA^{-1}). Moreover, the agreement at the Y (or Y_1) point is less good; the calculation implies that the Ta2-derived conduction band dips below the uppermost valence band at Y, opening a hybridisation gap, whereas experimentally it appears as if the conduction band sits entirely above the topmost valence band (see Fig. SI3 in [21]). These differences might be explained, at least partially, by the fact that DFT typically underestimates the band gaps in semiconductors, and by extension, overestimates the band overlap in semimetals. Here we chose the mBJ potential, developed specifically for better estimates of the band gaps, which is known to improve the agreement with experimental data in several semimetals and specifically Ta_2NiSe_5 [29], but residual inaccuracies on the $\sim 100 \text{ meV}$ scale may remain.

We now turn to the principal signature of the CDW in our ARPES measurements, namely the appearance of backfolded spectral weight at low temperatures, shown in Fig. 3(a). The backfolded bands appear as near-copies of the bands observed at $\bar{\Gamma}$, with the displacement being consistent

with the reported CDW wavevector $\mathbf{q}=(0, 0.483b^*, 0)$. The backfolded bands appear in a projected band gap between $\bar{\Gamma}$ and \bar{Y} , i.e. an empty region where there are no states at any k_{\perp} above T_c , as shown in Fig. 3(b). Fig. 3(d,e) shows that the backfolded spectral weight onsets at (or very close to) T_c .

In broad terms, the appearance of backfolded bands in ARPES can be either associated with electronic hybridisation, or structural replicas due to an imposed superstructure, in which case either Umklapp scattering of the initial state due to the new periodicity or diffraction of the photoelectron final state can yield similar spectra. A famous example of backfolding due to electronic hybridisation would be TiSe_2 , where in the $2\times 2\times 2$ ground state the hole bands from Γ appear as backfolded at the L point of the Brillouin zone [30]. However in that case the backfolded bands bear the signatures of electronic hybridisation with a flattening of the dispersion around the band maxima, and the intensity of the backfolded bands is bright, but decays away from the band maximum. The replica bands observed in graphene grown on various substrates, however, are usually interpreted in terms of diffraction replicas [31], and typically show approximately uniform intensity along the length replica dispersion, over $\sim\text{eV}$ energy scales.

The observed replica bands here appear over a wide energy scale: they can be traced from the Fermi level down to at least -0.6 eV below E_F , where their spectral weight then merges with deeper-lying bands. This high energy scale seems at odds with the temperature scale of the phase transition at 60 K , and furthermore the quantitative ratio of spectral weight which is backfolded is low ($\sim 6\%$). This evidence suggests that the origin of the backfolded spectral weight is either Umklapp scattering of the initial state, or diffraction of the photoelectron final state. These scenarios are notoriously hard to distinguish [31], and we are unable to make a conclusive statement on the origin in this case.

Independent of the mechanism giving rise to the backfolded spectral weight, in the context of a CDW material, it is unusual and interesting that the bands which are backfolded by the wavevector \mathbf{q} don't appear to be linked to an electronic hybridisation mechanism. However, it is worth observing that the main band which is backfolded by the wavevector \mathbf{q} , i.e. the outer hole band at Γ , has dominantly Ni character (Fig. 3(c)). Interestingly, the calculation in Fig. 3(c) suggests that the proportion of Ni weight along the band increases at higher binding energies, while the data in Fig. 3(a) shows a somewhat stronger backfolding at higher binding energies, suggesting a correlation between the Ni character and the degree of backfolding. Indeed, it makes sense for this band to experience Umklapp scattering by \mathbf{q} , because the band derives from Ni atoms (and some

Se) that also undergo a periodic lattice distortion with wavevector \mathbf{q} .

The fact that the bands that are replicated from Γ appear in a projected bandgap that is completely void of states above T_c underlines the central puzzle of Ta_2NiSe_7 - that there are simply no low energy states in the high temperature phase that are linked by the wavevector \mathbf{q} . We summarise the situation in Fig. 4. Relying on the data presented thus far for the occupied states, and the earlier calculations in Fig. 2(c) for the unoccupied states, we can state with confidence that there are no states within at least 0.4 eV of the Fermi level on either side that can possibly be linked by the wavevector \mathbf{q} . Nevertheless, the modulation at \mathbf{q} observed in previous scattering experiments is manifested here by the backfolding of bands by \mathbf{q} . However, the experimental electronic structure does provide one more clue that is likely to be linked to the overall understanding of the phase transition. Namely, there are states which can be linked by the wavevector $2\mathbf{q}$, and in Fig. 4 we draw a possible connection between two Ta2-derived states: the previously-identified conduction band at Y/Y_1 , and a peak in the spectral weight at Γ that corresponds to another barely-occupied electron-like dispersion (see Fig. 2(c) and [21]). Notably, the only significant atomic modulation at $2\mathbf{q}$ identified in Ref. [16] was the longitudinal motion of the Ta2 sites. Therefore, although we have not explicitly found energy gaps appearing on these states, we are led to speculate that the energy gain that drives the CDW might originate primarily from the $2\mathbf{q}$ modulation on the Ta chains, rather than the \mathbf{q} modulation on the Se and Ni sites. Supporting evidence that the $2\mathbf{q}$ order might play a leading role comes from the observation in Ref. [16] that the fluctuations associated with the $2\mathbf{q}$ order persist up to 200 K, while the fluctuations at \mathbf{q} can only be seen just above T_c . Although a full microscopic understanding is not within the scope of this experimental paper, we suggest that the $2\mathbf{q}$ ordering, and the Ta2 electron-like dispersions, may be the key to understanding the energetics of this unusual CDW.

Discussion

Comparing Ta_2NiSe_7 with the famous "215" stoichiometry, Ta_2NiSe_5 , there are similarities in that both are semimetals in their high-temperature phases (at least, according to DFT), and in both cases the conduction band(s) derives from a slight occupation of Ta $5d$ states. However, the nature of the resulting structural instabilities are very different in the two cases. In Ta_2NiSe_5 there is a $\mathbf{q} = 0$ orthorhombic-monoclinic structural distortion at a much higher temperature of 326 K in which a hybridisation between hole and conduction states in the low-temperature phase opens an energy gap of ~ 0.16 eV, with ongoing debate over the role of excitonic interactions in driving the transition [29, 32–34]. In contrast, in Ta_2NiSe_7 the ordering wavevector \mathbf{q} (and $2\mathbf{q}$) is finite and

incommensurate, with the system remaining metallic below T_c .

Our measurements were unable to detect direct evidence for any energy gaps opening at the Fermi level. We make the caveat that, although there is no gap resolved at the outer k_F of the hole pocket in the high-symmetry plane where the data is relatively sharp, the 3D character of the hole-like Fermi surfaces might further obscure more subtle signatures especially if located at non-zero k_\perp . Furthermore, we cannot exclude a gap forming on the Ta2-derived conduction band at Y, due to the low spectral weight, and subtle energy gaps on the scale of a few meV cannot be excluded due to the finite energy resolution. Another possibility is that the energy gap might lie primarily above E_F [35].

The transport measurements of Ta_2NiSe_7 might help to understand the absence of an observable CDW gap. The absolute deviation of the resistivity at T_c is fairly modest, as shown in Fig. 1(c), and the carrier densities remain relatively constant through T_c [12]. This would seem to imply that the majority of states at E_F remain ungapped and may be relatively unperturbed by the CDW. This situation is not without precedent; 1T-VSe₂ has a CDW which also manifests as a bump-like anomaly in resistivity at the onset of the CDW [36], but in that case as well, ARPES results on the bulk material have so far failed to reveal any energy gaps at E_F [6].

As for the prediction that Ta_2NiSe_7 could be a $Z_4 = 3$ 3D topological insulator [37], we comment that we have not observed any surface states in Ta_2NiSe_7 . An important consideration is that the DFT-based predictions of Ref. [37], using the standard generalized gradient approximation (GGA), substantially overestimate the degree of overlap between the Ni/Se hole-like bands and the Ta2 electron-like bands, compared with either our calculations using the mBJ potential, or with the experimental data, which could potentially alter the topological assignments. Nevertheless, the topological viewpoint on Ta_2NiSe_7 remains of interest and further calculations would be desirable, in order to confirm any topological characteristics of the band structure, in combination with the data shown here.

The unusual CDW in Ta_2NiSe_7 merits much further examination. For example, besides one study of Ni doping [14], it remains an open question to what extent the CDW can be tuned with chemical substitution, pressure, or strain. Given that the end compound is already reported to be stable [8], studying $\text{Ta}_2(\text{Ni}_{1-x}\text{Pt}_x)\text{Se}_7$ seems like a promising new avenue, while the chain-like structures make the system amenable to strain studies, which may be able to tune the band overlap. The early low-temperature scanning tunneling microscopy measurements yielded controversial results [38], but with modern atomic resolution systems one ought to be able to resolve the separate

\mathbf{q} and $2\mathbf{q}$ modulations residing on the Ni and Ta2 chains. Our interpretation leans heavily on the crystallographic work of Ref. [16] which first shed light on the $2\mathbf{q}$ modulation; reproducing and extending this with a systematic temperature-dependence seems a high priority for future studies. Inelastic x-ray scattering would also be highly informative, in order to establish which (if any) phonon modes soften at T_c , and at which \mathbf{q} . Most of all, our work clearly calls for in-depth *ab initio* studies to help develop a more microscopic framework for understanding the experimental results, particularly calculations of the electronic susceptibilities and k -dependent electron-phonon coupling [4, 6, 39].

In conclusion, we have experimentally determined the 3D Fermi surface and electronic structure of Ta_2NiSe_7 . We find small hole- and electron-like pockets, closely resembling our calculations. Importantly, our results show there is no possible nesting of any bands near E_F for the primary CDW wavevector, \mathbf{q} . Nevertheless below T_c , we observe backfolding of bands with mixed Ni and Se character by the wavevector \mathbf{q} , with the spectral weight transfer likely to be of structural origin (i.e. Umklapp scattering of the initial state, or perhaps scattering of the photoelectron final state) rather than reflecting an electronic hybridisation. In contrast, there is a possible nesting of states with Ta2 character with the wavevector $2\mathbf{q}$, aligning with the literature result that displacements associated with the $2\mathbf{q}$ modulation are dominantly on the Ta2. In the absence of any plausible energy gain from states linked by \mathbf{q} , we speculate that the $2\mathbf{q}$ component may play a key role in stabilising the order, although further experimental and theoretical work is called for to fully establish the role of the $2\mathbf{q}$ ordering. However, at the Fermi level, we do not resolve any changes through T_c and the CDW gap remains elusive. Our results establish the CDW in Ta_2NiSe_7 as a highly unusual case where the ordering at \mathbf{q} seems unrelated to any low energy electronic states, raising the intriguing possibility of a critical role for the $2\mathbf{q}$ ordering.

Methods

Single crystals were grown by a chemical vapor transport method with 5 at. % excess selenium as the transport agent. A temperature gradient was introduced to the sealed tube with the cold zone temperature 690°C and the hot zone temperature 790°C , and the tube was kept in the furnace for two weeks. ARPES measurements were performed on the HR branch of the I05 beamline of Diamond Light Source [40], using photon energies in the range 30-240 eV, at sample temperatures generally below 10 K except for temperature-dependent runs. DFT calculations were performed on the experimental crystal structure [16] within the Wien2k package [41], using the modified Becke-Johnson (TB-mBJ) functional [42] and accounting for spin-orbit coupling. The TB-mBJ

potential was used as it generally gives a better estimate of the band overlap in semimetals compared with standard GGA or LDA functionals [42], and specifically gives a reasonable description of Ta₂NiSe₅ [29]. 3D Fermi surfaces were plotted using FermiSurfer [43].

Data Availability

The data that support the findings of this study are available from the corresponding author upon reasonable request.

References

- [1] Wilson, J., Di Salvo, F. & Mahajan, S. Charge-density waves and superlattices in the metallic layered transition metal dichalcogenides. *Adv. Phys.* **24**, 117–201 (1975).
- [2] Whangbo, M.-H., Canadell, E., Foury, P. & Pouget, J. P. Hidden Fermi Surface Nesting and Charge Density Wave Instability in Low-Dimensional Metals. *Science* **252**, 96–98 (1991).
- [3] Guster, B., Pruneda, M., Ordejón, P., Canadell, E. & Pouget, J.-P. Evidence for the weak coupling scenario of the Peierls transition in the blue bronze. *Phys. Rev. Materials* **3**, 055001 (2019).
- [4] Johannes, M. D. & Mazin, I. I. Fermi surface nesting and the origin of charge density waves in metals. *Phys. Rev. B* **77**, 165135 (2008).
- [5] Rossmagel, K. On the origin of charge-density waves in select layered transition-metal dichalcogenides. *J. Phys.: Condens. Matter* **23**, 213001 (2011).
- [6] Henke, J., Flicker, F., Laverock, J. & van Wezel, J. Charge order from structured coupling in VSe₂. *SciPost Phys.* **9**, 056 (2020).
- [7] Zhu, X., Cao, Y., Zhang, J., Plummer, E. W. & Guo, J. Classification of charge density waves based on their nature. *Proc. Natl. Acad. Sci.* **112**, 2367–2371 (2015).
- [8] Sunshine, S. A. & Ibers, J. A. Synthesis, structure, and transport properties of tantalum nickel selenide (Ta₂NiSe₇) and tantalum platinum selenide (Ta₂PtSe₇). *Inorg. Chem.* **25**, 4355–4358 (1986).
- [9] Spijkerman, A., Meetsma, A., de Boer, J. L., Gao, Y. & van Smaalen, S. Modulated structure of NiTa₂Se₇ in its incommensurate charge-density-wave state at 16 K. *Phys. Rev. B* **52**, 3892–3899 (1995).
- [10] Zhu, X. *et al.* Superconductivity and Charge Density Wave in ZrTe_{3-x}Se_x. *Sci Rep* **6**, 26974 (2016).
- [11] Hoesch, M., Bosak, A., Chernyshov, D., Berger, H. & Krisch, M. Giant Kohn Anomaly and the Phase Transition in Charge Density Wave ZrTe₃. *Phys. Rev. Lett.* **102**, 086402 (2009).
- [12] He, J. *et al.* Band dependence of charge density wave in quasi-one-dimensional Ta₂NiSe₇ probed by orbital magnetoresistance. *Appl. Phys. Lett.* **111**, 052405 (2017).
- [13] He, J. *et al.* Angle-dependent magnetoresistance as a sensitive probe of the charge density wave in quasi-one-dimensional semimetal Ta₂NiSe₇. *Appl. Phys. Lett.* **113**, 192401 (2018).
- [14] Lüdecke, J., Riedl, E., Dierl, M., Hosseini, K. & van Smaalen, S. Influence of niobium on the charge-

- density-wave transition of $\text{Ni}(\text{Ta}_{1-x}\text{Nb}_x)_2\text{Se}_7$. *Phys. Rev. B* **62**, 7057–7062 (2000).
- [15] Fleming, R. M., Sunshine, S. A., Chen, C. H., Schneemeyer, L. F. & Waszczak, J. V. Defect-inhibited incommensurate distortion in Ta_2NiSe_7 . *Phys. Rev. B* **42**, 4954–4959 (1990).
- [16] Lüdecke, J., Schneider, M. & van Smaalen, S. Independent $q \rightarrow$ and $2q \rightarrow$ Distortions in the Incommensurately Modulated Low-Temperature Structure of NiTa_2Se_7 . *Journal of Solid State Chemistry* **153**, 152–157 (2000).
- [17] Canadell, E. & Whangbo, M. H. Metallic versus nonmetallic properties of ternary chalcogenides: Tantalum metal selenide, Ta_2MSe_7 (M = nickel, platinum), and tantalum nickel chalcogenide, Ta_2NiX_5 (X = sulfide, selenide). *Inorg. Chem.* **26**, 3974–3976 (1987).
- [18] Chen, H. & Sun, Z. Phonon dispersion and electronic structure in quasi-one-dimensional layered Ta_2NiSe_7 single crystal. *J. Mater. Chem. C* **9**, 5162–5166 (2021).
- [19] Kagoshima, S., Pouget, J. & Anzai, H. X-Ray Scattering Study of 2kF and 4kF CDW in TMTTF-TCNQ. *J. Phys. Soc. Jpn.* **52**, 1629–1634 (1983).
- [20] Lin, C. *et al.* Visualization of the strain-induced topological phase transition in a quasi-one-dimensional superconductor TaSe_3 . *Nat. Mater.* **20**, 1093–1099 (2021).
- [21] Supplementary Information Placeholder. Tech. Rep.
- [22] Shi, Z. *et al.* Incommensurate two-dimensional checkerboard charge density wave in the low-dimensional superconductor $\text{Ta}_4\text{Pd}_3\text{Te}_{16}$. *Phys. Rev. Research* **2**, 042042 (2020).
- [23] Jiao, W.-H. *et al.* Superconductivity in a Layered $\text{Ta}_4\text{Pd}_3\text{Te}_{16}$ with PdTe_2 Chains. *J. Am. Chem. Soc.* **136**, 1284–1287 (2014).
- [24] Helm, T. *et al.* Thermodynamic anomaly above the superconducting critical temperature in the quasi-one-dimensional superconductor $\text{Ta}_4\text{Pd}_3\text{Te}_{16}$. *Phys. Rev. B* **95**, 075121 (2017).
- [25] Yang, H. F. *et al.* Observation of electronic structure and electron-boson coupling in the low-dimensional superconductor $\text{Ta}_4\text{Pd}_3\text{Te}_{16}$. *Phys. Rev. B* **104**, L220501 (2021).
- [26] Bâldea, I. & Bădescu, M. Quasiregular impurity distribution driven by a charge-density wave. *Phys. Rev. B* **48**, 8619–8628 (1993).
- [27] Strocov, V. N. Intrinsic accuracy in 3-dimensional photoemission band mapping. *Journal of Electron Spectroscopy and Related Phenomena* **130**, 65–78 (2003).
- [28] Day, R. P., Elfimov, I. S. & Damascelli, A. Looking Beyond the Surface with Angle-Resolved Photoemission Spectroscopy (2021). 2109.13274.
- [29] Watson, M. D. *et al.* Band hybridization at the semimetal-semiconductor transition of Ta_2NiSe_5

- enabled by mirror-symmetry breaking. *Phys. Rev. Research* **2**, 013236 (2020).
- [30] Watson, M. D. *et al.* Orbital- and k_z -Selective Hybridization of Se 4*p* and Ti 3*d* States in the Charge Density Wave Phase of TiSe₂. *Phys. Rev. Lett.* **122**, 076404 (2019).
- [31] Polley, C. M. *et al.* Origin of the π -band replicas in the electronic structure of graphene grown on 4H-SiC(0001). *Phys. Rev. B* **99**, 115404 (2019).
- [32] Baldini, E. *et al.* The spontaneous symmetry breaking in Ta₂NiSe₅ is structural in nature. *Preprint at <https://arxiv.org/abs/2007.02909>* (2020).
- [33] Lu, Y. F. *et al.* Zero-gap semiconductor to excitonic insulator transition in Ta₂NiSe₅. *Nat Commun* **8**, 14408 (2017).
- [34] Fukutani, K. *et al.* Detecting photoelectrons from spontaneously formed excitons. *Nat. Phys.* **17**, 1024–1030 (2021).
- [35] van Efferen, C. *et al.* A full gap above the Fermi level: The charge density wave of monolayer VS₂. *Nat Commun* **12**, 6837 (2021).
- [36] Sayers, C. J. *et al.* Correlation between crystal purity and the charge density wave in 1T VSe₂. *Phys. Rev. Materials* **4**, 025002 (2020).
- [37] Vergniory, M. G. *et al.* All topological bands of all nonmagnetic stoichiometric materials. *Science* **376**, eabg9094 (2022).
- [38] Dai, Z., Slough, C. G., McNairy, W. W. & Coleman, R. V. Charge-density-wave formation in Ta₂NiSe₇ studied by scanning tunneling microscopy. *Phys. Rev. Lett.* **69**, 1769–1772 (1992).
- [39] Laverock, J. *et al.* *k*-resolved susceptibility function of 2H-TaSe₂ from angle-resolved photoemission. *Phys. Rev. B* **88**, 035108 (2013).
- [40] Hoesch, M. *et al.* A facility for the analysis of the electronic structures of solids and their surfaces by synchrotron radiation photoelectron spectroscopy. *Rev. Sci. Instrum.* **88**, 013106 (2017).
- [41] Blaha, P. *et al.* WIEN2k: An APW+lo program for calculating the properties of solids. *J. Chem. Phys.* **152**, 074101 (2020).
- [42] Koller, D., Tran, F. & Blaha, P. Improving the modified Becke-Johnson exchange potential. *Phys. Rev. B* **85**, 155109 (2012).
- [43] Kawamura, M. FermiSurfer: Fermi-surface viewer providing multiple representation schemes. *Computer Physics Communications* **239**, 197–203 (2019).

Acknowledgments

We thank T. K. Kim and P. D. C. King for insightful discussions. We acknowledge Diamond

Light Source for time on beamline I05 under proposal NT31067. We would like to thank Gavin Stenning for help on the PPMS2 instrument in the Materials Characterisation Laboratory at the ISIS Neutron and Muon Source. G. K., M. N. and Y. H. L. acknowledge support from the Institute for Basic Science (IBS-R011-D1).

Author Contributions

Crystals were grown and characterised by GK, SC, YHL, and MN. MW, AL and CC performed the ARPES experiments. AL performed the resistivity measurements. MW analysed the data and wrote the paper, with input from all coauthors.

Competing Interests Statement

The authors declare no competing interests.




FIG. 1. Structural and physical properties of Ta_2NiSe_7 . (a) Crystal structure of Ta_2NiSe_7 . The dashed line is the cleavage between Se atoms in adjacent layers. The chains direction is b , and the conventional unit cell is drawn. The metal coordination geometries are: Ta1: bicapped trigonal prismatic (BTP); Ta2: octahedral (OCT); Ni: distorted octahedral (d-OCT). (b) Resistivity measurement; the anomaly establishes a T_c of 59.5 K in this sample. Inset shows the resistivity curve up to 300 K, from which a residual resistivity ratio (RRR) of 5.2 is extracted. (c) Calculated density of states, showing a pronounced dip around E_F highlighted in the inset, but no gap. (d) Projection of the lattice in the ac plane, showing the periodic lattice distortion at \mathbf{q} , predominantly transverse displacement of the Ni and Se2 atoms, and (e) at $2\mathbf{q}$, involving a longitudinal displacement of the Ta2 atoms (see SM for in-plane projections).




FIG. 2. **3D electronic structure of Ta_2NiSe_7 .** (a) Labeled Brillouin zone, showing also the three experimentally-accessible k directions: k_{ch} along the chains, $k_{i,p}$ accessed by in-plane rotation, and k_{\perp} accessed by photon energy dependence. The equivalence of the Y and Y1 points is emphasised by plotting an adjacent zone (purple). (b) 3D Fermi surface; the blue Fermi surface is hole-like, while the green is electron-like. (c) Calculated band dispersions with projection of the dominant atomic character. (d) Calculated Fermi surface in the $k_{i,p} - k_{ch}$ plane, and (e) corresponding experimental measurement, i.e. the Fermi surface map obtained by rotation of the sample. (f) Fermi surface in the $k_{\perp} - k_{ch}$ plane, obtained at $T = 10$ K from $h\nu$ -dependent data (45 to 160 eV) using an inner potential of 17 eV. (g-i) selected high-symmetry dispersions extracted from the k_{\perp} data.




FIG. 3. **Evidence for backfolded spectral weight below T_c .** (a,b) Dispersion along k_{ch} taken at $h\nu = 79$ eV, at temperatures above and below T_c , highlighting the backfolded spectral weight at low temperatures. (c) DFT calculation along the Γ -Y path, highlighting the Ni character that is dominant on the band which is also observed to be backfolded. (d) Temperature-dependent momentum distribution curve (MDC) integrating between -0.15 and -0.11 eV. (e) Integrated intensity between $0.71 < k < 1.10 \text{ \AA}^{-1}$, showing an onset of the backfolded spectral weight close to T_c (dashed line).




FIG. 4. **Composite high-symmetry dispersion.** Data taken around $k_{ch} = 0$ at $h\nu = 95$ eV (Y_1 point), and data from a bulk Γ point (77 eV) shown with k_{ch} values shifted by $1.8040 \text{ \AA}^{-1} = 2\pi/b$, so that the k -path of the figure overall is equivalent to $Y_1 - \Gamma$ (same as Fig. 2(g,i)). A region of enhanced colour scale emphasises the weak intensity of a replica dispersion, corresponding to the fully occupied valence band from Y displaced by a wavevector of $|q| = 0.483(2\pi/b)$. A possible nesting between states with Ta2 character separated by $2q$ is indicated.