Superconductor-insulator transition in *d*-wave superconductors

A.G.Rojo^a and C.A.Balseiro^b

^a The Harrison Randall Labroratory of Physics, The University of Michigan, Ann Arbor, MI 48109-1120

^bCentro Atómico Bariloche, 8400-Bariloche, Argentina

We address the question of whether an anisotropic gap $d_{x^2-y^2}$ symmetry is compatible with localized states in the normal phase. The issue is important in high T_c superconductors where a superconductor to insulator transition is observed in the underdoped regime, together with a number of experiments that support *d*-wave pairing. We find a reentrant behavior of superconductivity in the strongly disorder phase.

PACS numbers: 75.50.Lk, 05.30.-d. 75.40.Gb

There is a growing body of experimental evidence in high Tc superconductors that indicate that the pairing state is of $d_{x^2-y^2}$ symmetry [1]. In superconductors with an anisotropic order parameter, both magnetic and non-magnetic impurities are pair breaking. For d-wave symmetry, the effect of non-magnetic impurities is equivalent to magnetic impurities in s-wave superconductors [2]. Perturbation theory in the impurity scattering introduces a mean free path ℓ for the extended states, and the standard treatment indicates that anisotropic superconductivity is destroyed when $\xi/\ell \simeq 0.1$ [3], with ξ the coherence length. The situation is somewhat different for the so called extended s-wave symmetry. This corresponds to an order parameter with uniform sign which could, in particular, vanish at certain \mathbf{k} directions [4]. Point impurities are not pair-breaking in this case, but they are "pair-weakening": for small impurity concentration $n_{\rm imp}$, T_c decreases linearly with $n_{\rm imp}$, but the critical impurity concentration is $n_{\rm imp}^{\rm (cr)} \rightarrow \infty$. On the other hand, charge dynamics in oxide superconductors is basically two-dimensional, and it is known from the scaling theory of localization that in two dimensions all the one particle states are localized [5]. Actually, the experimental evidence from resistivity measurements for low-doping is consistent with a divergent resistivity as $T \rightarrow 0$ that is cut-off by the superconducting transition [6]. The resistivity shows an upturn at a characteristic temperature T_{\min} that is apparent when $T_c < T_{\min}$. Qualitatively, T_{\min} corresponds to the temperature scale for which the inelastic scattering length is comparable to the localization length. Conversly, if the *elastic* mean free path is much bigger than the coherence length, then $T_c > T_{\min}$ the localization effects are not important, and the variation of T_c with disorder will be given by the usual pair breaking expressions. In the regime of $T_c < T_{\min}$, it is clear that superconductivity establishes at a temperature low enough for the effects of localization to be of importance. The purpose of the present work is to present a treatment of anisotropic superconductivity that incorporates the fact that states from which the superconducting state is built up are localized, and reconcile two seemingly conflicting properties: the observed insulator-superconductor transition, and anisotropic pairing. We also discuss a new prediction that emerges from our theory regarding reentrant superconducting to insulating transition at low temperatures.

For concreteness we consider fermions on a lattice described by the following Hamiltonian

$$H = H_0 - U \sum_x \hat{\Delta}_x^{\dagger} \hat{\Delta}_x, \qquad (0.1)$$

with H_0 being a one-electron Hamiltonian that includes disorder, with eigenstates $\varphi_{\nu}(x)$ and eigenvalues ε_{ν} . The second term in (0.1) corresponds to an instantaneous attractive interaction with an implicit cutoff at a characteristic energy ω_D . In order to model $d_{x^2-y^2}$ symmetry we choose $\hat{\Delta}_x^{\dagger}$ of the form

$$\hat{\Delta}_{x}^{\dagger} = \frac{1}{\sqrt{2}} \sum_{\delta} \epsilon_{\delta} \left(c_{x\uparrow}^{\dagger} c_{x+\delta\downarrow}^{\dagger} - c_{x\downarrow}^{\dagger} c_{x+\delta\uparrow}^{\dagger} \right), \qquad (0.2)$$

with $\delta = \pm \mathbf{e}_1, \pm \mathbf{e}_2$ being the lattice versors, and $\epsilon_{\pm \mathbf{e}_1} = -\epsilon_{\pm \mathbf{e}_2} = 1$. We argue below that the effects of localization on the critical temperature T_c for *d*-wave pairing are qualitatively the same as those for *p*-wave pairing, an example of which is the spin polarized phase [7], that we model with $\hat{\Delta}^{\dagger}_{x\sigma} = \sum_{\delta} \epsilon'_{\delta} c^{\dagger}_{x\sigma} c^{\dagger}_{x+\delta\sigma}$; $\epsilon_{+\mathbf{e}_1} = -\epsilon_{-\mathbf{e}_1} = 1$, and $\epsilon_{+\mathbf{e}_2} = \epsilon_{-\mathbf{e}_2} = 0$.

The critical temperature is determined by the self consistent solution of the following linearized gap equation [8]

$$\Delta_x = \sum_{x'} K(x, x') \Delta_{x'}, \tag{0.3}$$

where $\Delta_x = \langle \hat{\Delta}_x \rangle$, and the kernel K, written in terms of the exact eigenstates of H_0 is given by

$$K(x,x') = U\frac{T}{2} \sum_{\omega_n} \sum_{\mu\nu\delta\delta'} \epsilon_{\delta}\epsilon_{\delta'} \frac{\varphi_{\mu}^*(x)\varphi_{\nu}^*(x+\delta)\varphi_{\nu}(x')\varphi_{\mu}(x'+\delta)}{(\varepsilon_{\nu}-i\omega_n)(\varepsilon_{\mu}+i\omega_n)}$$
(0.4)

with T the temperature and $\omega_n = (2n+1)\pi T$ the Matsubara frequencies. Also, we have taken $\hbar = k_B = 1$. From now on we will take the eigenstates as real.

We next assume that the gap is uniform, $\Delta_x = |\Delta|$, which is justified for $\omega_D \gg \Delta W$, with ΔW the typical level spacing between states within a localization length of each other. In that case we can integrate (0.4) over x and x' and reach the condition

$$1 = \frac{T}{2} N_F U \int d\xi d\xi' \sum_{\omega_n} \frac{g(\xi - \xi')}{(\xi' + i\omega_n)(\xi - i\omega_n)}$$
(0.5)

with N_F the density of states at the Fermi level, and $g(\omega)$ is the power spectrum of the operator $\hat{D} = \sum_{x,\delta} \epsilon_{\delta} \left(|x+\delta\rangle\langle x| + |x\rangle\langle x+\delta| \right)$, given by

$$g(\omega) = \sum_{\nu} \overline{|\langle \mu | \hat{D} | \nu \rangle|^2} \delta(\varepsilon_{\nu} - \varepsilon_F - \omega), \qquad (0.6)$$

where the symbol represents an average over states μ such that $\varepsilon_{\mu} = \varepsilon_F$. For *s*-wave symmetry, \hat{D} corresponds to the density operator $\hat{D} = \sum_x |x\rangle \langle x|$, and $g(\omega) = \delta(\omega)$, since the density response is not sensitive to scattering (in the q = 0 limit, which is our case of interest). This is valid even when the states $\varphi_{\nu}(x)$ are localized. With this frequency dependence of $g(\omega)$ replaced in Eq. (0.5) one obtains an equation for the critical temperature identical to that of the pure system. This is the extension of the Anderson theorem to the case of localized states, which was discussed by Ma and Lee using a variational approach [9]. We conclude that under the above assumptions ($\omega_D \gg \Delta W$ and uniform gap), the effects of localization on the critical temperature are contained, through Eq.(0.5), on the frequency dependence of spectral function of the operator that has the symmetry of the order parameter. The function $g(\omega)$ can be calculated diagramatically, since it is given by a two-particle bubble with bare vertices $\gamma_{\mathbf{k}}^d = \cos k_x - \cos k_y$ for *d*-wave, and $\gamma_{\mathbf{k}}^p = i \sin k_x$ for *p*-wave symmetry. From now on we ignore the lattice effects, and take $\gamma_{\mathbf{k}}^d = \cos 2\theta_{\mathbf{k}}$, which corresponds to a gap function $\Delta(\mathbf{k}) = \Delta(T) \cos 2\theta_{\mathbf{k}}$.

We first write Eq. (0.6) as

$$g(\omega) = \frac{1}{2\pi^2} \operatorname{Re} \sum_{\mathbf{k}, \mathbf{k}'} \cos 2\theta_{\mathbf{k}} \Phi_{\mathbf{k}, \mathbf{k}'}(\omega) \cos 2\theta_{\mathbf{k}'} , \qquad (0.7)$$

with

$$\Phi_{\mathbf{k},\mathbf{k}'} = \langle G^{\mathrm{R}}(\mathbf{k},\mathbf{k}';\varepsilon_F)G^{\mathrm{A}}(\mathbf{k}',\mathbf{k},\varepsilon_F+\omega) \rangle , \qquad (0.8)$$

where now $\langle \ldots \rangle$ denotes impurity average. We follow the work of Vollhardt and Wölfle (VW) [10], and compute $g(\omega)$ within the self-consistent theory of localization. We prove that the frequency dependence of (0.7) is essentially the same as that of the conductivity. The quantity $\Phi_{\mathbf{k},\mathbf{k}'}$ obeys the Bethe–Salpeter equation

$$\Phi_{\mathbf{k},\mathbf{k}'}(\omega) = G_{\mathbf{k}}^{\mathrm{R}} G_{\mathbf{k}}^{\mathrm{A}} \delta_{\mathbf{k},\mathbf{k}'} + G_{\mathbf{k}}^{\mathrm{R}} G_{\mathbf{k}}^{\mathrm{A}} \sum_{\mathbf{k}''} U_{\mathbf{k},\mathbf{k}''}(\omega) \Phi_{\mathbf{k}'',\mathbf{k}'}(\omega) , \qquad (0.9)$$

with $U_{\mathbf{k},\mathbf{k}''}(\omega)$ the *irreducible* vertex function. In Anderson localization, *single*-particle quantities (e.g. the density of states) are smoothly varying functions of disorder. It is then reasonable to approximate the self energy Σ by the lowest order result in the impurity scattering U_0 , and use the Green's functions in the form

$$G_{\mathbf{k}}^{\mathrm{R}}(\varepsilon) = \frac{1}{\varepsilon - \varepsilon_{\mathbf{k}} + \frac{i}{2\tau}} , \qquad (0.10)$$

with, $1/\tau = 2\pi N_F U_0$, and $G^{\rm R} = (G^{\rm A})^*$. We have assumed a δ correlated disordered potential u(x), such that $\langle u(0)u(x)\rangle = u_0^2 n_{\rm imp}\delta(x) = U_0\delta(x)$. Using this expression for the Green's functions we can write the Bethe Salpeter equation as a kinetic equation in the form

$$(\omega - \frac{i}{\tau})\Phi_{\mathbf{k},\mathbf{k}'} = -\Delta G_{\mathbf{k}} \left[\delta_{\mathbf{k},\mathbf{k}'} + \sum_{\mathbf{k}''} U_{\mathbf{k},\mathbf{k}''}\Phi_{\mathbf{k}'',\mathbf{k}'} \right] , \qquad (0.11)$$

with $\Delta G_{\mathbf{k}} \equiv G_{\mathbf{k}}^{\mathrm{R}} - G_{\mathbf{k}}^{\mathrm{A}}$. If we replace in (0.11) the irreducible vertex by the bare vertex U_0 , we obtain

$$g(\omega) = \frac{N_F}{4\pi} \frac{\tau}{1 + (\omega\tau)^2} .$$
 (0.12)

A very similar expression was obtained before in a treatment of the Raman response in the l = 2 channel in the presence of impurities [11]. However, since the Raman response $R(\omega)$ is given by a correlation function, there is an additional factor of ω and $R(\omega) = \omega g(\omega)$. Inserting (0.12) in (0.5), we obtain the well known expression for the critical temperature variation [12] $-\ln(T_c/T_{c0}) = \Psi(1/2 + 1/4\pi\tau T_c) - \psi(1/2)$.

Following VW, we observe that since $\Delta G_{\mathbf{k}}$ is srongly peaked at $k = k_F$, the dependence of $\Phi_{\mathbf{k},\mathbf{k}'}$ on the magnitude of the wave vectors will be dominated by $\Delta G_{\mathbf{k}}$. We define $\Phi_{\mathbf{k}} = \sum_{\mathbf{k}'} \Phi_{\mathbf{k},\mathbf{k}'} \cos 2\theta_{\mathbf{k}'}$, and extract the angular dependence in \mathbf{k} using a Legendre expansion in which we keep up to the l = 2 term:

$$\Phi_{\mathbf{k}} = \frac{\Delta G_{\mathbf{k}}}{-2\pi i N_F} \sum_{\mathbf{k}'} \left[1 + 2\cos\theta_{\mathbf{k}}\cos\theta_{\mathbf{k}'} + 2\cos2\theta_{\mathbf{k}}\cos2\theta_{\mathbf{k}'} \right] \Phi_{\mathbf{k}'} .$$
(0.13)

Multiplying (0.11) by $\cos 2\theta_{\mathbf{k}} \cos 2\theta_{\mathbf{k}'}$, summing over \mathbf{k}, \mathbf{k}' , and using (0.13), we obtain

$$\sum_{\mathbf{k},\mathbf{k}'} \cos 2\theta_{\mathbf{k}} \Phi_{\mathbf{k},\mathbf{k}'} \cos 2\theta_{\mathbf{k}'} = \frac{-i\pi N_F}{\omega - M(\omega)} , \qquad (0.14)$$

where $M(\omega)$ is a "l = 2 relaxation kernel", given by

$$M(\omega) = \frac{i}{\tau} + \frac{i}{\pi N_F} \sum_{\mathbf{k},\mathbf{k}'} \cos 2\theta_{\mathbf{k}} \Delta G_{\mathbf{k}} U_{\mathbf{k},\mathbf{k}'} \Delta G_{\mathbf{k}'} \cos 2\theta_{\mathbf{k}'} .$$
(0.15)

The structure of $M(\omega)$ is very similar to that of the current relaxation kernel. Note that in deriving this expression we have neglected terms that mix different angular dependences in $M(\omega)$, and that give rise to factors $\cos m\theta_{\mathbf{k}} \cos 2\theta_{\mathbf{k}'}$, with m = 0, 1, 2. These terms do not appear in the treatment of VW. Neglecting these terms is justified, since we are anticipating the inclusion of the contribution to the irreducible vertex that originate the divergence of $M(\omega)$. The infrared divergence of M comes from the maximally crossed (MC) diagrams [13], which are irreducible, and contribute with

$$U_{\mathbf{k},\mathbf{k}'}^{\rm MC} = \frac{iU_0/\tau}{\omega + iD_0(\mathbf{k} + \mathbf{k}')^2} , \qquad (0.16)$$

for $\mathbf{k} \simeq -\mathbf{k}'$, and with D_0 the bare diffusion constant. Due to this divergence we can take $\mathbf{k} = \mathbf{k}'$ for the angular integral and the "off-diagonal" contributions vanish due to orthogonality. Using the above $U_{\mathbf{k},\mathbf{k}'}^{\mathrm{MC}}$ in (0.15) we obtain the logarithmic low-frequency divergence $M(\omega) \sim \log \omega$ that is familiar from perturbation theory of the conductivity [14]. Since the low frequency l = 2 kernel is essentially the same as the current relaxation kernel (the angular integrations give the same result), it will still be related to the diffusion constant $D(\omega) = iD_0[M(\omega)\tau]^{-1}$. This allows us to go beyond perturbation theory and determine $M(\omega)$ self consistently through the equation

$$M(\omega) = \frac{i}{\tau} - \frac{2}{\tau} \sum_{\mathbf{k}} \frac{1}{\omega - k^2 D_0 [M(\omega)\tau]^{-1}}$$
 (0.17)

Equation (0.17) can be solved for low frequencies, giving

$$M(\omega) = \frac{i}{\tau} - \frac{\omega_0^2}{\omega} \tag{0.18}$$

and

$$g(\omega) = \frac{N_F}{4\pi} \frac{\tau}{1 + (\widetilde{\omega}\tau)^2} , \qquad (0.19)$$

with $\tilde{\omega} = \omega + \omega_0^2/\omega$. The characteristic frequency ω_0 is finite in the localized phase, and is given by $\omega_0 = v_F/(\sqrt{2}\lambda)$, with *lambda* the localization length. This result implies an expression for the dependence of the critical temperature,

which can be considered as a generalization of the Abrikosov–Gorkov–Maki (AGM) formula for localized anisotropic superconductors. Our result is then

$$\ln(\frac{T_{c0}}{T_c}) = -\ln(\frac{T_{c0}}{\omega_D})\frac{2\tau}{\tau^-} + \frac{\tau}{\tau^+} \left[\psi(\frac{1}{2} + \rho_+) - \psi(\frac{1}{2})\right] - \frac{\tau}{\tau^-} \left[\psi(\frac{1}{2} + \rho_-) - \psi(\frac{1}{2})\right],\tag{0.20}$$

where $1/\tau^{\pm} = \sqrt{\omega_0^2 + (1/2\tau)^2} \pm 1/\tau$, and $\rho_{\pm} = 1/4\pi\tau^{\pm}T_c$.

The above expression gives the change in critical temperature as a function of τ and ω_0 . In contrast with the AGD formula, in our case the relative change in T_c is dependent of the cutoff frequency ω_D . In order to visualize the effects of localization on T_c predicted by our treatment, in Figure 1 we show plots of T_c as a function of τ , treating ω_0 as an independent parameter. In principle these two quantities are not independent, but the plot emphasizes the fact that when $T_c/T_{c0} < 0.1$ there is a reentrant behaviour to a normal phase at very low temperatures. We note that the reentrant behaviour corresponds to a parameter range that is realistic in high Tc oxides. The curves of Figure 1 show that there is reentrant behaviour when $\omega_0 \tau \sim 1$. From the self consistent theory, $\omega_0 \tau = \ell/\sqrt{2\lambda}$, where λ is the localization length. On the other hand $\frac{\lambda}{\ell} = (e^{2k_F\ell} - 1)^{1/2}$. In high T_c oxides, since the particle density is small, $k_F\ell$ can be of order one, and $\omega_0 \tau \sim 1$. We conclude that localization effects are important in high Tc oxides, and that d-wave superconductivity can coexist with Anderson localization.

Finally, we discuss briefly the mechanism underlying the reentrant behavior in T_c . The reentrance to a normal state as temperature decreases can occur if the entropy of the superconducting phase is higher than the entropy of the normal state at very low temperatures. This can happen if the localization length is of the order of the mean free path. In this regime one can estimate the density of states $\rho(E)$ of the quasiparticles by computing the quasiparticle energies E_{ν} as a correction of the *particle* energies ε_{ν} in second order in the pairing interaction [8]. Since states that are degenerate have negligible overlap in the localized phase, we can extract the typical correction to the quasiparticle energy from $g(\omega)$, and obtain

$$\rho(E) = \frac{N_0}{\left|\frac{\partial E}{\partial \varepsilon}\right|} = \frac{N_0}{1 + \frac{\partial}{\partial \varepsilon} \int d\omega \frac{g(\omega)}{\varepsilon + \omega}\Big|_{\varepsilon = E}}.$$
(0.21)

The result is then that the density of states at the fermi energy can be bigger than the normal state density of states, and the superconducting entropy is higher at low temperatures. The behavior of $\rho(E)$ is nonmonotonic in E and on e gets two transitions as temperature increases.

In comparing with experiments one should be able to isolate the effects of hole doping and the effects of disorder. Recent experiments on Bi₂Sr₂Ca(Cu,Co)O_{8+y} [15] it is shown that T_c shows a drastic decrease with increasing disorder and the resistivity shows a minimum suggesting Anderson localization. From angle resolved photoemission it is concluded that the carrier concentration is unchanged, as expected since Co is a 2⁺ ion. Hall effect measurements are also indicate that the carrier concentration does not change [16]. From Ma and Lee's theory [9] one does not expect a big decrease in T_c if the symmetry is *s*-wave, since Anderson theorem still holds if the mobility edge crosses the chemical potential. The fact that T_c is changing in the "coexistence region" between the insulating and superconductivity phases, can be better understood if the symmetry is *d*-wave. The reentrant behaviour has not been measured to our knowledge, and it constitutes a well defined experimental test of the present theory.

In summary, we have shown that d-wave superconductivity is compatible with Anderson localization of the oneparticle states. In addition, out treatment extends previous calculation of the Raman response in disordered systems to the localized phase. We also made the interesting prediction of reentrance to the normal phase as temperature is lowered in the superconducting phase, when disorder is strong.

ACKNOWLEDGMENTS

A.G.R would like to thank C. Balseiro and G. Dussel for their kind hospitality during stays at the Centro Atómico Bariloche and Universidad the Buenos Aires, where part of this work was done, and to L. Jaimovich from the Universidad de Tucumán, Argentina. We also thank K.Levin, Eduardo Fradkin and J. Rasul for discussions.

[1] D. A. Wollman et al., Phys. Rev. Lett. 72, 2134 (1993), C. C. Tsuei et al., Phys. Rev. Lett. 73 593 (1994)

- [2] D. Markowitz and L. P. Kadanoff, Phys. Rev. bf 131 563 (1993), T. Tsuneto, Prog. Thor. Phys. 28 857 (1962) 7
- [3] A. A. Abrikosov and L. P. Gor'kov, Zh, Eksp. Teor. Fiz. **39** 1781 (1960) [Sov. Phys.-JETP **12** 1243 (1961)]. K. Maki, in Superconductivity, edited by R. D. Parks (Marcel Dekker, New York, 1969), Vol. 2.
- [4] R. Feherenbacher and M. R. Norman, Argonne preprint.
- [5] P.A.Lee and T.V.Ramakrisnan, Rev. Mod. Phys. 57, 287 (1985).
- [6] H.Takagi et al., AT &T preprint.
- [7] A. J. Leggett, Rev. Mod. Phys. 47, 331 (1975)
- [8] P. G. de Gennes, Superconductivity of Metals and Alloys (Benjamin, New York, 1966).
- [9] M.Ma and P.A.Lee, Phys. Rev B **32** 5658 (1985)
- [10] D. Vollhardt and P.Wölfle, Phys. Rev. B 22 4666 (1980), D. Wollhardt and P.Wölfle, in *Electronic Phase transitions*, Edited by W. Hanke and Yu. V. Kopaev, Elsiever Science Publishers B.V. (1992).
- [11] A. Zawadowski and M. Cardona, Phys Rev. B 42 10732 (1990).
- [12] R. J. Radtke, K. Levin, H.-B. Schüttler and M. R. Norman, Rev. B, 48, 653 (1993).
- [13] J. S. Langer, and T. Neal, Phys. Rev. Lett. 16, 984 (1966).
- [14] L. P. Gor'kov, A. I. Larkin, and D. E. Khmel'nitskii, JETP Lett. 30, 228 (1979).
- [15] C. Quitmann, P. Almeras, Jian Ma, R.J. Kelley, H. Berger, G. Margaritondo and M. Onellion, Wisconsin preprint.
- [16] See for example A. Maeda, T. Yabe, S. Takebayashi, M. Hase, and K. Uchinokura, Phys. Rev. B 41 4112 (1990).

FIG. 1. Critical temperature vs. inverse scattering time $\Gamma = 1/4\pi\tau T_{c0}$ for fixed values of $\omega_0 = 0$. (solid), 0.1 (dashed), 0.2 (long dashed) 0.25 (dot-dashed).