Symmetry of the Gap Function in High- T_c Superconductors

Mihir Arjunwadkar and D. G. Kanhere

Department of Physics, University of Poona, Pune 411 007, India

G. Baskaran and Rahul Basu[‡]

The Institute of Mathematical Sciences, Madras 600 113, India (December 15, 1994 (revised 30 January 1995))

One of the most debated issues related to high- T_c superconductivity is the symmetry of the Cooper pair or the gap function. In this report, we present numerical results regarding the gap function in strongly correlated electron systems using t - J and Hubbard models in one and two dimensions. To this end, we use exact diagonalization to study the ground states of 8- and 16-site clusters consisting of single or coupled layers. We calculate a reduced two-particle density matrix in momentum space which is a measure of the gap function. We then analyze the eigenvectors of this density matrix, which display the possible Cooper pair symmetries. The eigenvector corresponding to the largest eigenvalue indicates a vanishing gap on the Fermi surface (which is in favour of odd-gap pairing) although $d_{x^2-y^2}$ symmetry is seen to be a very close contestant in many of the cases.

I. INTRODUCTION

In the theory of superconductivity, the quantity which characterizes the nature of pairing is the gap function. More precisely, it is the amplitude for pairing

$$\Delta_{\mathbf{k}} = \langle c_{\mathbf{k}\uparrow}^{\dagger} c_{-\mathbf{k}\downarrow}^{\dagger} \rangle, \qquad (1)$$

for a Cooper pair of electrons in states $(\mathbf{k} \uparrow, -\mathbf{k} \downarrow)$ in a singlet spin configuration. This quantity is closely related to the energy gap in the single-particle excitation spectrum of a superconductor, and has a direct bearing on many of the experimentally measurable quantities.

As an example, consider the standard BCS s-wave superconductor [1], which has an isotropic gap function which is *even* across the Fermi surface (FS), non-zero only in a thin shell of width $\sim \hbar \omega_D$ around ϵ_F . The energy gap $\Delta_{\mathbf{k}}^{(e)}$ is related to the gap function (1) through the relation

$$\Delta_{\mathbf{k}}^{(e)} = 2E_{\mathbf{k}}\Delta_{\mathbf{k}},\tag{2}$$

and obeys the celebrated gap equation

$$\Delta_{\mathbf{k}}^{(e)} = -\sum_{\mathbf{k}'} V_{\mathbf{k}\mathbf{k}'} \frac{\Delta_{\mathbf{k}'}^{(e)}}{2E_{\mathbf{k}'}},\tag{3}$$

where $E_{\mathbf{k}} = \sqrt{\epsilon_{\mathbf{k}}^2 + \Delta_{\mathbf{k}}^{(e)2}}$ is the quasiparticle energy, $\epsilon_{\mathbf{k}}$ is the single-particle energy with respect to ϵ_F , and $V_{\mathbf{k}\mathbf{k}'}$ is

the effective electron-electron interaction matrix element in the reduced BCS hamiltonian. The energy gap can be directly observed, for example, through superconductornormal metal or Giaver tunneling.

To understand the significance of the gap function (1), let us examine the behaviour of the BCS wavefunction close to the FS:

$$|BCS\rangle = \prod_{\mathbf{k}} (u_{\mathbf{k}} + v_{\mathbf{k}} c^{\dagger}_{\mathbf{k}\uparrow} c^{\dagger}_{-\mathbf{k}\downarrow})|0\rangle \tag{4}$$

which can be rewritten as

$$|BCS\rangle = \prod_{\mathbf{k}}' (u_{\mathbf{k}}^2 + \sqrt{2}u_{\mathbf{k}}v_{\mathbf{k}}b_{\mathbf{k},-\mathbf{k}}^{\dagger} + v_{\mathbf{k}}^2b_{\mathbf{k},-\mathbf{k}}^{\dagger}b_{\mathbf{k},-\mathbf{k}}^{\dagger})|0\rangle,$$
(5)

where the product is now over only half of the **k**-space (e.g. $k_x > 0$ and all k_y in 2D). Here we have

$$b_{\mathbf{k},-\mathbf{k}}^{\dagger} = \frac{1}{\sqrt{2}} (c_{\mathbf{k}\uparrow}^{\dagger} c_{-\mathbf{k}\downarrow}^{\dagger} - c_{\mathbf{k}\downarrow}^{\dagger} c_{-\mathbf{k}\uparrow}^{\dagger}) \tag{6}$$

as the singlet Cooper pair creation operator at points ${f k}$ and $-\mathbf{k}$ in **k**-space. It is clear that $u_{\mathbf{k}}^2$ is the *probabil*ity amplitude of finding no singlet pair with momentum $(\mathbf{k}, -\mathbf{k}), u_{\mathbf{k}}v_{\mathbf{k}}$ is that of finding one singlet pair (of charge 2e), and $v_{\mathbf{k}}^2$ that of finding two singlet pairs (of total charge 4e). The BCS state has identical phase relations for various configurations of pair occupancy in k-space. That is, when the product in Eq. (5) is expanded out, the resulting sum has identical phase for all terms, each term corresponding to different configurations of the $(\mathbf{k}, -\mathbf{k})$ occupancy. Superconductivity can thus be thought of as a coherent charge-2e fluctuating state in k-space. Since $\Delta_{\mathbf{k}}$ is non-zero only in a thin energy shell around the FS, the coherent 2e charge fluctuation is concentrated around the FS. (Note that this coherence in k-space results in phase coherence among the Cooper pairs in real space also). Away from the shell, we either have a completely filled band (inside the FS) or a completely empty band (outside the FS) and hence no charge fluctuations. The gap function (1), for the BCS wavefunction (5), reduces to

$$\Delta_{\mathbf{k}} = u_{\mathbf{k}} v_{\mathbf{k}},\tag{7}$$

and is thus a measure of coherent charge fluctuations in ${\bf k}\mbox{-space}.$

In the context of the high- T_c cuprates, it is generally believed that the gap function is not of simple BCS type (s-wave and even across \mathbf{k}_F). Some of the recent experiments have suggested that the gap is highly anisotropic, possibly with the $d_{x^2-y^2}$ symmetry. [10] Yet another proposal is that of odd-gap pairing, which is a favoured mode of pairing in the presence of a strong, purely repulsive interaction. [3] A recent proposal in the context of the interlayer tunneling mechanism is that of anisotropic swave pairing, which has deep minima but no actual nodes on the FS. [20] However, in spite of intense activity, both on theoretical and experimental sides, the issue of the symmetry of the gap function still remains unresolved. The importance of this issue cannot be overestimated, since the gap function is a quantity which, on the one hand, has direct experimental consequences, and on the other, may offer a unique signature pointing to the right kind of mechanism for high- T_c superconductivity.

The aim of the present work is to investigate the behaviour of $\Delta_{\mathbf{k}}$ using exact diagonalization, especially with reference to its nodal structure. We would like to find out the most likely pairing symmetries, both angular and radial, for clusters consisting of single or coupled chains and planes. In particular, we are interested in the $d_{x^2-y^2}$ symmetry and odd-gap pairing. In what follows, we first present a brief summary of the various proposed gap functions, especially $d_{x^2-y^2}$ and odd-gap pairing (section II). We then present our numerical procedure in section III and the results in section IV. Finally, conclusions are presented in section V.

II. $D_{X^2-Y^2}$, ODD-GAP AND OTHER PAIRING SYMMETRIES

In order to see, on general grounds, why gap functions with zeros are preferable as candidates for pairing in high- T_c superconductors, let us consider the one-band large-U Hubbard model or the t-J model. These models are believed to contain the essential low-energy physics of high- T_c superconductivity. Let us begin by noting that in the large-U Hubbard model, the on-site pairing amplitude $\Delta_{ii} = \langle c_{i\uparrow}^{\dagger} c_{i\downarrow}^{\dagger} \rangle$ is diminished considerably on account of the restriction on double occupancy. In the t-J model, of course, double occupancy is completely projected out. Thus $\Delta_{ii} = 0$, which reduces, in **k**-space, to

$$\Delta_{ii} = \sum_{\mathbf{k}} \langle c^{\dagger}_{\mathbf{k}\uparrow} c^{\dagger}_{-\mathbf{k}\downarrow} \rangle \equiv \sum_{\mathbf{k}} \Delta_{\mathbf{k}} = 0, \qquad (8)$$

where we have used the pairing condition $\langle c_{\mathbf{k}\uparrow}^{\dagger} c_{\mathbf{k}\downarrow\downarrow}^{\dagger} \rangle = \Delta_{\mathbf{k}} \delta_{\mathbf{k},-\mathbf{k}'}$. This is a constraint on the gap function, arising from a strong real-space repulsion, and implies the presence of zeros in the gap function.

The constraint, however, is a global constraint, and can be satisfied in several ways. One possibility is that of odd-gap pairing, in which case the gap function vanishes on the *entire* Fermi surface, and changes sign across the FS. Yet another possibility is that of a simple $d_{x^2-y^2}$ superconductor on a 2D square lattice, for which the gap function vanishes along the lines $k_x = \pm k_y$ which intersect the FS at exactly four points. We give below a brief account of these two and some of the other proposed pairing states.

A. Odd-Gap Pairing

The possibility of odd-gap pairing, in the presence of a dominantly repulsive interaction, was anticipated by Cohen [2] many years ago. The case for odd-gap pairing, in the context of high- T_c superconductivity, was put forward by Mila and Abrahams [3], within the framework of the weak coupling BCS theory. They have shown that an even solution to the BCS gap equation (3) exists only so long as the effective electron-electron interaction is dominantly attractive, albeit weak. This is the case with the standard BCS model of conventional superconductivity, where the weak attraction arises due to electron-phonon coupling. In the presence of a repulsive interaction, however, such a solution ceases to exist when the repulsive part of the interaction starts dominating, and an unusual solution is shown to exist which is *odd* across the FS. For example, in the toy models considered in [2] as well as [3], the energy gap is proportional to $(\epsilon - \epsilon_F)$, which is clearly odd across the FS. Moreover, an odd gap is independent of the *magnitude* of the repulsion, provided that it is the repulsion which dominates. This condition is met in the large-U Hubbard model, and odd-gap pairing is thus a candidate for pairing in the high- T_c superconductors. Mila and Abrahams have further shown that certain key features of the tunneling density of states in the cuprates, such as the temperature-insensitive peak, can be naturally explained on the basis of odd-gap pairing. This feature is in contrast with s-wave as well as $d_{x^2-y^2}$ pairing, in which the peak shifts towards ϵ_F as $T \to T_c$.

Anderson [4] has also pointed out in the context of the RVB theory that the gap function vanishes on, and changes sign across, the FS. For example, in the RVB mean field theory at half filling, [8] the gap function is constant and changes sign across the pseudo FS defined by $\cos k_x + \cos k_y = 0$ and satisfies the constraint (8). For the doped case, however, the analysis is difficult and Anderson did not provide any argument as to why the gap should vanish on the FS away from half-filling. [8] In the latter case, it is argued that strong correlations in real space lead to a suppression of coherent charge fluctuations close to the FS, [27] in the sense of Eq. (5), as follows. Strongly correlated electrons in 1D, described by a large-U Hubbard model, have certain unique features close to the FS. It is well known that in the 1D Hubbard model there is singular forward scattering between two electrons with opposite spins close to the FS. This leads to a finite phase shift [5] at the FS and the consequent failure of the Fermi liquid theory, resulting in the vanishing of the discontinuity in $n_{\mathbf{k}}$ at the FS (Luttinger liquid behaviour). It also implies an effective hard-core repulsive pseudopotential between electrons with opposite spins close to the FS. Thus no two electrons close to the FS, with opposite spins, can have the same momentum, thereby making **k**-points close to the FS essentially singly occupied. Coherent pair fluctuations are thus unlikely to develop on or very close to the FS, but are not forbidden away from the FS. It is therefore likely that the line of zeros of $\Delta_{\mathbf{k}}$ implied by the global constraint (Eq. (8)) will coincide with the FS.

Whether these arguments carry over to 2D or not is still unclear. It is believed that if the constraint of no double occupancy in real space leads to singular forward scattering and the consequent failure of Fermi liquid theory in 2D (in the spirit of Anderson's tomographic Luttinger liquid picture [6]), a gap function which vanishes on the entire FS is a natural candidate for pairing.

Odd-gap pairing has so far found very feeble experimental support. However, a very recent work [7] shows ARPES data in Bi2212 cuprates in which the gap *does not vanish* along $k_x = k_y$, but vanishes on either side of this line. This can be interpreted as a possible indication that the nodal lines in the gap coincide with the FS.

B. $d_{x^2-y^2}$ Pairing

The $d_{x^2-y^2}$ paired state is characterised by a gap function of the form

$$\Delta_{\mathbf{k}} = \Delta_d(\cos k_x - \cos k_y). \tag{9}$$

Support to $d_{x^2-y^2}$ pairing comes from numerous sources. Theoretical analysis of motion of holes in an antiferromagnetic background shows that exchange of spin fluctuations can induce singlet pairing of $d_{x^2-y^2}$ symmetry, for which hole-hole interaction is attractive. [9] Although antiferromagnetic fluctuations are rather subdued in the doped case in comparison with half-filling, it is reasonable to expect $d_{x^2-y^2}$ pairing as a possibility.

On the experimental side, numerous experiments have been performed recently, which seem to support $d_{x^2-u^2}$ pairing. London penetration depth data from Hardy et al. [11] shows a low-temperature linear temperature dependence which is in agreement with a $d_{x^2-y^2}$ superconductor, and very much in contrast with the BCS s-wave case (which shows an exponential behaviour). An experimental result strongly supporting $d_{x^2-y^2}$ pairing is the T^3 variation of Cu NMR relaxation rate [12]. ARPES measurements on Bi2212 compunds by Shen et al. [10] indicate lines of zeros compatible with a $d_{x^2-y^2}$ state, and incompatible with an extended-s state, although these measurements are unable to rule out pairings such as s + id or an anisotropic s-wave (next section). Certain other experiments, which support $d_{x^2-u^2}$ pairing, but cannot rule out the possibility of other kinds of pairing include SQUID experiments on YBCO [13] and electronic Raman scattering measurements on Bi2212 compounds. [14]

On the numerical side, studies in favour $d_{x^2-y^2}$ pairing include an exact diagonalization study of possible pairing symmetries by Riera and Young [15] (on which we comment in the next section). Dagotto and Riera [16] find bound hole pairs with $d_{x^2-y^2}$ symmetry near half-filling and on the verge of phase separation, although the value of $J/t \sim 3$ is rather too large in comparison with the experimentally relevant parameter range $J/t \sim 0.3$. Another notable work [17] calculates an anomalous Green's function for one and two holes using Lanczos technique, and finds signals of $d_{x^2-y^2}$ pairing over a wide range of parameter J/t (not specified).

C. Other Proposed Pairing Symmetries

A variational Monte Carlo study by Li *et al.* [18] supports s + id symmetry rather than a pure $d_{x^2-y^2}$. This calculation compares RVB variational states with extended-s, $d_{x^2-y^2}$, and mixed states s + d and s + id symmetries. The authors show that the mixed states are energetically preferred over pure s or $d_{x^2-y^2}$ states, and that the s + id state overcomes finite-size effects at a lattice size smaller than that required by the $d_{x^2-y^2}$ state. The authors also argue that the Knight shift data in the YBCO cuprates is better explained by s + id rather than pure $d_{x^2-y^2}$ pairing. Wheatley [19] has also analyzed the stability of various mixed states involving $d_{x^2-y^2}$.

Chakravarty *et al.* [20] have recently proposed an anisotropic *s*-wave pairing state based on the interlayer tunneling mechanism [21]. This state has no actual nodes on the FS although deep minima occur, and the gap is highly anisotropic. Since ARPES results, such as [10], are unable to detect the sign of the gap function (as well as the presence of a node unambiguously owing to the current energy resolution), they are consistent with such an anisotropic *s*-wave pairing as well. Interlayer tunneling is also responsible for a temperature-dependent anisotropy in the gap, as shown by Muthukumar and Sardar [23], which is incompatible with the $d_{x^2-y^2}$ scenario. Such a temperature-dependent anisotropy has been observed in the ARPES data by Ma et al. [22]

III. NUMERICAL PROCEDURE

In our exact diagonalization computation, since we have chosen to work in a number-conserving basis, it is not possible to evaluate $\Delta_{\mathbf{k}}$ directly. [24] We thus define a correlation function $A_{\mathbf{k},\mathbf{k}'}$ as

$$A_{\mathbf{k},\mathbf{k}'} = \langle b_{\mathbf{k},-\mathbf{k}}^{\dagger} b_{\mathbf{k}',-\mathbf{k}'} \rangle, \qquad (10)$$

where the average $\langle \dots \rangle$ is the expectation value in the ground-state of a finite cluster, obtained via exact diago-

nalization. This quantity is clearly a measure of coherent pair fluctuations between states $(\mathbf{k}, -\mathbf{k})$ and $(\mathbf{k}', -\mathbf{k}')$ in the ground state.

We find the gap function $\Delta_{\mathbf{k}}$ by diagonalizing this two particle reduced density matrix (10), which has the eigenfunction decomposition

$$A_{\mathbf{k},\mathbf{k}'} = \sum_{\alpha} \lambda_{\alpha} \Delta_{\alpha}(\mathbf{k}) \Delta_{\alpha}^{*}(\mathbf{k}').$$
(11)

Here, λ_{α} and $\Delta_{\alpha}(\mathbf{k})$ are the α th eigenvalue and eigenfunction of the $N \times N$ matrix $A_{\mathbf{kk'}}$. Here N is the number of points in the Brillouin zone and the index α orders λ_{α} 's as $\lambda_1 \geq \lambda_2 \geq \lambda_3 \geq \ldots$. Superconducting ODLRO is signalled [25] by a macroscopic separation of the largest eigen value λ_1 from the next one λ_2 , i.e. $\lambda_1 - \lambda_2 \approx N$. The required gap function $\Delta_{\mathbf{k}}$ is the eigenvector $\Delta_1(\mathbf{k})$ corresponding the largest eigen value λ_1 , which is the Cooper pair state with least energy for which condensation will take place, whereas the other eigenvectors represent the various excited states of the Cooper pair. For example, for the standard BCS ground state, $\lambda_1 = N$, $\Delta_1(\mathbf{k}) = u_{\mathbf{k}}v_{\mathbf{k}}$ and $\lambda_{\alpha} = 0$, for $\alpha = 2, 3 \dots N$.

A similar procedure was adopted by Riera and Young [15] in the context of the t - J model with the threesite term. However, the authors argue that from the expression (10) translated into real space,

$$A_{\mathbf{k},\mathbf{k}'} = \frac{1}{N^2} \sum_{klmn} e^{i\mathbf{k}\cdot(\mathbf{R}_k - \mathbf{R}_l)} e^{-i\mathbf{k}'\cdot(\mathbf{R}_m - \mathbf{R}_n)} \langle b_{kl}^{\dagger} b_{mn} \rangle,$$
(12)

(where $b_{mn}^{\dagger} = \frac{1}{\sqrt{2}} (c_{m\uparrow}^{\dagger} c_{n\downarrow}^{\dagger} - c_{m\downarrow}^{\dagger} c_{n\uparrow}^{\dagger})$ creates a spin-singlet pair of electrons at sites m, n), one should retain only those terms which have all the four indices k, l, m, n distinct, since it is only these terms which correspond to true pairing terms, rather than mere charge and spin correlations. The authors *post facto* justify this procedure on the basis that the $d_{x^2-y^2}$ symmetry starts dominating very close to where the two-hole binding energy becomes negative, as a function of J. We do not agree with this argument, since there is no clear cut way to justify such a removal *a priori*, in our calculation, since we are calculating a quantity in \mathbf{k} -space; Eq. (12) then dictates that all terms be retained in the Fourier transform. Indeed, such removal in the U < 0 case leads to an incorrect symmetry, whereas the gap function is known to be of a simple BCS type, *i. e.* an even function across the FS (with an s-wave symmetry in 2D). This is illustrated in Fig. 1 in which we plot the gap function corresponding to the highest eigenvalue for an 8-site Hubbard chain with U = -5, with and without following this removal of terms. Without the removal of terms, we see the expected behaviour, whereas with the removal, we observe a sign change across \mathbf{k}_F . On a $\sqrt{8} \times \sqrt{8}$ Hubbard plane at U = -5, with the removal of terms, we have observed a double sign change across the FS, indicating two nodal

lines encircling the FS on either side, whereas without such removal, we see the expected BCS-like symmetry.

We shall thus present results *without* the removal of these "on-site" terms. Note that with removal, we indeed obtain similar results as Riera and Young. [15] We would also like to point out that unlike their work, the focus of our work is the nodes in the gap function. We shall refer to the gap function corresponding to the highest eigenvalue of the density matrix (10) as the "topmost" gap function, and the term eigenspectrum will be used to refer to the eigenvalue spectrum of the density matrix.

IV. RESULTS AND DISCUSSION

The clusters used for these calculations are single-layer clusters of 8 (Hubbard) and 16 (t - J) sites, and clusters with two 8-site t - J layers coupled by an interlayer term of the form

$$H_{\perp} = -t_{\perp} \sum_{i l m \sigma} (1 - n_{i-\sigma}^l) c_{i\sigma}^{l\dagger} c_{i\sigma}^m (1 - n_{i-\sigma}^m)$$
(13)

where l, m are layer indices (= 1,2), i is the site index within a layer and σ is the spin label.

A. Results in One Dimension

We first present the gap function for the 1D clusters. Fig. 2 displays the topmost gap function for U = 10 at various fillings. A clear change of sign is visible across the corresponding Fermi point ($\frac{\pi}{2}$ at half filling, $\frac{\pi}{4}$ for 2 and 4 holes), indicating the presence of a node near \mathbf{k}_F . Similar behaviour is observed for all U > 0, and over a range of fillings (0, 2, 4 and 6 holes).

The results for a 16-site t-J chain are presented in Fig. 3 and 4, and are representative of the parameter range J = 0.08 - 0.32. Fig. 3 presents eigenspectrum of the density matrix for various cases: half-filling at J = 0.24(1), 2 holes at J = 0.32, 0.24, 0.16, 0.08 (2)-(5). All these spectra display a prominant, well-separated largest eigenvalue, indicating the possibility of ODLRO (as far as a finite size calculation can reveal). For comparison, we have also plotted the eigenspectrum for a antiparallel triplet Cooper pair density matrix in Fig. 3 (6) for J = 0.24, 2holes, which does not show a well-separated eigenvalue. Fig. 4 displays the topmost gap function at half-filling and 2 holes, where a clear sign change across \mathbf{k}_F indicates a node near \mathbf{k}_F .

Finally, Fig. 5 plots the topmost gap function for a single 8-site chain in a system of two 8-site t - J chains coupled by an interlayer coupling term (13), for 2 holes with J = 0.24 and $t_{\perp} = 0.05 - 0.7$. We see again a clear node near $\mathbf{k}_F = \frac{\pi}{2}$ very similar to the case of a single 16-site t - J chain.

B. Results in Two Dimensions

We now turn to the more interesting case of 2D clusters. These results are obtained for $\sqrt{8} \times \sqrt{8}$ Hubbard, $4 \times 4 \ t - J$ and coupled $\sqrt{8} \times \sqrt{8} \ t - J$ planes. The results are representative of a range of parameter values and fillings as specified below. $\sqrt{8} \times \sqrt{8}$ Hubbard cluster: all U > 0 (0, 2 and 4 holes); $4 \times 4 \ t - J$ plane: J = 0.08, 0.16, 0.24, 0.32 (0 and 2 holes); coupled $\sqrt{8} \times \sqrt{8} \ t - J$ planes: J = 0.24, 0.32 (0 and 2 holes); coupled $\sqrt{8} \times \sqrt{8} \ t - J$ planes: $J = 0.24, 0.32, \ t_{\perp} = 0.05 - 0.7$ (0 and 2 holes). To bring about the symmetry features of a gap function, we shall display the numerical values of the coefficients of the corresponding eigenvector (of the density matrix (10)) at all **k**-points in the Brillouin zone. The FS (and the nodal lines of $d_{x^2-y^2}$, wherever required) will be indicated by dashed lines.

We first discuss the characteristics of the eigenspectra. In all the cases presented, the eigenspectrum displays a separated largest eigenvalue, although not as well-separated as in the 1D case. Fig. 6 (1)-(3) are eigenspectra for 2 holes, respectively for a $\sqrt{8} \times \sqrt{8}$ Hubbard cluster with $U = 10, 4 \times 4 t - J$ plane with J = 0.24 and coupled $\sqrt{8} \times \sqrt{8} t - J$ planes with $J = 0.24, t_{\perp} = 0.2$. The most striking feature of these results is the close interplay between the odd-pairing and the $d_{x^2-y^2}$ gap functions. The odd-paired state is the topmost for all the three clusters, with the next dominant state as the $d_{x^2-y^2}$ state on 4×4 and coupled $\sqrt{8} \times \sqrt{8}$ clusters. For the $\sqrt{8} \times \sqrt{8}$ Hubbard cluster with 2 holes, however, the $d_{x^2-y^2}$ state is quite low down in the eigenspectrum. These two states, for a 4×4 plane, are displayed in Fig. 7.

C. Discussion

The overall picture that emerges out of this study is as follows. In 1D and 2D, the gap function shows the presence of a node near or at \mathbf{k}_F , indicating an oddpaired behaviour. The $d_{x^2-y^2}$ state is often seen as the next dominant state. Quite clearly, the numerical results seem to indicate the presence of a nodal "surface" (GNS) in the gap function closely following the FS. Recall that in the RVB mean-field theory at half-filling, the GNS coincides with the FS in 2D (also seen in our numerical results (not shown)). It may be argued that as doping increases from zero, the FS shrinks, dragging part of the GNS with it. [27] The non-overlap of the GNS with the FS in some parts in the BZ is possibly caused due to the enhancement of the interlayer pair tunneling matrix element $\frac{t_{\perp}^{2}(k)}{t}$ in those directions in **k**-space. For example, as emphasized by Chakravarty *et al.* [20], $\frac{t_{\perp}^2(k)}{t}$ is largest in the $(0, \pi)$ and $(\pi, 0)$ directions which enhances pairing in those regions of the FS by keeping the GNS away. Fig. 8 incorporates this idea as well as the eight nodal points of the recent ARPES data [7]. Based on the present numerical work, we believe that it may be possible to

construct novel scenarios where such a nodal surface is also consistent with $d_{x^2-y^2}$ pairing. This and such other aspects are discussed elsewhere. [27]

The major handicap of any exact diagonalization calculation is the cluster size restriction. It is not possible for us to rule out finite size effects, but the features we have observed are consistent within the sizes and geometries considered. It is indeed possible that finite size effects are more serious when symmetry issues are concerned, in comparison with, for example, the finite size effects in simple spin, charge or pairing correlation functions. [18]

Note that we do not interpret the present results as indicative of the presence of superconducting ODLRO in purely 2D systems. However, it does indicate that these pairing correlations show an odd-paired behaviour across the FS, a feature which seems to persist even in the presence of an interlayer coupling term.

V. SUMMARY

To summarise, we have investigated the behaviour of the gap function $\Delta_{\mathbf{k}}$ across the Fermi surface in the doped t - J and large-U Hubbard clusters in one and two dimensions, with special reference to odd-gap and $d_{x^2-y^2}$ pairing. For this purpose, we diagonalize a reduced twoparticle (Cooper pair) density matrix computed through exact diagonalization. The largest eigenvalue of this density matrix is well-separated from the rest, indicating the possibility of ODLRO. The corresponding eigenvector, the Cooper pair wavefunction with least energy, reflects the symmetry of the gap function $\Delta_{\mathbf{k}}$. The results on 8- and 16-site single or coupled chains and planes clearly indicate a change of sign of $\Delta_{\mathbf{k}}$ across \mathbf{k}_{F} , indicating the presence of a node close to the entire FS, a signature of odd-pairing behaviour. This state, on single and coupled planes, in addition, is isotropic, indicating an angular symmetry which is of the *s*-wave type. We also observe a close interplay between the odd-paired and $d_{x^2-y^2}$ states in the 2D systems.

ACKNOWLEDGMENTS

We would like to thank V. N. Muthukumar for many useful discussions. M. A. thankfully acknowledges R. E. Amritkar for his critical comments, the Council for Scientific and Industrial Research, New Delhi for financial support, and the Center for Development of Advanced Computing (C-DAC), Pune, for computing facility. Partial financial assistance was provided under Project No. SP/S2/M-47/89 by the Department of Science and Technology and DST project SBR 32 of the National Superconductivity Programme.

- [‡] *electronic address:* baskaran, rahul@imsc.ernet.in; kanhere, mihir@unipune.ernet.in.
- See, for example, J. R. Schrieffer, *Theory of Supercon*ductivity, W. A. Benjamin, Inc. (New York), 1964.
- [2] M. L. Cohen, Phys. Rev. Lett. **12**, 664 (1964); S. Nakajima, Prog. Theo. Phys. **32**, 871 (1964).
- [3] F. Mila and E. Abrahams, Phys. Rev. Lett. 67, 2379 (1991). Recently some authors have considered a more general type of singlet pairing that is odd in k and ω both; see, for example, V. L. Berezinskii, Pis'ma Zh. Eksp. Teor. Fiz. 20, 628 (1974) [JETP Lett. 20, 287 (1974)]; E. Abrahams, A. V. Balatsky, J. R. Schrieffer and P. B. Allen, Phys. Rev. B47, 513 (1993).
- [4] P. W. Anderson, Proceedings of the Workshop on Fermiology of High-T_c Superconductivity, Argonne, 1991; P.
 W. Anderson, Science 235 1196 (1987).
- [5] P. W. Anderson, Phys. Rev. Lett. 64, 1839 (1990); P. W. Anderson in the *Princeton RVB Book* on high-T_c super-conductors, Chapter V (unpublished). See also F. D. M. Haldane, Phys. Rev. Lett. 47 1840 (1981); H. Shiba and M. Ogata, Prog. Theor. Phys. Suppl. 108, 265 (1992).
- [6] P. W. Anderson, Phys. Rev. Lett. 65, 2306 (1990); P. W. Anderson, *ibid.* 66, 3226 (1991).
- [7] H. Ding et al., Argonne preprint, December 1994.
- [8] G. Baskaran, Z. Zou and P. W. Anderson, Solid State Commun. 63, 973 (1987).
- [9] K. Miyake, S. Schmitt-Rink and C. M. Varma, Phys. Rev. B34, 6554 (1986); D. J. Scalapino, E. Loh and J. E. Hirsch, Phys. Rev. B35, 6694 (1987); N. E. Bickers, D. J. Scalapino and S. R. White, Phys. Rev. Lett., 62, 961 (1989); P. Monthoux, A. Balatsky and D. Pines, Phys. Rev. B46, 14803 (1992); P. Monthoux and D. J. Scalapino, Phys. Rev. Lett. 72, 1874 (1994).
- [10] Z.-X. Shen *et al.*, Phys. Rev. Lett. **70** 1553 (1993);
- [11] W. N. Hardy et al., Phys. Rev. Lett. 70 3999 (1993);
- [12] J. A. Martindale et al., Phys. Rev. B47, 9155 (1993);
- [13] D. A. Wollman et al., Phys. Rev. Lett. 71, 2134 (1993).
- [14] T. P. Devereaux et al., Phys. Rev. Lett. 72, 396 (1994);
- [15] J. A. Riera and A. P. Young, Phys. Rev. B**39**, 9697 (1989).
- [16] E. Dagotto and J. Riera, Phys. Rev. Lett. **70** 682 (1993);
 E. Dagotto, to appear in Rev. Mod. Phys., July 1994;
 D. Poilbalnc, J. Riera and E. Dagotto, Phys. Rev. B49, 12318 (1994).
- [17] Y. Ohta, T. Shimozato, R. Eder and S. Maekawa, Phys. Rev. Lett. 73, 324 (1994).
- [18] Q. P. Li *et al.*, Phys. Rev. B48, 437 (1993); see also C. Gros, Phys. Rev. B38, 931 (1988).
- [19] J. Wheatley, Solid State Commun. 88, 593 (1993).
- [20] S. Chakravarty, A. Sudbo, P. W. Anderson and S. Strong, Science **261**, 337 (1993); A. Sudbo, S. Chakravarty, S. Strong, and P. W. Anderson, Phys. Rev. B**49**, 12245 (1994).
- [21] J. M. Wheatley, T. Hsu and P. W. Anderson, Phys. Rev. B37, 5897 (1988).
- [22] Ma *et al.*, Science, to be published.
- [23] V. N. Muthukumar and Manas Sardar, unpublished.
- [24] A direct calculation of $\Delta_{\mathbf{k}}$ involves calculating $\langle N 2|b_{\mathbf{k}}|N\rangle$, where $|N\rangle$ is the N-electron ground state; see, for example, D. Poilblanc, Phys. Rev. B49, 1477 (1994).

- [25] C. N. Yang, Rev. Mod. Phys. 34, 694 (1962).
- [26] More precisely, the largest eigenvalue of a density matrix with ODLRO scales as the number of particles in the system. However, for power-law correlations, the scaling will be with a power smaller than one.
- [27] G. Baskaran, D. G. Kanhere, Mihir Arjunwadkar and Rahul Basu, unpublished.

Figure Captions

- 1. Topmost gap function for an 8-site Hubbard chain with 2 holes at U = -5, with and without the removal of terms from the gap expression (12); $\mathbf{k}_F = \frac{\pi}{4}$. Notice the sign change across the FS with the removal of terms.
- 2. Topmost gap functions for an 8-site Hubbard chain with U = 10, for 0, 2 and 4 holes; $\mathbf{k}_F = \frac{\pi}{2}, \frac{\pi}{4}, \frac{\pi}{4}$ respectively.
- 3. Eigenvalue spectra of the density matrix for the 16site t - J chain. (1) Half-filled, J = 0.24, (2)-(5) 2 holes, J = 0.32, 0.24, 0.16, 0.08, (6) triplet antiparallel eigenspectrum for 2 holes, J = 0.24.
- 4. Topmost gap functions for a 16-site t J chain at half filling (J = 0.24) and 2 holes (J = 0.08 0.32). $\mathbf{k}_F = \frac{\pi}{2}, \frac{3\pi}{8}$ for 0 and 2 holes respectively.
- 5. Topmost gap function for a single 8-site t J chain in a coupled system of two chains with 2 holes, for values of $t_{\perp} = 0.05 - 0.7$, J = 0.24. $\mathbf{k}_F = \frac{\pi}{2}$ for $k_y = 0$.
- 6. Eigenvalue spectra of the density matrix for the three 2D clusters at half filling and for 2 holes. (1) $\sqrt{8} \times \sqrt{8}$ Hubbard plane, 2 holes, U = 10; (2) 4×4 t-J plane, 2 holes, J = 0.24; (3) coupled $\sqrt{8} \times \sqrt{8}$ t-J planes, 2 holes, J = 0.24, $t_{\perp} = 0.05 0.7$. The labels "o" and "d" near a level respectively stand for odd-paired and $d_{x^2-y^2}$ states. A numeral near a level indicates the degeneracy.
- 7. The topmost two degenerate gap functions for a 4×4 plane with 2 holes, J = 0.24. Points marked by squares lie within one Brilliouin zone, diamonds belong to the neighbouring ones. The FS and the nodes of the $d_{x^2-y^2}$ state are indicated by dashed lines. The numbers above and below a square are the coefficients of the gap function respectively for the topmost (odd-paired) and next $(d_{x^2-y^2})$ states.
- 8. A suggested form of the GNS with s-symmetry. The solid line is the FS and the dotted line is the GNS. The + and - symbols indicate relative signs of the gap function across the GNS.













Figure 6



