

Supplementary material for “Three-dimensional Phase Field Quasicrystals”

P. Subramanian¹, A.J. Archer², E. Knobloch³ and A.M. Rucklidge,¹

¹*Department of Applied Mathematics, University of Leeds, Leeds LS2 9JT, UK*

²*Department of Mathematical Sciences, Loughborough University, Loughborough LE11 3TU, UK*

³*Department of Physics, University of California at Berkeley, Berkeley, CA 94720, USA*

(Dated: February 17, 2016)

In this supplementary material we present two videos that explore the 3D quasicrystalline structure in more detail. Both videos present data obtained from 3D direct numerical simulations carried out in a periodic domain of size $(26 \times 2\pi)^3$, corresponding to 26 of the shorter wavelengths as defined in the main paper. This increased domain allows a closer approximation to quasiperiodicity, and so the distribution of maxima of U better approximate icosahedral symmetry. The system parameters are $\sigma_0 = -100$, $Q = 1$, $q = 1/\tau = 0.6180$, $\mu = -0.01$ and $\nu = -0.01$, just as in Fig. 2(c) of the main paper. In this case, the simulation was started from an initial condition where the icosahedral symmetry was imprinted in order to hasten the approach of the quasicrystalline asymptotic state.




FIG. 1: Left panel: Structure of the 3D quasicrystal depicted as a contour cloud of isosurfaces of the density perturbation U displaying the 5-fold rotational symmetry. Right panel: Isosurfaces (shown as red spheres) at a chosen diameter from the center of the periodic domain are seen to form a rhombic triacontahedron with 32 vertices in this frame.

The first video displays isosurfaces in the density perturbation $U(\mathbf{x}, t)$ as we revolve around the periodic domain. The red spheres represent the isosurfaces and are seemingly in a non-regular arrangement or seem to possess three-fold symmetry when viewed from multiple angles. The video stops at a viewpoint, perpendicular to the plane $(\tau, -1, 0)$, where the five-fold rotational symmetry is apparent, with ten radial lines originating from the center, as seen in the left panel of Fig. 1.

In another approach to understanding the structure of this 3D quasicrystal, we start from the center of the domain, where there is a maximum of U , and note the different polyhedral arrangements that are formed by the isosurfaces as we move radially outward. The second movie shows the first two such structures. The growing sphere displays the contours of U at the current radius with red and blue areas indicating positive and negative values of U , respectively. The first regular polyhedron, at radius $(0.3549 \times 2\pi)$, is an icosahedron with 12 vertices, represented by the 12 red spheres. As we move outward further, the next regular structure, at radius $(0.5938 \times 2\pi)$, is a rhombic triacontahedron with 32 vertices, as seen in the right panel of the Fig. 1. As we move outward even further, more intricate contours are observed on the surface of the growing sphere.

The data for this paper, including a file that allows interaction with the data behind Fig. 1 through the ParaView software, is available from the Research Data Leeds repository.