

Pressure-induced structural dimerization in the hyperhoneycomb iridate β -Li₂IrO₃ at low temperatures

L.S.I. Veiga,^{1,*} K. Glazyrin,² G. Fabbri,³ C.D. Dashwood,¹ J.G.
Vale,¹ H. Park,^{4,5} M. Etter,² T. Irifune,^{6,7} S. Pascarelli,⁸ D.F.
McMorrow,¹ T. Takayama,^{9,10} H. Takagi,^{9,10} and D. Haskel^{3,†}

¹*London Centre for Nanotechnology and Department of Physics and Astronomy,
University College London, Gower Street, London WC1E6BT, UK*

²*Deutsches Elektronen-Synchrotron (DESY), Hamburg 22607, Germany*

³*Advanced Photon Source, Argonne National Laboratory, Argonne, Illinois 60439, USA*

⁴*Physics Department, University of Illinois at Chicago, Chicago, IL 60607*

⁵*Materials Science Division, Argonne National Laboratory, Lemont, Illinois, 60439, USA*

⁶*Geodynamics Research Center, Ehime University, Matsuyama, 790-8577, Japan*

⁷*Earth-Life Science Institute, Tokyo Institute of Technology, Tokyo, Japan*

⁸*European Synchrotron Radiation Facility,
71 Avenue des Martyrs, 38043 Grenoble, France*

⁹*Max Planck Institute for Solid State Research,
Heisenbergstrasse 1, 70569 Stuttgart, Germany*

¹⁰*Department of Physics and Department of Advanced Materials,
University of Tokyo, 7-3-1 Hongo, Tokyo, 113-0033, Japan*

(Dated: May 30, 2019)

I. SUPPORTING DATA

Tables S1, S2, S5 and S6 summarizes the lattice parameters and atomic positions as a function of pressure for each identified crystal structure at $T = 50$ K. The R factor of the structural solutions is reported in Tables S3 ($Fddd$) and S4 ($C2/c$) along with the isotropic displacement parameter (U_{iso}), reciprocal space coverage, number of refined reflections, number of refined parameters and data completeness. The R factor is related to refinements on the square structure parameter F^2 . For the $C2/c$ structures, the Li positions were fixed to the center of the LiO_6 octahedra. All Li and O sites have the same isotropic displacement parameters and $U_{iso}(\text{Li}) = U_{iso}(\text{O})$ for the $C2/c$ structures. All the atomic positions were standardized using the software VESTA¹.

TABLE S1. Lattice parameters and atomic coordinates of $\beta\text{-Li}_2\text{IrO}_3$ with $Fddd$ (No. 70, $Z = 16$) space-group symmetry extracted from single crystal analysis at $T = 50$ K. $x = y = 1/8$ and $y = z = 1/8$ for the $16g$ and $16e$ Wyckoff positions, respectively.

	P (GPa)	0.2(1)	0.5(1)	2.5(1)	3.2(1)	3.5(1)	4.2(1)
a		5.8664(10)	5.8589(4)	5.8585(5)	5.8471(4)	5.8415(6)	5.821(2)
b	(Å)	8.3836(4)	8.3757(16)	8.4734(2)	8.4538(2)	8.4501(3)	8.4470(9)
c		17.6792(16)	17.6740(7)	16.8814(8)	16.8424(8)	16.8264(11)	16.798(4)
Volume	(Å ³)	869.48(17)	867.31(18)	838.02(8)	832.52(7)	830.57(11)	825.9(4)
Ir ($16g$)	z	0.04151(5)	0.04154(5)	0.04654(2)	0.04659(3)	0.04665(2)	0.04671(4)
Li1 ($16g$)	z	0.545(2)	0.541(4)	0.5426(12)	0.5434(16)	0.5435(14)	0.543(2)
Li2 ($16g$)	z	0.381(4)	0.382(3)	0.3801(13)	0.3786(18)	0.3792(16)	0.376(3)
O1 ($16e$)	x	0.355(3)	0.361(4)	0.3798(16)	0.385(2)	0.3798(19)	0.370(3)
O2 ($32h$)	x	0.130(3)	0.132(3)	0.1410(10)	0.1360(15)	0.1396(11)	0.144(2)
	y	0.3645(7)	0.3645(7)	0.3648(6)	0.3652(9)	0.3655(7)	0.3663(10)
	z	0.0377(3)	0.0383(3)	0.0382(3)	0.0387(5)	0.0384(4)	0.0389(6)

TABLE S2. Lattice parameters and atomic coordinates of β -Li₂IrO₃ with $C2/c$ (No. 15, $Z = 8$) space-group symmetry extracted from single crystal analysis at $T = 50$ K.

	P (GPa)	2.5(1)	3.2(1)	3.5(1)	4.2(1)	6.5(1)	8.2(1)	9.4(1)
a		5.8487(11)	5.852(5)	5.843(2)	5.830(3)	5.776(2)	5.748(2)	5.732(3)
b	(Å)	8.1071(4)	8.0751(18)	8.0610(7)	8.0590(10)	8.0297(6)	7.9858(8)	7.9628(9)
c		9.1979(19)	9.190(7)	9.167(4)	9.167(5)	9.115(4)	9.096(5)	9.074(5)
β	°	107.04(2)	107.24(1)	107.05(5)	107.03(6)	106.74(5)	106.80(6)	106.82(6)
Volume	(Å ³)	416.98(12)	414.8(5)	412.8(3)	411.8(3)	404.8(2)	399.7(3)	396.5(3)
Ir	x	0.07805(16)	0.0771(2)	0.07750(16)	0.07714(14)	0.0771(2)	0.07693(19)	0.07683(14)
	y	0.11562(6)	0.11483(9)	0.11451(7)	0.11440(7)	0.11403(8)	0.11395(9)	0.11373(7)
	z	0.42186(9)	0.42246(13)	0.42235(10)	0.42257(9)	0.42261(11)	0.42261(11)	0.42274(9)
Li1	x	0.2500(15)	0.250(2)	0.2500(15)	0.2500(13)	0.2500(18)	0.250(2)	0.2500(15)
	y	0.3701(4)	0.3676(7)	0.3701(5)	0.3703(4)	0.3708(6)	0.3705(8)	0.3701(5)
	z	0.2500(9)	0.2500(12)	0.2500(9)	0.2500(8)	0.2500(10)	0.2500(13)	0.2500(9)
Li2	x	0.4167(15)	0.417(2)	0.4167(15)	0.4167(13)	0.4167(18)	0.417(2)	0.4167(15)
	y	0.1217(4)	0.1211(7)	0.1215(5)	0.1211(4)	0.1211(6)	0.1196(8)	0.1212(5)
	z	0.0833(9)	0.0833(12)	0.0833(9)	0.0833(8)	0.0833(10)	0.0833(13)	0.0833(9)
O1	x	0.231(4)	0.235(5)	0.242(4)	0.234(3)	0.234(5)	0.221(5)	0.230 (4)
	y	0.1150(10)	0.1133(15)	0.1145(11)	0.1134(10)	0.1134(13)	0.1089(18)	0.1137(12)
	z	0.251(2)	0.247(3)	0.246(2)	0.250(2)	0.252(3)	0.262(3)	0.256(3)
O2	x	0.090(3)	0.096(4)	0.092(3)	0.092(3)	0.096(4)	0.101(5)	0.096(3)
	y	0.3604(13)	0.353(2)	0.3604(15)	0.3609(12)	0.3625(18)	0.362(3)	0.3603(16)
	z	0.4232(18)	0.419(2)	0.4231(19)	0.4225(19)	0.420(2)	0.418(3)	0.4185(19)
O3	x	0.409(3)	0.393(5)	0.403(4)	0.407(3)	0.410(4)	0.414(5)	0.414(3)
	y	0.3711(12)	0.3731(18)	0.3679(14)	0.3668(12)	0.3650(18)	0.363(3)	0.3698(16)
	z	0.087(2)	0.093(3)	0.088(2)	0.087(2)	0.083(2)	0.077(3)	0.081(2)

TABLE S3. R factors in %, reciprocal space coverage, number of refined reflections, number of refined parameters, the isotropic displacement parameter (U_{iso}) and data completeness (in %) from the single crystal structural solution within the $Fddd$ space group. The R factors and χ^2 values refer to the solution performed with the intensity threshold $I > 3\sigma(I)$. U_{iso} is given in \AA^2 units.

P (GPa)	0.2(1)	0.5(1)	2.5(1)	3.2(1)	3.5(1)	4.2(1)
R factor	2.32	2.93	2.89	4.16	3.51	4.23
Reciprocal space coverage	$-7 \leq H \leq 8$	$-8 \leq H \leq 7$	$-7 \leq H \leq 9$	$-7 \leq H \leq 9$	$-7 \leq H \leq 9$	$-9 \leq H \leq 5$
	$-17 \leq K \leq 17$	$-17 \leq K \leq 17$	$-17 \leq K \leq 17$	$-17 \leq K \leq 17$	$-17 \leq K \leq 17$	$-17 \leq K \leq 15$
	$-29 \leq L \leq 31$	$-31 \leq L \leq 29$	$-29 \leq L \leq 26$	$-25 \leq L \leq 29$	$-28 \leq L \leq 25$	$-27 \leq L \leq 26$
No. of ref. reflex.	223	221	259	241	250	236
No. of ref. param.	13	13	10	10	10	13
Data completeness	32.5	31.5	31.5	31.1	29.9	32.4
$U_{\text{iso}}(\text{Ir})$	0.00029(12)	0.00311(14)	0.00416(14)	0.0063(2)	0.00557(17)	0.0048(2)
$U_{\text{iso}}(\text{Li1})$	0.002(4)	0.007(5)	0.0049(8)	0.0056(12)	0.0061(10)	0.010(7)
$U_{\text{iso}}(\text{Li2})$	0.015(8)	0.004(6)	0.0049(8)	0.0056(12)	0.0061(10)	0.013(8)
$U_{\text{iso}}(\text{O1})$	0.0009(12)	0.0038(14)	0.0049(8)	0.0056(12)	0.0061(10)	0.007(2)
$U_{\text{iso}}(\text{O2})$	0.0023(9)	0.0021(10)	0.0049(8)	0.0056(12)	0.0061(10)	0.0031(14)

TABLE S4. R factors in %, reciprocal space coverage, number of refined reflections, number of refined parameters, the isotropic displacement parameter (U_{iso}) and data completeness (in %) from the single crystal structural solution within the $C2/c$ space group. The R factors and χ^2 values refer to the solution performed with the intensity threshold $I > 3\sigma(I)$. U_{iso} is given in \AA^2 units.

P (GPa)	2.5(1)	3.2(1)	3.5(1)	4.2(1)	6.5(1)	8.2(1)	9.4(1)
R factor	5.54	6.93	5.25	4.41	6.02	6.91	5.85
Reciprocal space coverage	$-9 \leq H \leq 7$	$-9 \leq H \leq 7$	$-9 \leq H \leq 7$	$-7 \leq H \leq 9$	$-9 \leq H \leq 7$	$-9 \leq H \leq 7$	$-9 \leq H \leq 7$
	$-16 \leq K \leq 16$	$-16 \leq K \leq 16$	$-16 \leq K \leq 16$	$-16 \leq K \leq 16$	$-16 \leq K \leq 16$	$-16 \leq K \leq 16$	$-16 \leq K \leq 16$
	$-10 \leq L \leq 12$	$-10 \leq L \leq 12$	$-10 \leq L \leq 12$	$-12 \leq L \leq 10$	$-10 \leq L \leq 12$	$-9 \leq L \leq 12$	$-9 \leq L \leq 11$
No. of ref. reflex.	376	332	353	365	368	329	322
No. of ref. param.	15	15	15	15	15	15	15
Data completeness	22.8	21.7	21.7	21.1	21.3	20.8	19.7
$U_{\text{iso}}(\text{Ir})$	0.0064(2)	0.0124(3)	0.0073(2)	0.00623(18)	0.0066(2)	0.0044(3)	0.0036(2)
$U_{\text{iso}}(\text{Li})$	0.0065(12)	0.0132(18)	0.0090(12)	0.0056(10)	0.0080(15)	0.0119(19)	0.0043(12)
$U_{\text{iso}}(\text{O})$	0.0065(12)	0.0132(18)	0.0090(12)	0.0056(10)	0.0080(15)	0.0119(19)	0.0043(12)

TABLE S5. Structural parameters of β -Li₂IrO₃ at $P = 1.5$ GPa and $T = 50$ K. The space group is $P2_1/n$ (N^o 14), $Z = 16$ and the lattice constants are $a = 5.8418(13)$ Å, $b = 16.445(1)$ Å, $c = 9.252(2)$ Å, $\beta = 107.62(2)^\circ$ and $V = 847.2(3)$ Å³. Site occupancy is 1 for all atoms; U_{iso} is the isotropic displacement parameter and is given in Å² units. The final R factor is $R = 4.9\%$ and goodness of the fit $\chi^2 = 3.34$. No. of refined reflections: 1121; No. of fitted parameters: 51; Criterion for observed reflections: $I > 3\sigma(I)$.

Atom	x	y	z	U_{iso}
Ir1	0.07461(19)	0.18731(3)	0.41245(16)	
Ir2	0.5932(2)	0.43345(3)	0.42158(17)	
Ir3	0.4139(2)	0.43621(3)	0.08167(17)	0.00280(9)
Ir4	0.1052(2)	0.68201(3)	0.42746(17)	
Li1	0.2474(17)	0.0594(2)	0.2505(14)	
Li2	0.7382(17)	0.3093(2)	0.2438(14)	
Li3	0.9148(17)	0.4356(2)	0.0821(14)	
Li4	0.2374(17)	0.3098(2)	0.2440(14)	
Li5	0.4048(17)	0.1866(2)	0.0779(14)	0.0042(6)
Li6	0.5694(17)	0.1870(2)	0.4106(14)	
Li7	0.2518(17)	0.5595(2)	0.2497(14)	
Li8	0.0835(17)	0.4372(2)	0.4160(14)	
O1	0.056(4)	0.3083(5)	0.409(3)	
O2	0.565(4)	0.0575(5)	0.416(3)	
O3	0.084(4)	0.8022(5)	0.424(3)	
O4	0.396(5)	0.3154(5)	0.072(4)	
O5	0.085(5)	0.0652(5)	0.422(4)	
O6	0.571(5)	0.3117(5)	0.412(4)	
O7	0.080(5)	0.5601(5)	0.415(4)	0.0042(6)
O8	0.727(4)	0.4337(5)	0.245(3)	
O9	0.205(4)	0.1856(5)	0.239(3)	
O10	0.237(4)	0.6845(5)	0.252(3)	
O11	0.281(4)	0.4353(5)	0.256(3)	
O12	0.437(4)	0.0541(5)	0.086(3)	

TABLE S6. Structural parameters of β -Li₂IrO₃ at $P = 2.0$ GPa and $T = 50$ K. The space group is $P2_1/n$ (N^o 14), $Z = 16$ and the lattice constants are $a = 5.8383(7)$ Å, $b = 16.4217(5)$ Å, $c = 9.2429(11)$ Å, $\beta = 107.593(13)^\circ$ and $V = 844.72(14)$ Å³. Site occupancy is 1 for all atoms; U_{iso} is the isotropic displacement parameters and is given in Å² units. The final R factor is $R = 5.2\%$ and goodness of the fit $\chi^2 = 3.48$. No. of refined reflections: 1139; No. of fitted parameters: 51; Criterion for observed reflections: $I > 3\sigma(I)$.

Atom	x	y	z	U_{iso}
Ir1	0.0753(2)	0.18715(3)	0.41272(16)	
Ir2	0.5927(3)	0.43360(3)	0.42143(17)	
Ir3	0.4144(3)	0.43621(3)	0.08174(17)	0.00326(11)
Ir4	0.1048(2)	0.68216(3)	0.42729(16)	
Li1	0.2459(18)	0.0591(2)	0.2504(14)	
Li2	0.7412(17)	0.3093(2)	0.2442(14)	
Li3	0.9147(19)	0.4354(2)	0.0821(15)	
Li4	0.2379(17)	0.3098(2)	0.2442(14)	
Li5	0.4068(18)	0.1863(2)	0.0781(14)	0.0052(7)
Li6	0.5698(17)	0.1867(2)	0.4106(14)	
Li7	0.2508(19)	0.5593(2)	0.2496(15)	
Li8	0.0850(19)	0.4368(2)	0.4163(15)	
O1	0.073(4)	0.3086(7)	0.416(3)	
O2	0.424(4)	0.5579(7)	0.078(3)	
O3	0.096(4)	0.8036(7)	0.430(3)	
O4	0.399(5)	0.3152(7)	0.073(4)	
O5	0.087(5)	0.0649(7)	0.421(4)	
O6	0.573(5)	0.3119(7)	0.412(4)	
O7	0.085(5)	0.5602(7)	0.414(4)	0.0052(7)
O8	0.744(5)	0.4323(5)	0.251(4)	
O9	0.213(5)	0.1850(5)	0.244(4)	
O10	0.246(5)	0.6839(5)	0.257(4)	
O11	0.265(5)	0.4344(5)	0.250(4)	
O12	0.428(4)	0.0545(7)	0.081(3)	

REFERENCES

* l.veiga@ucl.ac.uk

† haskel@aps.anl.gov

¹ K. Momma and F. Izumi, *Journal of Applied Crystallography* **41**, 653 (2008).