

Supplementary materials

A practicable process for lignin color reduction: fractionation of lignin using methanol/water as solvent

Hui Zhang, Youcan Bai, Boming Yu, Xinxin Liu and Fangeng Chen*

State Key Laboratory of Pulp and Paper Engineering, South China University of Technology, Guangzhou 510640, Guangdong, China

*Corresponding author, Tel.: +8613430364029; E-mail: huizhang5066@163.com

List of Supplementary materials:

Table S1 Molecular weight of lignin fractions fractionated by ethanol/water solution.

Fig. S1 Yield of lignin fractions fractionated by ethanol/water solution.

Table S1

Ethanol ratio		Mw	Mn	Mw/Mn
95%	dissolved	2955	1522	1.94
	undissolved	27333	13205	2.07
75%	dissolved	6428	2738	2.35
	undissolved	38689	15987	2.42
50%	dissolved	3228	2517	1.28
	undissolved	30198	7296	4.14

Fig. S1

